

INTERNATIONAL STANDARD

**Coaxial communication cables –
Part 1-201: Environmental test methods – Test for cold bend performance of
cable**

IECNORM.COM : Click to view the full PDF of IEC 61196-1-201:2009



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2009 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch
Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00

IECNORM.COM : Click to view the full PDF of IEC 61196-1-201:2009



IEC 61196-1-201

Edition 1.0 2009-02

INTERNATIONAL STANDARD

**Coaxial communication cables –
Part 1-201: Environmental test methods – Test for cold bend performance of
cable**

IECNORM.COM : Click to view the full PDF of IEC 61196-1-201:2009

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

H

ICS 33.120.10

ISBN 978-2-88910-441-3

CONTENTS

| | |
|---|---|
| FOREWORD..... | 3 |
| 1 Scope..... | 5 |
| 2 Normative references | 5 |
| 3 Terms and definitions | 5 |
| 4 Test for cold bend performance – Method A | 5 |
| 4.1 Principle..... | 5 |
| 4.2 Test equipment | 5 |
| 4.3 Test specimen..... | 5 |
| 4.4 Test method | 6 |
| 4.5 Inspection | 6 |
| 4.6 Requirement..... | 7 |
| 5 Test for cold bend performance – Method B | 7 |
| 5.1 Principle..... | 7 |
| 5.2 Preparation of test specimen | 7 |
| 5.3 Procedure | 7 |
| 5.4 Requirement..... | 7 |
| 6 Test for cold bend performance – Method C | 7 |
| 6.1 Principle..... | 7 |
| 6.2 Test equipment | 7 |
| 6.3 Preparation of test specimen | 7 |
| 6.4 Test method | 8 |
| 6.5 Inspection | 8 |
| 6.6 Requirement..... | 8 |
| Figure 1 – | 6 |
| Figure 2 – | 8 |

IECNORM.COM : Click to view the full PDF of IEC 61196-1-201:2009

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COAXIAL COMMUNICATION CABLES –

**Part 1-201: Environmental test methods –
Test for cold bend performance of cable**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61196-1-201 has been prepared by subcommittee 46A: Coaxial cables, of IEC technical committee 46: Cables, wires, waveguides, r.f. connectors, r.f. and microwave passive components and accessories.

The text of this standard is based on the following documents:

| | |
|--------------|------------------|
| FDIS | Report on voting |
| 46A/921/FDIS | 46A/928/RVD |

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of IEC 61196 series, published under the general title *Coaxial communication cables*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM : Click to view the full PDF of IEC 61196-1-201:2009

COAXIAL COMMUNICATION CABLES –

Part 1-201: Environmental test methods – Test for cold bend performance of cable

1 Scope

This part of IEC 61196 applies to CATV and telecommunications cables. It specifies test methods for determining the cold bend performance of coaxial cables for use in cabled distribution telecommunications networks.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-726:1982, *International Electrotechnical Vocabulary – Transmission lines and waveguides*

IEC 60068-2-1:2007, *Environmental testing – Part 2-1: Tests: Test A - Cold*

IEC 61196-1:2005, *Coaxial communication cables – Part 1: Generic specification – General, definitions and requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-726 and IEC 61196-1 apply.

4 Test for cold bend performance – Method A

4.1 Principle

The purpose of this procedure is to provide instructions to measure the cold bend properties of flexible coaxial cables.

4.2 Test equipment

An environmental chamber having an interior chamber vertical dimension suitable to accommodate the test sample, and capable of maintaining temperatures as required in the relevant cable standard for 24 h.

Test mandrels having a diameter that is ten times the cable diameter ($10 \times$ cable diameter). For example, cable having an outside diameter of 0,75 cm, the mandrel diameter would be 7,5 cm.

4.3 Test specimen

The cable specimen should be long enough to make 4 complete wraps around the mandrel.

4.4 Test method


One end of the cable specimen shall be clamped on a mandrel whose diameter is ten (10) times the nominal outside diameter of the cable sample under test. Wrap the cable sample around the mandrel for one full turn and hold in place with a mechanical device. The test specimen shall be cooled in accordance with test Ab of IEC 60068-2-1 and maintained for a period of not less than 2 h at -40°C for PVC or -55°C for polyethylene. During the conditioning period, the unwrapped portion of the cable specimen shall be kept reasonably straight. This can be achieved by attaching a small amount of weight (1 kg to 2 kg) at the end of the cable specimen (see Figure 1).

After the conditioning period and while the cable sample is still at the test temperature, the cable specimen shall be wrapped around the mandrel for three (3) full and close turns. The mandrel shall be turned at a uniform rate of 15 ± 3 revolutions per minute during this operation.

After the cable sample has been wrapped around the mandrel, open the environmental chamber door and remove the mandrel and cable sample from the environmental chamber without disturbing the cable sample. Condition the cable sample at room temperature for 1 h maximum. This step should be performed with the cable sample wrapped on the mandrel.

4.5 Inspection

Unwind the cable sample from the mandrel and examine for cracks, flaws or other damage in the jacket material. The area of the cable sample that was clamped to the mandrel should be excluded. Any cracks, flaws or other damage are cause for failure. Additional inspection requirements may be specified in the relevant cable specification.



IEC 120/09

Figure 1 –

4.6 Requirement

The acceptance criteria for the test shall be stated in the sectional or detailed specification.

5 Test for cold bend performance – Method B

5.1 Principle

The purpose of this procedure is to provide instructions to measure the cold bend properties of cables with a braided outer conductor as defined in IEC 61196-1, 4.6.1 a), b), d), e), f) and g).

5.2 Preparation of test specimen

A sample shall be cut from the finished cable and shall have a length of at least 150 times the overall diameter of the cable if it is less than 12,5 mm and 120 times the overall diameter of the cable if it is 12,5 mm or greater. The sample shall be coiled to a diameter of not less than thirty times the overall diameter of the cable.

5.3 Procedure

The test specimen shall be cooled in accordance with test Ab of IEC 60068-2-1 and maintained at that temperature for a period of not less than 2 h or as indicated in the relevant cable specification.

At the end of this period and while still within the cold chamber, the test specimen shall be wrapped continuously around a mandrel with a diameter as indicated in the relevant cable specification and at a velocity of approximately one turn per 4 s.

For cables having a nominal diameter of less than 12,5 mm, there shall be three touching turns around the mandrel and for cables with diameters of 12,5 mm or greater, there shall be two touching turns.

The test specimen shall be stripped down and examined with normal vision or corrected vision without magnification. Additional inspection requirements may be specified in the relevant cable specification.

5.4 Requirement

There shall be no signs of physical damage to the conductors, the dielectric, the sheath or the intermediate sheath if applicable.

6 Test for cold bend performance – Method C

6.1 Principle

The purpose of this procedure is to provide instructions to measure the cold bend properties of coaxial cables with a solid tube outer conductor as defined in 61196-1, 4.6.1 c).

6.2 Test equipment

An environmental chamber capable of maintaining temperatures as required in the relevant cable standard for 24 h. Test mandrels having a minimum bend radius that is specified in the detailed specification.

6.3 Preparation of test specimen

The test specimens should be at minimum 1 m long.