
Stainless steels — Chemical composition

Aciers inoxydables — Composition chimique

STANDARDSISO.COM : Click to view the full PDF of ISO 15510:2010



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 15510:2010



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Chemical composition	1
5 Designation of comparable steels	1
Annex A (informative) Designation of the steels given in Table 1 and of comparable grades covered in various designation systems	15
Annex B (informative) Steels given in Table 1 and of comparable grades covered in various International Standards	33
Annex C (informative) Classification of grades	42
Annex D (informative) Density values for stainless steels	45
Bibliography	51

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15510 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 4, *Heat treatable and alloy steels*.

This first edition cancels and replaces ISO/TS 15510:2003, which has been technically revised.

Stainless steels — Chemical composition

1 Scope

This International Standard lists the chemical compositions of stainless steels agreed by ISO/TC 17/SC 4, mainly on the basis of a composition of the specifications in existing ISO, ASTM, EN, JIS and GB (Chinese) standards. They apply to all wrought product forms, including ingots and semi-finished material.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6929:1987, *Steel products — Definitions and classification*

3 Terms and definitions

For the purposes of this document, the terms and definition given in ISO 6929:1987 and the following apply.

3.1

stainless steel

steel with at least 10,5 % (mass fraction) Cr and maximum 1,2 % (mass fraction) C

NOTE For the classification of stainless steels according to their structure, composition and application, see Annex C.

4 Chemical composition

The chemical composition of stainless steels approved by ISO/TC 17/SC 4 is given in Table 1.

WARNING — Due to hazardous effects to health and environmental problems of lead (Pb) it is recommended to use steels with sulfur additions instead. These steels generally have comparable properties relating to machinability.

NOTE If, in special cases, for example, an ISO committee charged with the establishment or revision of a standard for a specific product or application of stainless steels sees the necessity of deviating from the specifications in Table 1, it should inform ISO/TC 17/SC 4 (Secretariat's address: FES/DIN, Postfach 10 51 45, 40042 Dusseldorf, Germany) of the reasons for this and try, before such deviations are considered, to achieve consensus for a corresponding modification to Table 1.

5 Designation of comparable steels

The steel designation according to this International Standard is based on a 10-digit code presented in 4 subgroups of digits: 4 digits-3 digits-2 digits-1 digit.

XXXX-YYY-ZZ-A

The ISO designation of each grade is based on a decision of the ISO/TC 17/SC 4 group, taking into account several commonly used existing standards and designations.

In particular, the principles below have been used for the designation.

- The first subgroup contains 4 digits and is comparable to the European designation (EN numbers): keeping the number on the right side and dropping the “1.”.
- The second subgroup contains 3 digits and refers, in most cases, to the 3 middle digits of the UNS number used by ASTM. In the case of the ISO designation, contrary to the UNS system, no letter (an S or an N in the case of stainless steels) is used as a start. This 3-digit subgroup allows reference to the obsolete AISI numbers or to the numerical part of the standard designations used in other countries, such as Japan (JIS) and China (GB).
- The third subgroup contains 2 digits. In most cases, similar principles to those used in the UNS have been adopted. Care should be taken because some differences may exist between UNS, Chinese and ISO designations (see Table 2). The principles stated in Table 2 apply within each YYY series.
- The last digit is a single letter that allows the reader to identify, in a simple way, if the grade composition corresponds exactly to that included in one or more of the 4 existing standard practices from Europe, the USA, Japan or China. If the composition is a compromise between several standards, it is then a new and genuine ISO composition. The last digit of the ISO designation is then I (see Table 3).

Table 4 gives complementary explanations for the use of the ISO numbering system through examples.

Tables A.1, A.2 and A.3 give the designations of stainless steels which are listed in other designation systems and are identical or comparable to the grades in Table 1. In Table A.1, the sequence of steels is the same as in Table 1. In Table A.2, the sequence is given in the order of the second column. In Table A.3, the sequence is given in the order of the first column.

Table B.1 gives a list where the steel grades of Table 3 are to be found in other International Standards.

NOTE 1 To compare similar grades, it is necessary to check each element before making a substitution.

NOTE 2 The line number in the steel designation is an internal reference to ease the reading of the document. It is by no means a designation and it is not for commercial purposes or as a technical reference. The number in brackets behind gives the old line number as mentioned in ISO/TS 15510:2003.

Table 1 — Internationally agreed specifications for the composition of stainless steels (applicable for cast analysis)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
a) Austenitic steel												
4318-301-53-I	X2CrNiN18-7	A25A (04)	0,030	1,00	2,00	0,045	0,015	0,10 to 0,20	16,0 to 18,5	—	6,0 to 8,0	—
4319-301-00-I	X5CrNi17-7	A24H (05)	0,07	1,00	2,00	0,045	0,030 ^b	0,10	16,0 to 18,0	—	6,0 to 8,0	—
4310-301-00-I	X10CrNi18-8	A26L (11)	0,05 to 0,15	2,00	2,00	0,045	0,030 ^b	0,10	16,0 to 19,0	0,80	6,0 to 9,5	—
4325-302-00-E	X9CrNi18-9	A27N	0,030 to 0,15	1,00	2,00	0,045	0,030	0,10	17,0 to 19,0	—	8,0 to 10,0	—
4326-302-15-I	X12CrNiSi18-9-3	A27P (46)	0,15	2,00 to 3,00	2,00	0,045	0,030	—	17,0 to 19,0	—	8,0 to 10,0	—
4307-304-03-I	X2CrNi18-9	A27B (01)	0,030	1,00	2,00	0,045	0,030 ^b	0,10	17,5 to 19,5	—	8,0 to 10,5 ^c	—
4306-304-03-I	X2CrNi19-11	A30A (02)	0,030	1,00	2,00	0,045	0,030 ^b	0,10	18,0 to 20,0	—	10,0 to 12,0 ^c	—
4311-304-53-I	X2CrNiN18-9	A27A (03)	0,030	1,00	2,00	0,045	0,030 ^b	0,12 to 0,22	17,5 to 19,5	—	8,0 to 11,0	—
4301-304-00-I	X5CrNi18-10	A28E (06)	0,07	1,00	2,00	0,045	0,030 ^b	0,10	17,5 to 19,5	—	8,0 to 10,5 ^c	—
4315-304-51-I	X5CrNiN19-9	A28F (10)	0,08	1,00	2,50	0,045	0,030	0,10 to 0,25	18,0 to 20,0	—	7,5 to 10,5	—
4948-304-09-I	X7CrNi18-9	A27L (07)	0,04 to 0,10	1,00	2,00	0,045	0,030 ^b	0,10	17,5 to 19,5	—	8,0 to 11,0	—
4818-304-15-E	X6CrNiSiN18-10	A29J	0,04 to 0,08	1,00 to 2,00	1,00	0,045	0,015 ^b	0,12 to 0,20	18,0 to 20,0	—	9,0 to 11,0	Ce: 0,03 to 0,08
4650-304-75-E	X2CrNiCu19-10	A29A	0,030	1,00	2,00	0,045	0,015	0,08	18,5 to 20,0	—	9,0 to 10,0	Cu: 1,00
4649-304-76-J	X6CrNiCu19-9-1	A28I	0,08	1,00	2,00	0,045	0,030	—	18,0 to 20,0	—	8,0 to 10,5	Cu: 0,70 to 1,30
4305-303-00-I	X10CrNiSi18-9	A27M (14)	0,12	1,00	2,00	0,060	≥ 0,15	0,10	17,0 to 19,0	—	8,0 to 10,0	Cu ^d
4625-303-23-X	X12CrNiSe18-9	A27O	0,15	1,00	2,00	0,20	0,060	—	17,0 to 19,0	—	8,0 to 10,0	Se: ≥ 0,15
4570-303-31-I	X6CrNiCuS18-9-2	A27I (44)	0,08	1,00	2,00	0,045	≥ 0,15	0,10	17,0 to 19,0	0,60	8,0 to 10,0	Cu: 1,40 to 1,80
4667-303-76-J	X12CrNiCuS18-9-3	A27Q	0,15	1,00	3,00	0,20	≥ 0,15	—	17,0 to 19,0	—	8,0 to 10,0	Cu: 1,50 to 3,5
4615-201-75-E	X3CrMnNiCu15-8-5-3 ^e	A28C	0,030	1,00	7,0 to 9,0	0,040	0,010	0,02 to 0,06	14,0 to 16,0	0,80	4,5 to 6,0	Cu: 2,0 to 4,0
4541-321-00-I	X6CrNiTi18-10	A28G (16)	0,08	1,00	2,00	0,045	0,030 ^b	—	17,0 to 19,0	—	9,0 to 12,0 ^c	Ti: 5xC to 0,70
4940-321-09-I	X7CrNiTi18-10	A28O (17)	0,04 to 0,10	1,00	2,00	0,045	0,030 ^b	—	17,0 to 19,0	—	9,0 to 12,0 ^c	Ti: 5xC to 0,80
4941-321-09-I	X6CrNiTiB18-10	A28J (18)	0,04 to 0,08	1,00	2,00	0,035	0,015	—	17,0 to 19,0	—	9,0 to 12,0	Ti: 5xC to 0,70 B: 0,001 5 to 0,005 0
4550-347-00-I	X6CrNiNb18-10	A28H (19)	0,08	1,00	2,00	0,045	0,030 ^b	—	17,0 to 19,0	—	9,0 to 12,0 ^c	Nb: 10xC to 1,00
4912-347-09-I	X7CrNiNb18-10	A28K (20)	0,04 to 0,08	1,00	2,00	0,045	0,030 ^b	—	17,0 to 19,0	—	9,0 to 12,0 ^c	Nb: 10xC to 1,00
4961-347-77-E	X8CrNiNb16-13	A29L	0,04 to 0,10	0,30 to 0,60	1,50	0,035	0,015	—	15,0 to 17,0	—	12,0 to 14,0	Nb: 10xC to 1,20

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
a) Austenitic steel												
4567-304-30-I	X3CrNiCu18-9-4	A27F (15)	0,04	1,00	2,00	0,045	0,030 ^b	0,10	17,0 to 19,0	—	8,0 to 10,5	Cu: 3,0 to 4,0
4567-304-76-I	X6CrNiCu17-8-2	A25J (45)	0,08	1,70	3,00	0,045	0,030	—	15,0 to 18,0	—	6,0 to 9,0	Cu: 1,00 to 3,0
4567-304-98-X	X6CrNiCu18-9-2	A27J	0,08	1,00	2,00	0,045	0,030	—	17,0 to 19,0	—	8,0 to 10,5	Cu: 1,00 to 3,0
4660-315-77-I	X6CrNiCuSiMo19-10-3-2	A30J	0,08	0,50 to 2,50	2,00	0,045	0,030	—	17,0 to 20,5	0,50 to 1,50	8,5 to 11,5	Cu: 1,50 to 3,5
4867-316-77-J	X40CrNiWSi15-14-3-2	A29P	0,35 to 0,45	1,50 to 2,50	0,60	0,040	0,030	—	14,0 to 16,0	—	13,0 to 15,0	W: 2,00 to 3,00
4303-305-00-I	X6CrNi18-12	A30I (08)	0,08	1,00	2,00	0,045	0,030 ^b	0,10	17,0 to 19,0	—	10,5 to 13,0	—
4828-305-09-I	X15CrNiSi20-12	A32R	0,20	1,50 to 2,50	2,00	0,045	0,030	0,10	19,0 to 21,0	—	11,0 to 13,0	—
4835-308-15-U	X7CrNiSiN11-11	A32N	0,05 to 0,10	1,40 to 2,00	0,80	0,040	0,030	0,14 to 0,20	20,0 to 22,0	—	10,0 to 12,0	Ce: 0,03 to 0,08
4884-305-00-X	X6CrNiSi18-13-4	A31H	0,08	3,0 to 5,0	2,00	0,045	0,030	—	15,0 to 20,0	—	11,5 to 15,0	—
4389-384-00-I	X3NiCr18-16	A34F (09)	0,04	1,00	2,00	0,045	0,030 ^b	0,10	15,0 to 17,0	—	17,0 to 19,0	—
4371-201-53-I	X2CrMnNiN17-7-5	A29B	0,030	1,00	6,0 to 8,0	0,045	0,015	0,15 to 0,25	16,0 to 17,5	—	3,5 to 5,5	Cu: 1,00
4372-201-00-I	X12CrMnNiN17-7-5	A29O (13)	0,15	1,00	5,5 to 7,5	0,045	0,030 ^b	0,05 to 0,25	16,0 to 18,0	—	3,5 to 5,5	—
4597-204-76-I	X8CrMnCuN17-8-3	A25L (40)	0,10	2,00	6,5 to 8,5	0,040	0,030	0,15 to 0,30	16,0 to 18,0	1,00	2,00	Cu: 2,00 to 3,5
4617-201-76-J	X6CrNiMnCu17-8-4-2	A29I	0,08	1,70	3,0 to 5,0	0,045	0,030	—	15,0 to 18,0	—	6,0 to 9,0	Cu: 1,00 to 3,0
4618-201-76-E	X9CrMnNiCu17-8-5-2	A30L	0,10	1,00	5,5 to 9,5	0,070	0,010	0,15	16,5 to 18,5	—	4,5 to 5,5	Cu: 1,00 to 2,50
4373-202-00-I	X12CrMnNiN18-9-5	A32O	0,15	1,00	7,5 to 10,0	0,060	0,030	0,15 to 0,30	17,0 to 19,0	—	4,0 to 6,0	—
4982-215-00-E	X10CrNiMoMnNbVB 15-10-1	A32P	0,06 to 0,15	0,20 to 1,00	5,50 to 7,0	0,035	0,015	0,10	14,0 to 16,0	0,80 to 1,20	9,0 to 11,0	V: 0,15 to 0,40 Nb: 0,75 to 1,25 B: 0,003 to 0,009
4369-202-91-I	X11CrNiMnN19-8-6	A33L (43)	0,07 to 0,15	0,50 to 1,00	5,0 to 7,5	0,030	0,015	0,20 to 0,30	17,5 to 19,5	—	6,5 to 8,5	—
4890-202-09-X	X53CrMnNiN21-9-4	A34V	0,48 to 0,58	0,35	8,0 to 10,0	0,040	0,030	0,35 to 0,50	20,0 to 22,0	—	3,25 to 4,5	—
4648-315-77-I	X6CrNiSiCuMo19-13-3-3-1	A33I	0,08	2,50 to 4,0	2,00	0,045	0,030	—	17,0 to 20,5	0,50 to 1,50	11,0 to 14,0	Cu: 1,50 to 3,5
4404-316-03-I	X2CrNiMo17-12-2	A31A (21)	0,030	1,00	2,00	0,045	0,030 ^b	0,10	16,5 to 18,5	2,00 to 3,00	10,0 to 13,0 ^c	—
4432-316-03-I	X2CrNiMo17-12-3	A32A (22)	0,030	1,00	2,00	0,045	0,030 ^b	0,10	16,5 to 18,5	2,50 to 3,00	10,5 to 13,0 ^c	—
4435-316-91-I	X2CrNiMo18-14-3	A35A (23)	0,030	1,00	2,00	0,045	0,030	0,10	17,0 to 19,0	2,50 to 3,00	12,5 to 15,0	—
4406-316-53-I	X2CrNiMoN17-11-2	A30B (25)	0,030	1,00	2,00	0,045	0,030 ^b	0,12 to 0,22	16,5 to 18,5	2,00 to 3,00	10,0 to 12,5 ^c	—

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
a) Austenitic steel												
4665-316-76-J	X6CrNiMoCu18-12-2-2	A32I	0,08	1,00	2,00	0,045	0,030	—	17,0 to 19,0	1,20 to 2,75	10,0 to 14,0	Cu: 1,00 to 2,50
4647-316-75-X	X2CrNiMoCu18-14-2-2	A34A	0,030	1,00	2,00	0,045	0,030	—	17,0 to 19,0	1,20 to 2,75	12,0 to 16,0	Cu: 1,00 to 2,50
4578-316-76-E	X3CrNiCuMo17-11-3-2	A30F	0,04	1,00	2,00	0,045	0,015	0,10	16,5 to 17,5	2,00 to 2,50	10,0 to 11,0	Cu: 3,0 to 3,5
4429-316-53-I	X2CrNiMoN17-12-3	A32B (26)	0,030	1,00	2,00	0,045	0,030 ^b	0,12 to 0,22	16,5 to 18,5	2,50 to 3,00	10,5 to 13,0 ^c	—
4401-316-00-I	X5CrNiMo17-12-2	A31I (30)	0,08	1,00	2,00	0,045	0,030 ^b	0,10	16,0 to 18,0	2,00 to 3,00	10,0 to 13,0	—
4436-316-00-I	X3CrNiMo17-12-3	A32F (31)	0,05	1,00	2,00	0,045	0,030 ^b	0,10	16,5 to 18,5	2,50 to 3,00	10,5 to 13,0 ^c	—
4449-316-76-E	X3CrNiMo18-12-3	A33F	0,035	1,00	2,00	0,045	0,015	0,08	17,0 to 18,2	2,25 to 2,75	11,5 to 12,5	Cu: 1,00
4910-316-77-E	X3CrNiMoBN17-13-3	A33G	0,04	0,75	2,00	0,035	0,015	0,10 to 0,18	16,0 to 18,0	2,00 to 3,0	12,0 to 14,0	B: 0,001 5 to 0,005 0
4494-316-74-J	X6CrNiMoSi17-12-3	A32K	0,08	1,00	2,00	0,045	≥ 0,10	—	16,0 to 18,0	2,00 to 3,0	10,0 to 14,0	—
4495-316-51-J	X6CrNiMoN17-12-3	A32H	0,08	1,00	2,00	0,045	0,030	0,10 to 0,22	16,0 to 18,0	2,00 to 3,0	10,0 to 14,0	—
4571-316-35-I	X6CrNiMoTi17-12-2	A31F (32)	0,08	1,00	2,00	0,045	0,030 ^b	—	16,5 to 18,5	2,00 to 2,50	10,5 to 13,5 ^c	Ti: 5xC to 0,70
4580-316-40-I	X6CrNiMoNb17-12-2	A31G (33)	0,08	1,00	2,00	0,045	0,030 ^b	—	16,5 to 18,5	2,00 to 2,50	10,5 to 13,5	Nb: 10xC to 1,00
4879-317-77-J	X30CrNiMoPB20-11-2	A33R	0,25 to 0,35	1,00	1,20	0,18 to 0,25	0,030	—	19,0 to 21,0	1,8 to 2,50	10,0 to 12,0	B: 0,001 to 0,010
4438-317-03-I	X2CrNiMo19-14-4	A37A (24)	0,030	1,00	2,00	0,045	0,030 ^b	0,10	17,5 to 20,0	3,0 to 4,0	12,0 to 15,0	—
4439-317-26-E	X2CrNiMoN17-13-5	A35B	0,030	1,00	2,00	0,045	0,015	0,12 to 0,22	16,5 to 18,5	4,0 to 5,0	12,5 to 14,5	—
4483-317-26-I	X2CrNiMoN18-15-5	A38A (28)	0,030	1,00	2,00	0,045	0,030	0,10 to 0,20	17,0 to 20,0	4,0 to 5,0	13,5 to 17,5	—
4434-317-53-I	X2CrNiMoN18-12-4	A34B (27)	0,030	1,00	2,00	0,045	0,030 ^b	0,10 to 0,20	17,5 to 20,0	3,00 to 4,0	11,0 to 14,0 ^c	—
4445-317-00-U	X6CrNiMo19-13-4	A36I	0,08	1,00	2,00	0,045	0,030	0,10	18,0 to 20,0	3,0 to 4,0	11,0 to 15,0	—
4476-317-92-X	X3CrNiMo18-16-5	A39F	0,04	1,00	2,50	0,045	0,030	—	16,0 to 19,0	4,0 to 6,0	15,0 to 17,0	—
4824-308-09-J	X20CrNiN22-11	A33Q	0,15 to 0,25	1,00	1,00 to 1,60	0,040	0,030	0,15 to 0,30	20,5 to 22,5	—	10,0 to 12,0	—
4950-309-08-E	X6CrNi23-13	A36J	0,04 to 0,08	0,70	2,00	0,035	0,015	0,10	22,0 to 24,0	—	12,0 to 15,0	—
4833-309-08-I	X18CrNi23-13	A36R	0,20	1,00	2,00	0,045	0,030	0,10	22,0 to 24,0	—	12,0 to 15,0	—
4496-309-51-J	X4CrNiMoN25-14-1	A40F	0,06	1,50	2,00	0,045	0,030	0,25 to 0,40	23,0 to 26,0	0,50 to 1,20	12,0 to 16,0	—
4335-310-02-I	X1CrNi25-21	A46A (12)	0,020	0,25	2,00	0,025	0,010	0,10	24,0 to 26,0	0,20	20,0 to 22,0	—
4951-310-08-I	X6CrNi25-20	A45L	0,04 to 0,10	0,70	2,00	0,035	0,015	0,10	24,0 to 26,0	—	19,0 to 22,0	—
4845-310-08-E	X8CrNi25-21	A46L	0,10	1,50	2,00	0,045	0,030	0,10	24,0 to 26,0	—	19,0 to 22,0	—

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
a) Austenitic steel												
4845-310-09-X	X23CrNi25-21	A46C	0,25	1,50	2,00	0,040	0,030	—	24,0 to 26,0	—	19,0 to 22,0	—
4841-314-00-E	X15CrNiSi25-21	A46R	0,20	1,50 to 2,50	2,00	0,045	0,015	0,10	24,0 to 26,0	—	19,0 to 22,0	—
4466-310-50-E	X1CrNiMoN25-22-2	A49A (29)	0,020	0,70	2,00	0,025	0,010	0,10 to 0,16	24,0 to 26,0	2,00 to 2,50	21,0 to 23,0	—
4547-312-54-I	X1CrNiMoCuN20-18-7	A45A (34)	0,020	0,70	1,00	0,035	0,015	0,18 to 0,25	19,5 to 20,5	6,0 to 7,0	17,5 to 18,5	Cu: 0,50 to 1,00
4659-312-66-I	X1CrNiMoCuNW24-22-6	A52B (41)	0,020	0,70	2,0 to 4,0	0,030	0,010	0,35 to 0,50	23,0 to 25,0	5,5 to 6,5	21,0 to 23,0	Cu: 1,00 to 2,00 W: 1,50 to 2,50
4652-326-54-I	X1CrNiMoCuN24-22-8	A54A (38)	0,020	0,50	2,0 to 4,0	0,030	0,005	0,45 to 0,55	23,0 to 25,0	7,0 to 8,0	21,0 to 23,0	Cu: 0,30 to 0,60
4565-345-65-I	X2CrNiMnMoN25-18-6-5	A54B (42)	0,030	1,00	5,0 to 7,0	0,030	0,015	0,30 to 0,60	24,0 to 26,0	4,0 to 5,0	16,0 to 19,0	Nb: 0,15
4971-314-79-I	X12CrNiCoMoWmNb21-20-20-3-3-2	A64R	0,08 to 0,16	1,00	1,00 to 2,00	0,035	0,015	0,10 to 0,20	20,0 to 22,5	2,50 to 3,5	19,0 to 21,0	Co: 18,5 to 21,0 W: 2,00 to 3,0 Nb: 0,75 to 1,25
4537-310-92-E	X1CrNiMoCuN25-25-5	A55A	0,020	0,70	2,00	0,030	0,010	0,17 to 0,25	24,0 to 26,0	4,7 to 5,7	24,0 to 27,0	Cu: 1,00 to 2,00
4656-089-04-I	X1NiCrMoCu22-20-5-2	A47A	0,020	1,00	2,00	0,040	0,030	0,10	19,0 to 21,0	4,0 to 5,0	21,0 to 23,0	Cu: 1,00 to 2,00
4539-089-04-I	X1NiCrMoCu25-20-5	A50A (35)	0,020	0,75	2,00	0,035	0,015	0,15	19,0 to 22,0	4,0 to 5,0	23,5 to 26,0	Cu: 1,00 to 2,00
4529-089-26-I	X1NiCrMoCuN25-20-7	A52A (37)	0,020	0,75	2,00	0,035	0,015	0,15 to 0,25	19,0 to 21,0	6,0 to 7,0	24,0 to 26,0	Cu: 0,50 to 1,50
4478-083-67-U	X2NiCrMoN25-21-7	A53A	0,030	1,00	2,00	0,040	0,030	0,18 to 0,25	20,0 to 22,0	6,0 to 7,0	23,5 to 25,5	Cu: 0,75
4958-088-77-E	X5NiCrAlTi31-20	A51J	0,03 to 0,08	0,70	1,50	0,015	0,010	0,030	19,0 to 22,0	—	30,0 to 32,5	Al: 0,20 to 0,50 Co: 0,50 Cu: 0,50 Nb: 0,10 Ti: 0,20 to 0,50 Al+Ti: 0,70 Ni+Co: 30,0 to 32,5
4563-080-28-I	X1NiCrMoCu31-27-4	A62A (36)	0,020	0,70	2,00	0,030	0,010	0,10	26,0 to 28,0	3,0 to 4,0	30,0 to 32,0	Cu: 0,70 to 1,50
4876-088-00-I	X8NiCrAlTi32-21	A53L (54)	0,10	1,00	1,50	0,015	0,015	—	19,0 to 23,0	—	30,0 to 34,0	Al: 0,15 to 0,60 Ti: 0,15 to 0,60 Cu: 0,70
4959-088-77-E	X8NiCrAlTi32-20	A52L	0,05 to 0,10	0,70	1,50	0,015	0,010	0,030	19,0 to 22,0	—	30,0 to 34,0	Al: 0,20 to 0,65 Co: 0,50 Cu: 0,50 Ti: 0,20 to 0,65 Ni+Co: 30,0 to 34,0

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
a) Austenitic steel												
4959-088-10-U	X7NiCrAlTi33-21	A54L	0,05 to 0,10	1,00	1,50	0,045	0,015	—	19,0 to 23,0	—	30,0 to 35,0	Cu: 0,75 Fe: ≥ 39,5 Ti: 0,15 to 0,60 Al: 0,15 to 0,60
4959-088-11-U	X8NiCrAlTi33-21	A54M	0,06 to 0,10	1,00	1,50	0,040	0,015	—	19,0 to 23,0	—	30,0 to 35,0	Cu: 0,75 Fe: ≥ 39,5 Ti: 0,15 to 0,60 Al: 0,15 to 0,60 Al+Ti: 0,85 to 1,2
4864-083-77-X	X13NiCr35-16	A51O	0,15	1,50	2,00	0,040	0,030	—	14,0 to 17,0	—	33,0 to 37,0	—
4657-080-20-U	X4NiCrCuMo35-20-4-3	A58F	0,07	1,00	2,00	0,045	0,035	—	19,0 to 21,0	2,00 to 3,00	32,0 to 38,0	Cu: 3,0 to 4,0 Nb: (8xC) to 1,00
4854-353-15-E	X6NiCrSiNCE35-25	A60J	0,04 to 0,08	1,20 to 2,00	2,00	0,040	0,015	0,12 to 0,20	24,0 to 26,0	—	34,0 to 36,0	Ce: 0,03 to 0,08
4479-089-36-U	X1NiCrMoMn34-27-6-5 ^e	A72A	0,020	0,50	4,0 to 6,0	0,025	0,010	0,30 to 0,50	26,0 to 28,0	5,0 to 6,0	33,0 to 35,0	Cu: 0,50
b) Austenitic-ferritic (duplex) steels												
4062-322-02-U	X2CrNiN22-2 ^e	D24A	0,030	1,00	2,00	0,040	0,010	0,18 to 0,26	21,5 to 24,0	0,45	1,00 to 2,80	—
4162-321-01-E	X2CrMnNiN21-5-1 ^e	D27F	0,040	1,00	4,0 to 6,0	0,040	0,015	0,20 to 0,25	21,0 to 22,0	0,10 to 0,80	1,35 to 1,70	Cu: 0,10 to 0,80
4362-323-04-I	X2CrNiN23-4	D27B (51)	0,030	1,00	2,00	0,035	0,015	0,05 to 0,20	22,0 to 24,0	0,10 to 0,60	3,5 to 5,5	Cu: 0,10 to 0,60
4424-315-00-I	X2CrNiMoSiMn19-5-3-2-2	D29A	0,030	1,40 to 2,00	1,20 to 2,00	0,035	0,030	0,05 to 0,10	18,0 to 19,0	2,50 to 3,0	4,3 to 5,2	—
4462-318-03-I	X2CrNiMoN22-5-3 ^f	D30A (52)	0,030	1,00	2,00	0,035	0,015	0,10 to 0,22	21,0 to 23,0	2,50 to 3,5	4,5 to 6,5	—
4481-312-60-J	X2CrNiMoN25-7-3	D35A	0,030	1,00	1,50	0,040	0,030	0,08 to 0,30	24,0 to 26,0	2,50 to 3,5	5,5 to 7,5	—
4507-325-20-I	X2CrNiMoCuN25-6-3	D34A (53)	0,030	0,70	2,00	0,035	0,015	0,20 to 0,30	24,0 to 26,0	3,0 to 4,0	6,0 to 8,0	Cu: 1,00 to 2,50
4507-325-50-X	X3CrNiMoCuN26-6-3-2	D35F	0,04	1,00	1,50	0,040	0,030	0,10 to 0,25	24,0 to 27,0	2,9 to 3,9	4,5 to 6,5	Cu: 1,50 to 2,50
4410-327-50-E	X2CrNiMoN25-7-4	D36A (54)	0,030	1,00	2,00	0,035	0,015	0,24 to 0,35	24,0 to 26,0	3,0 to 4,5	6,0 to 8,0	—
4501-327-60-I	X2CrNiMoCuWN25-7-4	D36B (56)	0,030	1,00	1,00	0,030	0,010	0,20 to 0,30	24,0 to 26,0	3,0 to 4,0	6,0 to 8,0	Cu: 0,50 to 1,00 W: 0,50 to 1,00
4460-312-00-I	X3CrNiMoN27-5-2	D34F (55)	0,050	1,00	2,00	0,035	0,030 ^b	0,05 to 0,20	25,0 to 28,0	1,30 to 2,00	4,5 to 6,5	—
4480-329-00-U	X6CrNiMo26-4-2	D32F	0,08	0,75	1,00	0,040	0,030	—	23,0 to 28,0	1,00 to 2,00	2,5 to 5,0	—
4477-329-06-E	X2CrNiMoN29-7-2 ^e	D38A	0,030	0,80	0,80 to 1,50	0,030	0,030	0,30 to 0,40	28,0 to 30,0	1,50 to 2,60	5,8 to 7,5	Cu: 0,80

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
b) Austenitic-ferritic (duplex) steels												
4658-327-07-U	X2CrNiMoCoN28-8-5-1 ^e	D42A	0,030	0,50	1,50	0,035	0,010	0,30 to 0,50	26,0 to 29,0	4,0 to 5,0	5,5 to 9,5	Cu: 1,00 Co: 0,50 to 2,00
4485-332-07-U	X2CrNiMoN31-8-4	D43A	0,030	0,80	1,50	0,035	0,010	0,40 to 0,60	29,0 to 33,0	3,0 to 5,0	6,0 to 9,0	Cu: 1,00
c) Ferritic steels												
4030-410-90-X	X2Cr12	F12A	0,030	1,00	1,00	0,040	0,030	—	11,0 to 13,5	—	—	—
4003-410-77-I	X2CrNi12	F12C (61)	0,030	1,00	2,00	0,040	0,015	0,030	10,5 to 12,5	—	0,30 to 1,10	—
4720-409-00-I	X2CrTi12 ^j	F12B (62)	0,030	1,00	1,00	0,040	0,030 ^b	0,030	10,5 to 12,5	—	0,50	Ti: 6x(C+N) to 0,65
4516-409-75-I	X6CrNiTi12	F13F (64)	0,08	1,00	2,00	0,040	0,015	0,030	10,5 to 12,5	—	0,50 to 1,50	Ti: 0,05 to 0,35
4000-410-08-I	X6Cr13	F13G (65)	0,08	1,00	1,00	0,040	0,030 ^b	—	11,5 to 14,0	—	0,75	—
4002-405-00-I	X6CrAl13	F13H (66)	0,08	1,00	1,00	0,040	0,030 ^b	—	11,5 to 14,0	—	—	Al: 0,10 to 0,30
4724-405-77-I	X10CrAlSi13	F13L	0,12	0,70 to 1,40	1,00	0,040	0,015	—	12,0 to 14,0	—	1,00	Al: 0,70 to 1,20
4012-429-00-X	X10Cr15	F15L	0,12	1,00	1,00	0,040	0,030	—	14,0 to 16,0	—	—	—
4595-429-71-I	X1CrNb15	F15A	0,020	1,00	1,00	0,035	0,015	0,020	14,0 to 16,0	—	—	Nb: 0,20 to 0,60
4589-429-70-E	X5CrNiMoTi15-2	F17H	0,08	1,00	1,00	0,040	0,015	—	13,5 to 15,5	0,2 to 1,2	1,00 to 2,50	Ti: 0,30 to 0,50
4016-430-00-I	X6Cr17	F17I (67)	0,08 ^g	1,00	1,00	0,040	0,030 ^b	—	16,0 to 18,0	—	—	—
4004-430-20-I	X7CrSi17	F17L (68)	0,09	1,50	1,50	0,040	≥ 0,15	—	16,0 to 18,0	0,60	—	—
4520-430-70-I	X2CrTi17	F17A	0,025	0,50	0,50	0,040	0,015	0,015	16,0 to 18,0	—	—	Ti: 8x(C+N) to 0,60 ^h
4664-430-75-J	X2CrCuTi18	F18A	0,025	1,00	1,00	0,040	0,030	0,025	16,0 to 20,0	—	—	Ti: 8x(C+N) to 0,80 ^h Cu: 0,30 to 0,80
4509-439-40-X	X2CrTiNb18	F18B	0,030	1,00	1,00	0,040	0,015	—	17,5 to 18,5	—	—	Ti: 0,10 to 0,60 Nb: 0,30 + 3xC to 1,00
4510-430-35-I	X3CrTi17	F17F (70)	0,05	1,00	1,00	0,040	0,030 ^b	0,030	16,0 to 19,0	—	—	Ti: 0,15 to 0,75 ^h
4511-430-71-I	X3CrNb17	F17G (73)	0,05	1,00	1,00	0,040	0,015	0,030	16,0 to 18,0	—	—	Nb: 12xC to 1,00
4742-430-77-I	X10CrAlSi18	F18N	0,12	0,70 to 1,40	1,00	0,040	0,015	—	17,0 to 19,0	—	1,00	Al: 0,70 to 1,20
4017-430-91-E	X6CrNi17-1	F18H	0,08	1,00	1,00	0,040	0,015	—	16,0 to 18,0	—	1,20 to 1,60	—

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
c) Ferritic steels												
4113-434-00-I	X6CrMo17-1	F18I (69)	0,08	1,00	1,00	0,040	0,030 ^b	—	16,0 to 18,0	0,75 to 1,40	—	—
4513-436-00-J	X2CrMoNbTi18-1	F19A	0,025	1,00	1,00	0,040	0,030	0,025	16,0 to 19,0	0,75 to 1,50 to 0,80	—	Ti+Nb+Zr: 8x(C+N) to 0,80
4609-436-77-J	X2CrMo19	F19B	0,025	1,00	1,00	0,040	0,030	0,025	17,0 to 20,0	0,40 to 0,80	—	Ti+Nb+Zr: 8x(C+N) to 0,80
4526-436-00-I	X6CrMoNb17-1	F18J (71)	0,08	1,00	1,00	0,040	0,015	0,040	16,0 to 18,0	0,80 to 1,40	—	Nb: 5xC to 1,00
4521-444-00-I	X2CrMoTi18-2	F20A (72)	0,025	1,00	1,00	0,040	0,015	0,030	17,0 to 20,0	1,75 to 2,50	—	Ti: $\geq 4x(C+N)$ and $0,15 \leq Ti \leq 0,75^h$
4523-182-35-I	X2CrMoTiS18-2	F20B (74)	0,030	1,00	0,50	0,040	0,15 to 0,35	—	17,5 to 19,0	2,00 to 2,50	—	Ti: 0,30 to 0,80 (C + N) $\leq$ 0,040
4621-445-00-E	X2CrNbCu21	F21A	0,030	1,00	1,00	0,040	0,015	0,030	20, 0 to 21,5	—	—	Nb: 0,20 to 1,00 Cu: 0,10 to 1,00
4764-442-72-J	X8CrAl19-3	F19N	0,10	1,50	1,00	0,040	0,030	—	17,0 to 21,0	—	—	Al: 2,00 to 4,0
4128-445-92-J	X2CrMo23-1	F24A	0,025	1,00	1,00	0,040	0,030	0,025	21,0 to 24, 0	0,70 to 1,50	—	—
4129-445-92-J	X2CrMo23-2	F25A	0,025	1,00	1,00	0,040	0,030	0,025	21,0 to 24,0	1,50 to 2,50	—	—
4762-445-72-I	X10CrAlSi25	F25N	0,12	0,70 to 1,40	1,00	0,040	0,015	—	23,0 to 26,0	—	1,00	Al: 1,20 to 1,70
4749-446-00-I	X15CrN26	F26R	0,20	1,00	1,00	0,040	0,030	0,15 to 0,25	24,0 to 28,0	—	1,00	—
4131-446-92-C	X1CrMo26-1	F27A	0,010	0,40	0,40	0,030	0,020	0,015	25,0 to 27,5	0,75 to 1,50	—	—
4750-446-60-U	X2CrMoNi27-4-2	F33A	0,030	1,00	1,00	0,040	0,030	0,040	25,0 to 28,0	3,0 to 4,0	1,00 to 3,5	(Ti + Nb): 0,20 + 6 x (C+N) to 1,00
4135-447-92-C	X1CrMo30-2	F32A	0,010	0,40	0,40	0,030	0,020	0,015	28,5 to 32,0	1,50 to 2,50	—	—
d) Martensitic steels												
4006-410-00-I	X12Cr13	M13B (82)	0,08 to 0,15	1,00	1,50	0,040	0,030 ^b	—	11,5 to 13,5	—	0,75	—
4024-410-09-E	X15Cr13	M13F	0,12 to 0,17	1,00	1,00	0,040	0,015	—	12,0 to 14,0	—	—	—
4119-410-92-C	X13CrMo13	M13G	0,08 to 0,18	0,60	1,00	0,040	0,030	—	11,5 to 14,0	0,30 to 0,60	—	—

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
d) Martensitic steels												
4642-416-72-J	X13CrPb13	M13A	0,15	1,00	1,00	0,040	0,030	—	11,5 to 13,5	—	—	Pb: 0,05 to 0,30
4005-416-00-I	X12CrS13	M13C (83)	0,08 to 0,15	1,00	1,50	0,040	≥ 0,15	—	12,0 to 14,0	0,60	—	—
4021-420-00-I	X20Cr13	M13I (84)	0,16 to 0,25	1,00	1,50	0,040	0,030 ^b	—	12,0 to 14,0	—	—	—
4916-600-77-J	X18CrMnMoNbVN12	M12G	0,15 to 0,20	0,50	0,50 to 1,00	0,040	0,030	0,05 to 0,10	10,0 to 13,0	0,30 to 0,90	0,60	Nb: 0,20 to 0,60 V: 0,10 to 0,40
4929-422-00-I	X23CrMoWmMnNiV12-1-1	M13J	0,20 to 0,25	0,50	0,50 to 1,00	0,040	0,025	—	11,0 to 12,5	0,75 to 1,25	0,50 to 1,00	V: 0,20 to 0,30 W: 0,75 to 1,25
4923-422-77-E	X22CrMoV12-1	M13H	0,18 to 0,24	0,50	0,40 to 0,90	0,025	0,015	—	11,0 to 12,5	0,8 to 1,2	0,30 to 0,80	V: 0,25 to 0,35
4028-420-00-I	X30Cr13	M13M (85)	0,26 to 0,35	1,00	1,50	0,040	0,030 ^b	—	12,0 to 14,0	—	—	—
4029-420-20-I	X33CrS13	M13N	0,25 to 0,40	1,00	1,50	0,060	≥ 0,15	—	12,0 to 14,0	0,60	0,60	—
4643-420-72-J	X33CrPb13	M13O	0,26 to 0,40	1,00	1,00	0,040	0,030	—	12,0 to 14,0	—	—	Pb: 0,05 to 0,30
4031-420-00-I	X39Cr13	M13P (86)	0,36 to 0,42	1,00	1,00	0,040	0,030 ^b	—	12,5 to 14,5	—	—	—
4419-420-97-E	X38CrMo14	M14P	0,36 to 0,42	1,00	1,00	0,040	0,015	—	13,0 to 14,5	0,60 to 1,00	—	—
4123-431-77-E	X40CrMoVN16-2	M18T	0,35 to 0,50	1,00	1,00	0,040	0,015	0,10 to 0,30	14,0 to 16,0	1,00 to 2,50	0,50	V: 1,50
4034-420-00-I	X46Cr13	M13Q (87)	0,43 to 0,50	1,00	1,00	0,040	0,030 ^b	—	12,5 to 14,5	—	—	—
4035-420-74-E	X46CrS13	M13R	0,43 to 0,50	1,00	2,00	0,040	0,15 to 0,35	—	12,5 to 14,0	—	—	—
4038-420-00-I	X52Cr13	M13U (88)	0,48 to 0,55	1,00	1,00	0,040	0,030 ^b	—	12,5 to 14,5	—	—	—
4110-420-69-E	X55CrMo14	M14U	0,48 to 0,60	1,00	1,00	0,040	0,015	—	13,0 to 15,0	0,50 to 0,80	—	V: 0,15
4039-420-09-I	X60Cr13	M13V (89)	0,56 to 0,65	1,00	1,00	0,040	0,030 ^b	—	12,5 to 14,5	—	—	—
4313-415-00-I	X3CrNiMo13-4	M17A (81)	0,05	0,70	0,50 to 1,00	0,040	0,015	—	12,0 to 14,0	0,30 to 1,00	3,5 to 4,5	—
4415-415-92-E	X2CrNiMoV13-5-2	M20A	0,030	0,50	0,50	0,040	0,015	—	11,5 to 13,5	1,50 to 2,50	4,5 to 6,5	Ti: 0,010 V: 0,10 to 0,50
4116-420-77-E	X50CrMoV15	M15U	0,45 to 0,55	1,00	1,00	0,040	0,015	—	14,0 to 15,0	0,50 to 0,80	—	V: 0,10 to 0,20
4057-431-00-X	X17CrNi16-2	M18G (91)	0,12 to 0,22	1,00	1,50	0,040	0,030	—	15,0 to 17,0	—	1,50 to 2,50	—
4058-429-99-J	X33Cr16	M16O	0,25 to 0,40	1,00	1,00	0,040	0,030	—	15,0 to 17,0	—	—	—
4418-431-77-E	X4CrNiMo16-5-1	M22A	0,06	0,70	1,50	0,040	0,015	≥ 0,020	15,0 to 17,0	0,80 to 1,50	4,0 to 6,0	—

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
d) Martensitic steels												
4019-430-20-I	X14CrS17	M17F (90)	0,10 to 0,17	1,00	1,50	0,040	≥ 0,15	—	16,0 to 18,0	0,60	—	—
4122-434-09-I	X39CrMo17-1	M18R (92)	0,33 to 0,45	1,00	1,50	0,040	0,015	—	15,5 to 17,5	0,80 to 1,30	1,00	—
4040-440-02-X	X68Cr17	M17U	0,60 to 0,75	1,00	1,00	0,040	0,030	—	16,0 to 18,0	0,75	0,60	—
4041-440-03-X	X85Cr17	M17V	0,75 to 0,95	1,00	1,00	0,040	0,030	—	16,0 to 18,0	0,75	0,60	—
4023-440-04-I	X110Cr17	M17W	0,95 to 1,20	1,00	1,00	0,040	0,030	—	16,0 to 18,0	0,75	0,60	—
4025-440-74-X	X110CrS17	M17Z	0,95 to 1,20	1,00	1,25	0,060	≥ 0,15	—	16,0 to 18,0	0,75	0,60	—
4766-440-77-X	X80CrSiNi20-2	M20U	0,75 to 0,85	1,75 to 2,25	0,20 to 0,60	0,030	0,030	—	19,0 to 20,50	—	1,15 to 1,65	—
e) Precipitation-hardening steels												
4594-155-92-E	X5CrNiMoCuNb14-5	P19I	0,07	0,70	1,00	0,040	0,015	—	13,0 to 15,0	1,20 to 2,00	5,0 to 6,0	Cu: 1,20 to 2,00 Nb: 0,15 to 0,60
4542-174-00-I	X5CrNiCuNb16-4	P20I (101)	0,07	1,00	1,50	0,040	0,030 ^b	—	15,0 to 17,0	0,60	3,0 to 5,0	Cu: 3,0 to 5,0 Nb: 0,15 to 0,45
4568-177-00-I	X7CrNiAl17-7	P24L (102)	0,09	1,00	1,00	0,040	0,015	—	16,0 to 18,0	—	6,5 to 7,8 ^l	Al: 0,70 to 1,50
4530-455-77-E	X1CrNiMoAlTi12-9-2	P23A	0,015	0,10	0,10	0,010	0,005	0,01	11,5 to 12,5	1,85 to 2,15	8,5 to 9,5	Ti: 0,28 to 0,37 Al: 0,60 to 0,80
4596-455-77-E	X1CrNiMoAlTi12-10-2	P24A	0,015	0,10	0,10	0,010	0,005	0,02	11,5 to 12,5	1,85 to 2,15	9,2 to 10,2	Ti: 0,28 to 0,40 Al: 0,80 to 1,10
4532-157-00-I	X8CrNiMoAl15-7-2	P24M (103)	0,10	1,00	1,20	0,040	0,015	—	14,0 to 16,0	2,00 to 3,00	6,5 to 7,8	Al: 0,75 to 1,50
4534-138-00-X	X3CrNiMoAl13-8-3	P24H	0,05	0,10	0,20	0,010	0,008	0,010	12,3 to 13,2	2,00 to 3,00	7,5 to 8,5	Al: 0,90 to 1,35
4645-469-10-U	X2CrNiMoCuAlTi12-9-4-3 ^e	P25A	0,030	0,70	1,00	0,030	0,015	—	11,0 to 13,0	3,5 to 5,0	8,0 to 10,0	Al: 0,15 to 0,50 Cu: 1,50 to 3,5 Ti: 0,50 to 1,20
4457-350-00-X	X9CrNiMoNi17-5-3	P25M	0,07 to 0,11	0,50	0,50 to 1,25	0,040	0,030	0,07 to 0,13	16,0 to 17,0	2,5 to 3,2	4,0 to 5,0	—
4980-662-86-X	X6NiCrTiMoVB25-15-2	P42J	0,08	1,00	2,00	0,040	0,030	—	13,5 to 16,0	1,90 to 1,50	24,0 to 27,0	Ti: 1,90 to 2,35 Al: 0,35 V: 0,10 to 0,50 B: 0,001 to 0,010
4644-662-20-U	X4NiCrMoTiMnSiB26-14-3-2	P43J	0,08	0,40 to 1,00	0,40 to 1,00	0,040	0,030	—	12,0 to 15,0	2,0 to 3,5	24,0 to 28,0	Ti: 1,80 to 2,10 Al: 0,35 B: 0,001 to 0,010

Table 1 (continued)

Steel designation			% (mass fraction) ^a									
ISO number	ISO name	Line (old)	C	Si	Mn	P	S	N	Cr	Mo	Ni	Others
a	Maximum values unless indicated otherwise.											
b	Particular ranges of sulfur mass fraction may provide improvement of particular properties. For machinability, a controlled sulfur mass fraction of 0,015 % to 0,030 % is recommended. For weldability, a controlled sulfur mass fraction of 0,008 % to 0,020 % may be beneficial. For polishability, a controlled sulfur mass fraction of 0,015 % maximum is recommended.											
c	Where, for special reasons (e.g., hot workability or low magnetic permeability), it is necessary to minimize the ferrite mass fraction, the maximum nickel mass fraction may be increased by the following amounts: — by 0,50 % for steels in lines (old) 01, 06 and 32; — by 1,00 % for steels in lines (old) 02, 16, 17, 19, 20, 25, 26, 27 and 31; — by 1,50 % for steels in lines (old) 21 and 22.											
d	Copper may be added up to 1,00 %. If it is added, it must be reported in the inspection document, provided such a document has been ordered.											
e	Patented grade.											
f	For special applications, the lower limits of N, Cr and Mo can be limited to 0,14 %, 22,0 % and 3,0 %.											
g	For certain applications, e.g. weldability or high-strength wire, a maximum of 0,12 % C may be agreed upon.											
h	Stabilization may be obtained by the use of titanium or niobium or zirconium. The equivalence shall be the following: Nb [% (mass fraction)] = Zr [% (mass fraction)] = 7/4 Ti [% (mass fraction)].											
i	By special agreement, the steel, when intended for cold deformation, may also be ordered with 7,00 % to 8,30 % Ni.											
j	S40900 (4720-409-00) has been replaced by S40971, S40978 and S40979. Unless otherwise specified in the ordering information, an order specifying S40900 shall be satisfied by any one of S40971 [with Ti: 6x(C+N) to 0,50, Nb: ≤ 0,17], S40978 [with 8x(C+N) ≤ Ti: 0,15 to 0,50 and Nb: ≤ 0,10] or S40979 [with 0,08 + 8x(C+N) ≤ (Nb +Ti) ≤ 0,75 and 0,05 ≤ Ti] at the option of the seller. Material meeting the requirements of S40971, S40978 and S40979 may, at the option of the manufacturer, be certified as S40900.											

Table 2 — Principles used for allocation of the last two digits of the ISO steel designation according to this International Standard

Last two digits	Allocation
03, 90	Low carbon
91	Low carbon, increased nickel
25, 50, 54, 92	Low carbon, increased molybdenum
93	Low carbon, increased nickel and molybdenum
53, 50, 54, 94	Low carbon, increased nitrogen
95	Low carbon, increased molybdenum and nitrogen
00, 96	Normal carbon
97	Normal carbon, increased molybdenum
51, 98	Normal carbon, increased nitrogen
09	High carbon
35, 36, 70	Titanium addition
40, 41, 42, 71	Niobium (columbium) addition
23, 72	Addition of cerium or aluminium or silicon or selenium or lead
73	High carbon, increased nickel
20, 74	Sulfur addition
75	Low carbon, copper addition
76	Normal carbon, copper addition
77	Miscellaneous
78	Miscellaneous
79	Miscellaneous

Table 3 — Rules for allocating the last letter of the ISO steel designation according to this International Standard

Last digit 'A'	Allocation
E	Grade origin is a standard in Europe and grade is defined by the "Stahl-Eisen-Liste"
U	Grade origin is a standard in the United States of America and grade is defined by an existing UNS number
J	Grade origin is a standard in Japan (appears in a JIS standard)
C	Grade origin is a standard in China (appears in a Chinese National Standard)
I	First definition of the composition in this International Standard
X	Grade composition fulfils 2 or more of the above E, U, J, C criteria

Table 4 — Examples of ISO steel designations according to this International Standard

ISO designation	Explanations
4307-304-03-I	The designation ends with I: composition is defined by this International Standard: — this is a “compromise” composition between existing standards; — the composition defined in Europe as EN 1.4307 and in the US as S30403 are considered as close matches to this ISO grade. NOTE As stated in Table A.3: standardized compositions that are close matches also exist in the JIS standard (grade SUS304L) and in Chinese National Standard (grade S30403). Ending of the designation with 03 refers to the low carbon content.
4325-302-00-E	The designation ends with E: grade origin is a European standard: — the ISO composition is identical to the existing standardized European grade: 1.4325; — the composition defined by UNS grade S30200 is a close match to this ISO grade. NOTE As stated in Table A.3: standardized compositions that are close matches also exist in the JIS standard (grade SUS302) and in the Chinese standard (Chinese grade S30210). The steel composition should also be checked with former AISI 302, now designated as S30200 under the UNS system.
4959-088-10-U	The designation ends with U: grade origin is a standard of the USA: — the ISO composition is identical to the existing standardized grade UNS N08810; — the composition defined in Europe as EN 1.4959 is a close match to this ISO grade. NOTE As stated in Table A.3: standardized compositions that are close matches also exist in the JIS standard (grade NCF800H). Grade UNS N08810 is listed in Table A.3.
4494-316-74-J	The designation ends with J: grade origin is a Japanese standard : — the ISO composition is identical to the existing SUS316F grade standardized by JIS as shown in Table A.3; — the composition defined in Europe as EN 1.4494 is a close match to this ISO grade. NOTE Ending of the designation with 20 refers to the addition of sulfur.
4040-440-02-X	The designation ends with X: grade origin is a standard of China and of Japan: — the ISO composition is identical to the existing Chinese standardized grade S44070 listed in GB/T20878 and is identical to Japanese grade SUS440A listed in a JIS standard; — the composition defined in Europe as 1.4040 in the “Stahl-Eisen-Liste” and is identical to the ISO grade; — composition defined in UNS as S44002 has a wider match to this ISO grade. NOTE Ending of the designation with 02 refers to a high carbon level.
4665-316-76-J	The designation ends with J: grade origin is a Japanese standard: — the ISO composition is identical to the existing SUS316J1 grade standardized by JIS; — the composition is introduced in the “Stahl-Eisen-Liste” as grade 1.4665; — ending with the digits 76 refers to the addition of Cu compared to the general 316 grades.

Annex A

(informative)

Designation of the steels given in Table 1 and of comparable grades covered in various designation systems

Table A.1 — Designations of the steels given in Table 1 and of comparable grades covered in various designation systems

ISO number	ISO name	Steel designations according to ^a							
		Line (old)	ASTM A959/UNS ^b	EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ISC ^e	
			I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
a) Austenitic steels									
4318-301-53-I	X2CrNiN18-7	A25A (04)	S30153	W	1.4318	N	SUS301L	W	S30153
4319-301-00-I	X5CrNi17-7	A24H (05)	S30100	W	1.4319	I	SUS301	W	S30110
4310-301-00-I	X10CrNi18-8	A26L (11)	S30100	W	1.4310	N	—	—	S30110
4325-302-00-E	X9CrNi18-9	A27N	S30200	W	1.4325	I	SUS302	W	S30210
4326-302-15-I	X12CrNiSi18-9-3	A27P (46)	S30215	W	(1.4326)	I	SUS302B	I	S30240
4307-304-03-I	X2CrNi18-9	A27B (01)	S30403	W	1.4307	N	SUS304L	W	S30403
4306-304-03-I	X2CrNi19-11	A30A (02)	S30403	W	1.4306	N	SUS304L	W	S30403
4311-304-53-I	X2CrNiN18-9	A27A (03)	S30453	W	1.4311	N	SUS304LN	W	S30453
4301-304-00-I	X5CrNi18-10	A28E (06)	S30400	W	1.4301	I	SUS304	W	S30408
4315-304-51-I	X5CrNiN19-9	A28F (10)	S30451	N	1.4315	W	SUS304N1	W	S30458
4948-304-09-I	X7CrNi18-9	A27L (07)	S30409	W	1.4948	W	SUS304H	W	S30409
4818-304-15-E	X6CrNiSiN18-9-10	A29J	S30415	W	1.4818	I	—	—	S30450
4650-304-75-E	X2CrNiCu19-10	A29A	—	—	1.4650	I	SUS304L	W	S30403
4649-304-76-J	X6CrNiCu19-9-1	A28I	—	—	(1.4649)	I	SUS304Cu	I	S30488
4305-303-00-I	X10CrNiSi18-9	A27M (14)	S30300	W	1.4305	W	SUS303	W	S30317
4625-303-23-X	X12CrNiSe18-9	A27O	S30323	I	(1.4625)	I	SUS303Se	I	S30327
4570-303-31-I	X6CrNiCuSi18-9-2	A27I (44)	S30331	I	1.4570	N	—	—	—
4667-303-76-J	X12CrNiCuSi18-9-3	A27Q	—	—	(1.4667)	I	SUS303Cu	I	—
4615-201-75-E	X3CrMnNiCu15-8-5-3	A28C	—	—	1.4615	I	—	—	—
4541-321-00-I	X6CrNiTi18-10	A28G (16)	S32100	W	1.4541	I	SUS321	W	S32168
4940-321-09-I	X7CrNiTi18-10	A28O (17)	S32109	W	1.4940	N	SUS321H	W	S32169
4941-321-09-I	X6CrNiTiB18-10	A28J (18)	S32109	W	1.4941	W	—	—	S32169
4550-347-00-I	X6CrNiNb18-10	A28H (19)	S34700	I	1.4550	N	SUS347	W	S34778
4912-347-09-I	X7CrNiNb18-10	A28K (20)	S34709	W	1.4912	N	SUS347H	W	S34779
4961-347-77-E	X8CrNiNb16-13	A29L	—	—	1.4961	I	—	—	—
4567-304-30-I	X3CrNiCu18-9-4	A27F (15)	S30430	W	1.4567	N	SUSXM7	W	S30488
4567-304-76-I	X6CrNiCu17-8-2	A25J (45)	—	—	1.4567	W	SUS304J1	I	S30480
4567-304-98-X	X6CrNiCu18-9-2	A27J	—	—	1.4567	W	SUS304J3	I	S30480
4660-315-77-I	X6CrNiCuSiMo19-10-3-2	A30J	—	—	(1.4660)	I	SUS315J1	N	—

Table A.1 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
a) Austenitic steels										
4867-316-77-J	X40CrNiWSi15-14-3-2	A29P	—	—	(1.4867)	I	SUH31	I	—	—
4303-305-00-I	X6CrNi18-12	A30I (08)	S30500	W	1.4303	N	SUS305	W	S30510	W
4828-305-09-I	X15CrNiSi20-12	A32R	—	—	1.4828	N	—	—	—	—
4835-308-15-U	X7CrNiSiNCe21-11	A32N	S30815	I	1.4835	N	—	—	—	—
4884-305-00-X	X6CrNiSi18-13-4	A31H	S30500	W	(1.4884)	I	SUSXM15J1	I	S38148	I
4389-384-00-I	X3NiCr18-16	A34F (09)	S38400	W	(1.4389)	I	SUS384	W	S38408	W
4371-201-53-I	X2CrMnNiN17-7-5	A29B	S20153	N	1.4371	N	—	—	—	—
4372-201-00-I	X12CrMnNiN17-7-5	A29O (13)	S20100	N	1.4372	N	SUS201	W	S35350	N
4597-204-76-I	X8CrMnCuN17-8-3	A25L (40)	—	—	1.4597	N	—	—	—	—
4617-201-76-J	X6CrNiMnCu17-8-4-2	A29I	—	—	(1.4617)	I	SUS304J2	I	—	—
4618-201-76-E	X9CrMnNiCu17-8-5-2	A30L	—	—	1.4618	I	—	—	—	—
4373-202-00-I	X12CrMnNiN18-9-5	A32O	S20200	W	1.4373	N	SUS202	W	S35450	N
4982-215-00-E	X10CrNiMoMnNbVB 15-10-1	A32P	S21500	N	1.4982	I	—	—	—	—
4369-202-91-I	X11CrNiMnN19-8-6	A33L (43)	—	—	1.4369	I	—	—	—	—
4890-202-09-X	X53CrMnNiN21-9-4	A34V	—	—	(1.4890)	I	SUH35	I	S35650	I
4648-315-77-I	X6CrNiSiCuMo19-13-3-3-1	A33I	—	—	(1.4648)	I	SUS315J2	W	—	—
4404-316-03-I	X2CrNiMo17-12-2	A31A (21)	S31603	W	1.4404	N	SUS316L	W	S31603	N
4432-316-03-I	X2CrNiMo17-12-3	A32A (22)	S31603	W	1.4432	I	SUS316L	W	S31603	W
4435-316-91-I	X2CrNiMo18-14-3	A35A (23)	—	—	1.4435	N	SUS316L	W	S31603	W
4406-316-53-I	X2CrNiMoN17-11-2	A30B (25)	S31653	W	1.4406	N	SUS316LN	W	S31653	N
4665-316-76-J	X6CrNiMoCu18-12-2-2	A32I	—	—	(1.4665)	I	SUS316J1	I	—	—
4647-316-75-X	X2CrNiMoCu18-14-2-2	A34A	—	—	(1.4647)	I	SUS316J1L	I	S31683	I
4578-316-76-E	X3CrNiCuMo17-11-3-2	A30F	—	—	1.4578	I	—	—	—	—
4429-316-53-I	X2CrNiMoN17-12-3	A32B (26)	S31653	W	1.4429	N	SUS316LN	W	S31653	N
4401-316-00-I	X5CrNiMo17-12-2	A31I (30)	S31600	W	1.4401	N	SUS316	W	S31608	N
4436-316-00-I	X3CrNiMo17-12-3	A32F (31)	S31600	W	1.4436	I	SUS316	W	S31608	W
4449-316-76-E	X3CrNiMo18-12-3	A33F	—	—	1.4449	I	—	—	—	—
4910-316-77-E	X3CrNiMoBN17-13-3	A33G	—	—	1.4910	I	—	—	—	—
4494-316-74-J	X6CrNiMoS17-12-3	A32K	—	—	(1.4494)	I	SUS316F	I	—	—
4495-316-51-J	X6CrNiMoN17-12-3	A32H	S31651	N	(1.4495)	I	SUS316N	I	S31658	N
4571-316-35-I	X6CrNiMoTi17-12-2	A31F (32)	S31635	W	1.4571	N	SUS316Ti	W	S31668	W
4580-316-40-I	X6CrNiMoNb17-12-2	A31G (33)	S31640	W	1.4580	N	—	—	S31678	W
4879-317-77-J	X30CrNiMoPB20-11-2	A33R	—	—	(1.4879)	I	SUH38	I	—	—
4438-317-03-I	X2CrNiMo19-14-4	A37A (24)	S31703	W	1.4438	W	SUS317L	W	S31703	W
4439-317-26-E	X2CrNiMoN17-13-5	A35B	S31726	N	1.4439	I	—	—	S31723	W
4483-317-26-I	X2CrNiMoN18-15-5	A38A (28)	S31726	W	(1.4483)	I	—	—	S31723	N
4434-317-53-I	X2CrNiMoN18-12-4	A34B (27)	S31753	W	1.4434	N	SUS317LN	W	S31753	W
4445-317-00-U	X6CrNiMo19-13-4	A36I	S31700	I	(1.4445)	I	SUS317	W	S31708	N
4476-317-92-X	X3CrNiMo18-16-5	A39F	—	—	(1.4476)	I	SUS317J1	I	S31794	I

Table A.1 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
a) Austenitic steels										
4824-308-09-J	X20CrNiN22-11	A33Q	—	—	(1.4824)	I	SUH37	I	S30850	W
4950-309-08-E	X6CrNi23-13	A36J	S30908	W	1.4950	I	SUS309S	W	S30908	W
4833-309-08-I	X18CrNi23-13	A36R	S30908	W	1.4833	N	SUH309	W	S30908	W
4496-309-51-J	X4CrNiMoN25-14-1	A40F	—	—	(1.4496)	I	SUS317J2	I	—	—
4335-310-02-I	X1CrNi25-21	A46A (12)	S31002	W	1.4335	I	—	—	—	—
4951-310-08-I	X6CrNi25-20	A45L	S31008	W	1.4951	N	SUS310S	W	S31008	W
4845-310-08-E	X8CrNi25-21	A46L	S31008	W	1.4845	I	SUS310S	W	S31008	N
4845-310-09-X	X23CrNi25-21	A46O	S31008	W	1.4845	N	SUH310	I	S31020	I
4841-314-00-E	X15CrNiSi25-21	A46R	S31400	N	1.4841	I	—	—	—	—
4466-310-50-E	X1CrNiMoN25-22-2	A49A (29)	S31050	W	1.4466	I	—	—	S31053	W
4547-312-54-I	X1CrNiMoCuN20-18-7	A45A (34)	S31254	W	1.4547	N	SUS312L	W	S31252	N
4659-312-66-I	X1CrNiMoCuNW24-22-6	A52B (41)	S31266	W	1.4659	I	—	—	—	—
4652-326-54-I	X1CrNiMoCuN24-22-8	A54A (38)	S32654	N	1.4652	I	—	—	S32652	N
4565-345-65-I	X2CrNiMnMoN25-18-6-5	A54B (42)	S34565	W	1.4565	I	—	—	S34553	N
4971-314-79-I	X12CrNiCoMoWmNnNb21-20-20-3-3-2	A64R	—	—	1.4971	N	SUH661	W	—	—
4537-310-92-E	X1CrNiMoCuN25-25-5	A55A	—	—	1.4537	I	—	—	—	—
4656-089-04-I	X1NiCrMoCu22-20-5-2	A47A	N08904	N	(1.4656)	I	—	—	S39042	N
4539-089-04-I	X1NiCrMoCu25-20-5	A50A (35)	N08904	W	1.4539	N	SUS890L	W	S39042	N
4529-089-26-I	X1NiCrMoCuN25-20-7	A52A (37)	N08926	W	1.4529	N	—	—	—	—
4478-083-67-U	X2NiCrMoN25-21-7	A53A	N08367	I	(1.4478)	I	SUS836L	W	—	—
4958-088-77-E	X5NiCrAlTi31-20	A51J	—	—	1.4958	I	—	—	—	—
4563-080-28-I	X1NiCrMoCu31-27-4	A62A (36)	N08028	W	1.4563	I	—	—	—	—
4876-088-00-I	X8NiCrAlTi32-21	A53L	N08800	W	1.4876	N	NCF800	W	—	—
4959-088-77-E	X8NiCrAlTi32-20	A52L	—	—	1.4959	I	—	—	—	—
4959-088-10-U	X7NiCrAlTi33-21	A54L	N08810	I	1.4959	N	NCF800H	N	—	—
4959-088-11-U	X8NiCrAlTi33-21	A54M	N08811	I	1.4959	W	—	—	—	—
4864-083-77-X	X13NiCr35-16	A51O	—	—	1.4864	N	SUH 330	I	S33010	I
4657-080-20-U	X4NiCrCuMo35-20-4-3	A58F	N08020	I	(1.4657)	I	—	—	—	—
4854-353-15-E	X6NiCrSiNc35-25	A60J	S35315	N	1.4854	I	—	—	—	—
4479-089-36-U	X1NiCrMoMnN34-27-6-5	A72A	N08936	I	(1.4479)	I	—	—	—	—
b) Austenitic-ferritic (duplex) steels										
4062-322-02-U	X2CrNiN22-2	D24A	S32202	I	1.4062	N	—	—	—	—
4162-321-01-E	X2CrMnNiN21-5-1	D27F	S32101	N	1.4162	I	—	—	—	—
4362-323-04-I	X2CrNiN23-4	D27B (51)	S32304	W	1.4362	I	—	—	S23043	W
4424-315-00-I	X2CrNiMoSiMnN19-5-3-2-2	D29A	S31500	N	1.4424	N	—	—	—	—
4462-318-03-I	X2CrNiMoN22-5-3	D30A (52)	S32205	N	1.4462	I	SUS329J3L	W	S22053	N
4481-312-60-J	X2CrNiMoN25-7-3	D35A	S31260	W	(1.4481)	I	SUS329J4L	I	S22583	W
4507-325-20-I	X2CrNiMoCuN25-6-3	D34A (53)	S32550	W	1.4507	I	—	—	S25554	—
4507-325-50-X	X3CrNiMoCuN26-6-3-2	D35F	S32550	I	1.4507	W	—	—	S25554	I

Table A.1 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
b) Austenitic-ferritic (duplex) steels										
4410-327-50-E	X2CrNiMoN25-7-4	D36A (54)	S32750	W	1.4410	I	—	—	S25073	W
4501-327-60-I	X2CrNiMoCuWN25-7-4	D36B (56)	S32760	I	1.4501	N	—	—	S27603	N
4460-312-00-I	X3CrNiMoN27-5-2	D34F (55)	S31200	W	1.4460	I	—	—	S22553	W
4480-329-00-U	X6CrNiMo26-4-2	D32F	S32900	I	(1.4480)	I	SUS329J1	W	—	—
4477-329-06-E	X2CrNiMoN29-7-2	D38A	S32906	N	1.4477	I	—	—	—	—
4658-327-07-U	X2CrNiMoCoN28-8-5-1	D42A	S32707	I	(1.4658)	I	—	—	—	—
4485-332-07-U	X2CrNiMoN31-8-4	D43A	S33207	U	(1.4485)	I	—	—	—	—
c) Ferritic steels										
4030-410-90-X	X2Cr12	F12A	—	—	(1.4030)	I	SUS410L	I	S11203	I
4003-410-77-I	X2CrNi12	F12C (61)	S41003	N	1.4003	N	—	—	S11213	N
4720-409-00-I	X2CrTi12	F12B (62)	S40900	W	1.4720	N	SUH409L	W	S11163	—
4516-409-75-I	X6CrNiTi12	F13F (64)	S40975	W	1.4516	N	—	—	—	—
4000-410-08-I	X6Cr13	F13G (65)	S41008	W	1.4000	N	SUS410S	N	S41008	N
4002-405-00-I	X6CrAl13	F13H (66)	S40500	W	1.4002	N	SUS405	W	S11348	N
4724-405-77-I	X10CrAlSi13	F13L	—	—	1.4724	N	—	—	—	—
4012-429-00-X	X10Cr15	F15L	S42900	I	(1.4012)	I	SUS429	I	S11510	I
4595-429-71-I	X1CrNb15	F15A	—	—	1.4595	N	—	—	—	—
4589-429-70-E	X5CrNiMoTi15-2	F17H	—	—	1.4589	I	—	—	—	—
4016-430-00-I	X6Cr17	F17I (67)	S43000	W	1.4016	I	SUS430	W	S11710	W
4004-430-20-I	X7CrS17	F17L (68)	S43020	W	(1.4004)	I	SUS430F	W	S11717	W
4520-430-70-I	X2CrTi17	F17A	—	—	1.4520	N	SUS430LX	W	—	—
4664-430-75-J	X2CrCuTi18	F18A	—	—	(1.4664)	I	SUS430J1L	I	—	—
4509-439-40-X	X2CrTiNb18	F18B	S43940	I	1.4509	N	SUS430LX	W	S11873	I
4510-430-35-I	X3CrTi17	F17F (70)	S43035	W	1.4510	N	SUS430LX	W	S11863	W
4511-430-71-I	X3CrNb17	F17G (73)	—	—	1.4511	N	SUS430LX	W	—	—
4742-430-77-I	X10CrAlSi18	F18N	—	—	1.4742	N	—	—	—	—
4017-430-91-E	X6CrNi17-1	F18H	—	—	1.4017	I	—	—	—	—
4113-434-00-I	X6CrMo17-1	F18I (69)	S43400	W	1.4113	N	SUS434	W	S11790	W
4513-436-00-J	X2CrMoNbTi18-1	F19A	S43600	W	(1.4513)	N	SUS436L	I	S11862	W
4609-436-77-J	X2CrMo19	F19B	—	—	(1.4609)	I	SUS436J1L	I	—	—
4526-436-00-I	X6CrMoNb17-1	F18J (71)	S43600	W	1.4526	N	—	—	S11770	W
4521-444-00-I	X2CrMoTi18-2	F20A (72)	S44400	W	1.4521	N	SUS444	W	S11972	W
4523-182-35-I	X2CrMoTiS18-2	F20B (74)	S18235	W	1.4523	I	—	—	—	—
4621-445-00-E	X2CrNbCu21	F21A	S44500	W	1.4621	I	—	—	—	—
4764-442-72-J	X8CrAl19-3	F19N	—	—	(1.4764)	I	SUH21	I	—	—
4128-445-92-J	X2CrMo23-1	F24A	—	—	(1.4128)	I	SUS445J1	I	—	—
4129-445-92-J	X2CrMo23-2	F25A	—	—	(1.4129)	I	SUS445J2	I	—	—
4762-445-72-I	X10CrAlSi25	F25N	—	—	1.4762	N	—	—	—	—

Table A.1 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
c) Ferritic steels										
4749-446-00-I	X15CrN26	F26R	S44600	W	1.4749	W	SUH446	W	S12550	W
4131-446-92-C	X1CrMo26-1	F27A	S44627	W	(1.4131)	I	SUSXM27	N	S12791	I
4750-446-60-U	X2CrMoNi27-4-2	F33A	S44660	I	(1.4750)	I	—	—	—	—
4135-447-92-C	X1CrMo30-2	F32A	S44700	N	(1.4135)	I	SUS447J1	N	S13091	I
d) Martensitic steels										
4006-410-00-I	X12Cr13	M13B (82)	S41000	W	1.4006	I	SUS410	W	S41010	W
4024-410-09-E	X15Cr13	M13F	—	—	1.4024	I	SUS410	W	—	—
4119-410-92-C	X13CrMo13	M13G	—	—	(1.4119)	I	SUS410J1	N	S45710	I
4642-416-72-J	X13CrPb13	M13A	—	—	(1.4642)	I	SUS410F2	I	—	—
4005-416-00-I	X12CrS13	M13C (83)	S41600	W	1.4005	N	SUS416	W	S41617	N
4021-420-00-I	X20Cr13	M13I (84)	S42000	W	1.4021	I	SUS420J1	N	S42020	N
4916-600-77-J	X18CrMnMoNbVN12	M12G	—	—	(1.4916)	I	SUH 600	I	S46250	N
4929-422-00-I	X23CrMoWMnNiV12-1-1	M13J	S42200	W	(1.4929)	I	SUH 616	N	S47220	N
4923-422-77-E	X30Cr13	M13H	—	—	1.4923	I	—	—	—	—
4028-420-00-I	X30Cr13	M13M (85)	S42000	W	1.4028	I	SUS420J2	W	S42030	N
4029-420-20-I	X33CrS13	M13N	S42020	W	1.4029	N	SUS420F	N	S42037	N
4643-420-72-J	X33CrPb13	M13O	—	—	(1.4643)	I	SUS420F2	I	—	—
4031-420-00-I	X39Cr13	M13P (86)	S42000	W	1.4031	I	—	—	S42040	W
4419-420-97-E	X38CrMo14	M14P	—	—	1.4419	I	—	—	S45830	W
4123-431-77-E	X40CrMoVN16-2	M18T	—	—	1.4123	I	—	—	—	—
4034-420-00-I	X46Cr13	M13Q (87)	S42000	W	1.4034	I	—	—	S42040	W
4035-420-74-E	X46CrS13	M13R	—	—	1.4035	I	—	—	—	—
4038-420-00-I	X52Cr13	M13U (88)	S42000	W	(1.4038)	I	—	—	—	—
4110-420-69-E	X55CrMo14	M14U	—	—	1.4110	I	—	—	—	—
4039-420-09-I	X60Cr13	M13V (89)	—	—	(1.4039)	I	—	—	—	—
4313-415-00-I	X3CrNiMo13-4	M17A (81)	S41500	W	1.4313	N	SUSF6NM	W	S41595	W
4415-415-92-E	X2CrNiMoV13-5-2	M20A	—	—	1.4415	I	—	—	—	—
4116-420-77-E	X50CrMoV15	M15U	—	—	1.4116	I	—	—	—	—
4057-431-00-X	X17CrNi16-2	M18G (91)	S43100	W	1.4057	I	SUS431	W	S43120	I
4058-429-99-J	X33Cr16	M16O	—	—	(1.4058)	I	SUS429J1	I	—	—
4418-431-77-E	X4CrNiMo16-5-1	M22A	—	—	1.4418	I	—	—	—	—
4019-430-20-I	X14CrS17	M17F (90)	S43020	W	1.4019	I	—	—	S11717	W
4122-434-09-I	X39CrMo17-1	M18R (92)	—	—	1.4122	I	—	—	—	—
4040-440-02-X	X68Cr17	M17U	S44002	W	(1.4040)	I	SUS440A	I	S44070	I
4041-440-03-X	X85Cr17	M17V	S44003	W	(1.4041)	I	SUS440B	I	S44080	I
4023-440-04-I	X110Cr17	M17W	S44004	W	(1.4023)	I	SUS440C	N	S44096	N
4025-440-74-X	X110CrS17	M17Z	—	—	(1.4025)	I	SUS440F	I	S44097	I
4766-440-77-X	X80CrSiNi20-2	M20U	—	—	(1.4766)	I	SUH4	I	S48380	I

Table A.1 (continued)

ISO number	ISO name	Steel designations according to ^a							
		Line (old)	ASTM A959/UNS ^b	EN 10088-1:2005 Number ^c	JIS ^d		GB/T20878/ISC ^e		
				I/N/W ^f		I/N/W ^f		I/N/W ^f	
e) Precipitation-hardening steels									
4594-155-92-E	X5CrNiMoCuNb14-5	P19I	—	—	1.4594	I	—	—	—
4542-174-00-I	X5CrNiCuNb16-4	P20I (101)	S17400	W	1.4542	N	SUS630	W	S51740
4568-177-00-I	X7CrNiAl17-7	P24L (102)	S17700	N	1.4568	N	SUS631	W	S51770
4530-455-77-E	X1CrNiMoAlTi12-9-2	P23A	—	—	1.4530	I	—	—	—
4596-455-77-E	X1CrNiMoAlTi12-10-2	P24A	—	—	1.4596	I	—	—	—
4532-157-00-I	X8CrNiMoAl15-7-2	P24M (103)	S15700	N	1.4532	N	—	—	S51570
4534-138-00-X	X3CrNiMoAl13-8-3	P24H	S13800	I	1.4534	N	—	—	S51380
4645-469-10-U	X2CrNiMoCu AlTi12-9-4-3	P25A	(S46910)	I	(1.4645)	I	—	—	—
4457-350-00-X	X9CrNiMoN17-5-3	P25M	(S35000)	I	(1.4457)	W	—	—	S51750
4980-662-86-X	X6NiCrTiMoVB25-15-2	P42J	(S66286)	I	1.4980	N	SUH660	I	S51525
4644-662-20-U	X4NiCrMoTiMnSiB26-14-3-2	P43J	(S66220)	I	(1.4644)	I	—	—	—
NOTE The grades given in this table are comparable to those given in Table 1. However, to compare similar grades, it is necessary to check each element before making a substitution. ^a See the sources in the Bibliography. ^b US steel listed in ASTM A959 and in UNS; if the steel number is given in brackets then the steel has only a UNS number. ^c European steel listed in EN 10088-1:2005 and in the "Stahl-Eisen-Liste"; if the steel number is given in brackets then the steel is only listed in the "Stahl-Eisen-Liste". ^d Japanese Industrial Standard. ^e Chinese steel of ISC number listed in GB/T20878. ^f I = identical steel to ISO steel grade; N = steel grade with closer match of composition, but not identical; W = wider match.									

Table A.2 — Designations of the steels given in Table 1 and of comparable grades covered in various designation systems listed according to the AISI numbers

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
a) Austenitic steels										
4657-080-20-U	X4NiCrCuMo35-20-4-3	A58F	N08020	I	(1.4657)	I	—	—	—	—
4563-080-28-I	X1NiCrMoCu31-27-4	A62A (36)	N08028	W	1.4563	I	—	—	—	—
4478-083-67-U	X2NiCrMoN25-21-7	A53A	N08367	I	(1.4478)	I	SUS836L	W	—	—
4864-083-77-X	X13NiCr35-16	A51O	—	—	1.4864	N	SUH 330	I	S33010	I
4876-088-00-I	X8NiCrAlTi32-21	A53L	N08800	W	1.4876	N	NCF800	W	—	—
4959-088-10-U	X7NiCrAlTi33-21	A54L	N08810	I	1.4959	N	NCF800H	N	—	—
4959-088-11-U	X8NiCrAlTi33-21	A54M	N08811	I	1.4959	W	—	—	—	—
4958-088-77-E	X5NiCrAlTi31-20	A51J	—	—	1.4958	I	—	—	—	—
4959-088-77-E	X8NiCrAlTi32-20	A52L	—	—	1.4959	I	—	—	—	—
4656-089-04-I	X1NiCrMoCu22-20-5-2	A47A	N08904	N	(1.4656)	I	—	—	S39042	N
4539-089-04-I	X1NiCrMoCu25-20-5	A50A (35)	N08904	W	1.4539	N	SUS890L	W	S39042	N
4529-089-26-I	X1NiCrMoCuN25-20-7	A52A (37)	N08926	W	1.4529	N	—	—	—	—
4479-089-36-U	X1NiCrMoMnN34-27-6-5	A72A	N08936	I	(1.4479)	I	—	—	—	—
4372-201-00-I	X12CrMnNiN17-7-5	A29O (13)	S20100	N	1.4372	N	SUS201	W	S35350	N
4371-201-53-I	X2CrMnNiN17-7-5	A29B	S20153	N	1.4371	N	—	—	—	—
4615-201-75-E	X3CrMnNiCu15-8-5-3	A28C	—	—	1.4615	I	—	—	—	—
4618-201-76-E	X9CrMnNiCu17-8-5-2	A30L	—	—	1.4618	I	—	—	—	—
4617-201-76-J	X6CrNiMnCu17-8-4-2	A29I	—	—	(1.4617)	I	SUS304J2	I	—	—
4373-202-00-I	X12CrMnNiN18-9-5	A32O	S20200	W	1.4373	N	SUS202	W	S35450	N
4890-202-09-X	X53CrMnNiN21-9-4	A34V	—	—	(1.4890)	I	SUH35	I	S35650	I
4369-202-91-I	X11CrNiMnN19-8-6	A33L (43)	—	—	1.4369	I	—	—	—	—
4597-204-76-I	X8CrMnCuN17-8-3	A25L (40)	—	—	1.4597	N	—	—	—	—
4982-215-00-E	X10CrNiMoMnNbVB 15-10-1	A32P	S21500	N	1.4982	I	—	—	—	—
4319-301-00-I	X5CrNi17-7	A24H (05)	S30100	W	1.4319	I	SUS301	W	S30110	W
4310-301-00-I	X10CrNi18-8	A26L (11)	S30100	W	1.4310	N	—	—	S30110	W
4318-301-53-I	X2CrNiN18-7	A25A (04)	S30153	W	1.4318	N	SUS301L	W	S30153	W
4325-302-00-E	X9CrNi18-9	A27N	S30200	W	1.4325	I	SUS302	W	S30210	W
4326-302-15-I	X12CrNiSi18-9-3	A27P (46)	S30215	W	(1.4326)	I	SUS302B	I	S30240	N
4305-303-00-I	X10CrNiSi18-9	A27M (14)	S30300	W	1.4305	W	SUS303	W	S30317	W
4625-303-23-X	X12CrNiSe18-9	A27O	S30323	I	(1.4625)	I	SUS303Se	I	S30327	I
4667-303-76-J	X12CrNiCuS18-9-3	A27Q	—	—	(1.4667)	I	SUS303Cu	I	—	—
4570-303-31-I	X6CrNiCuS18-9-2	A27I (44)	S30331	I	1.4570	N	—	—	—	—
4301-304-00-I	X5CrNi18-10	A28E (06)	S30400	W	1.4301	I	SUS304	W	S30408	W
4307-304-03-I	X2CrNi18-9	A27B (01)	S30403	W	1.4307	N	SUS304L	W	S30403	W
4306-304-03-I	X2CrNi19-11	A30A (02)	S30403	W	1.4306	N	SUS304L	W	S30403	N
4948-304-09-I	X7CrNi18-9	A27L (07)	S30409	W	1.4948	W	SUS304H	W	S30409	W
4818-304-15-E	X6CrNiSiNCe19-10	A29J	S30415	W	1.4818	I	—	—	S30450	N
4567-304-30-I	X3CrNiCu18-9-4	A27F (15)	S30430	W	1.4567	N	SUSXM7	W	S30488	W

Table A.2 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
a) Austenitic steels										
4315-304-51-I	X5CrNiN19-9	A28F (10)	S30451	N	1.4315	W	SUS304N1	W	S30458	W
4311-304-53-I	X2CrNiN18-9	A27A (03)	S30453	W	1.4311	N	SUS304LN	W	S30453	W
4650-304-75-E	X2CrNiCu19-10	A29A	—	—	1.4650	I	SUS304L	W	S30403	W
4567-304-76-I	X6CrNiCu17-8-2	A25J (45)	—	—	1.4567	W	SUS304J1	I	S30480	W
4649-304-76-J	X6CrNiCu19-9-1	A28I	—	—	(1.4649)	I	SUS304Cu	I	S30488	W
4567-304-98-X	X6CrNiCu18-9-2	A27J	—	—	1.4567	W	SUS304J3	I	S30480	I
4303-305-00-I	X6CrNi18-12	A30I (08)	S30500	W	1.4303	N	SUS305	W	S30510	W
4884-305-00-X	X6CrNiSi18-13-4	A31H	S30500	W	(1.4884)	I	SUSXM15J1	I	S38148	I
4828-305-09-I	X15CrNiSi20-12	A32R	—	—	1.4828	N	—	—	—	—
4824-308-09-J	X20CrNiN22-11	A33Q	—	—	(1.4824)	I	SUH37	I	S30850	W
4835-308-15-U	X7CrNiSiNCe21-11	A32N	S30815	I	1.4835	N	—	—	—	—
4950-309-08-E	X6CrNi23-13	A36J	S30908	W	1.4950	I	SUS309S	W	S30908	W
4833-309-08-I	X18CrNi23-13	A36R	S30908	W	1.4833	N	SUH309	W	S30908	W
4496-309-51-J	X4CrNiMoN25-14-1	A40F	—	—	(1.4496)	I	SUS317J2	I	—	—
4335-310-02-I	X1CrNi25-21	A46A (12)	S31002	W	1.4335	I	—	—	—	—
4845-310-08-E	X8CrNi25-21	A46L	S31008	W	1.4845	I	SUS310S	W	S31008	N
4951-310-08-I	X6CrNi25-20	A45L	S31008	W	1.4951	N	SUS310S	W	S31008	W
4845-310-09-X	X23CrNi25-21	A46O	S31008	W	1.4845	N	SUH310	I	S31020	I
4466-310-50-E	X1CrNiMoN25-22-2	A49A (29)	S31050	W	1.4466	I	—	—	S31053	W
4537-310-92-E	X1CrNiMoCuN25-25-5	A55A	—	—	1.4537	I	—	—	—	—
4547-312-54-I	X1CrNiMoCuN20-18-7	A45A (34)	S31254	W	1.4547	N	SUS312L	W	S31252	N
4659-312-66-I	X1CrNiMoCuNW24-22-6	A52B (41)	S31266	W	1.4659	I	—	—	—	—
4841-314-00-E	X15CrNiSi25-21	A46R	S31400	N	1.4841	I	—	—	—	—
4971-314-79-I	X12CrNiCoMoWMnNNb21-20-3-3-2	A64R	—	—	1.4971	N	SUH661	W	—	—
4660-315-77-I	X6CrNiCuSiMo19-10-3-2	A30J	—	—	(1.4660)	I	SUS315J1	N	—	—
4648-315-77-I	X6CrNiSiCuMo19-13-3-3-1	A33I	—	—	(1.4648)	I	SUS315J2	W	—	—
4401-316-00-I	X5CrNiMo17-12-2	A31I (30)	S31600	W	1.4401	N	SUS316	W	S31608	N
4436-316-00-I	X3CrNiMo17-12-3	A32F (31)	S31600	W	1.4436	I	SUS316	W	S31608	W
4404-316-03-I	X2CrNiMo17-12-2	A31A (21)	S31603	W	1.4404	N	SUS316L	W	S31603	N
4432-316-03-I	X2CrNiMo17-12-3	A32A (22)	S31603	W	1.4432	I	SUS316L	W	S31603	W
4571-316-35-I	X6CrNiMoTi17-12-2	A31F (32)	S31635	W	1.4571	N	SUS316Ti	W	S31668	W
4580-316-40-I	X6CrNiMoNb17-12-2	A31G (33)	S31640	W	1.4580	N	—	—	S31678	W
4495-316-51-J	X6CrNiMoN17-12-3	A32H	S31651	N	(1.4495)	I	SUS316N	I	S31658	N
4406-316-53-I	X2CrNiMoN17-11-2	A30B (25)	S31653	W	1.4406	N	SUS316LN	W	S31653	N
4429-316-53-I	X2CrNiMoN17-12-3	A32B (26)	S31653	W	1.4429	N	SUS316LN	W	S31653	N
4494-316-74-J	X6CrNiMoS17-12-3	A32K	—	—	(1.4494)	I	SUS316F	I	—	—
4647-316-75-X	X2CrNiMoCu18-14-2-2	A34A	—	—	(1.4647)	I	SUS316J1L	I	S31683	I
4578-316-76-E	X3CrNiCuMo17-11-3-2	A30F	—	—	1.4578	I	—	—	—	—
4449-316-76-E	X3CrNiMo18-12-3	A33F	—	—	1.4449	I	—	—	—	—

Table A.2 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
a) Austenitic steels										
4665-316-76-J	X6CrNiMoCu18-12-2-2	A32I	—	—	(1.4665)	I	SUS316J1	I	—	—
4910-316-77-E	X3CrNiMoBN17-13-3	A33G	—	—	1.4910	I	—	—	—	—
4867-316-77-J	X40CrNiWSi15-14-3-2	A29P	—	—	(1.4867)	I	SUH31	I	—	—
4435-316-91-I	X2CrNiMo18-14-3	A35A (23)	—	—	1.4435	N	SUS316L	W	S31603	W
4445-317-00-U	X6CrNiMo19-13-4	A36I	S31700	I	(1.4445)	I	SUS317	W	S31708	N
4438-317-03-I	X2CrNiMo19-14-4	A37A (24)	S31703	W	1.4438	W	SUS317L	W	S31703	W
4439-317-26-E	X2CrNiMoN17-13-5	A35B	S31726	N	1.4439	I	—	—	S31723	W
4483-317-26-I	X2CrNiMoN18-15-5	A38A (28)	S31726	W	(1.4483)	I	—	—	S31723	N
4434-317-53-I	X2CrNiMoN18-12-4	A34B (27)	S31753	W	1.4434	N	SUS317LN	W	S31753	W
4879-317-77-J	X30CrNiMoPB20-11-2	A33R	—	—	(1.4879)	I	SUH38	I	—	—
4476-317-92-X	X3CrNiMo18-16-5	A39F	—	—	(1.4476)	I	SUS317J1	I	S31794	I
4541-321-00-I	X6CrNiTi18-10	A28G (16)	S32100	W	1.4541	I	SUS321	W	S32168	W
4940-321-09-I	X7CrNiTi18-10	A28O (17)	S32109	W	1.4940	N	SUS321H	W	S32169	N
4941-321-09-I	X6CrNiTiB18-10	A28J (18)	S32109	W	1.4941	W	—	—	S32169	W
4652-326-54-I	X1CrNiMoCuN24-22-8	A54A (38)	S32654	N	1.4652	I	—	—	S32652	N
4565-345-65-I	X2CrNiMnMoN25-18-6-5	A54B (42)	S34565	W	1.4565	I	—	—	S34553	N
4550-347-00-I	X6CrNiNb18-10	A28H (19)	S34700	I	1.4550	N	SUS347	W	S34778	N
4912-347-09-I	X7CrNiNb18-10	A28K (20)	S34709	W	1.4912	N	SUS347H	W	S34779	W
4961-347-77-E	X8CrNiNb16-13	A29L	—	—	1.4961	I	—	—	—	—
4854-353-15-E	X6NiCrSiNCe35-25	A60J	S35315	N	1.4854	I	—	—	—	—
4389-384-00-I	X3NiCr18-16	A34F (09)	S38400	W	(1.4389)	I	SUS384	W	S38408	W
b) Austenitic-ferritic (duplex) steels										
4460-312-00-I	X3CrNiMoN27-5-2	D34F (55)	S31200	W	1.4460	I	—	—	S22553	W
4481-312-60-J	X2CrNiMoN25-7-3	D35A	S31260	W	(1.4481)	I	SUS329J4L	I	S22583	W
4424-315-00-I	X2CrNiMoSiMnN19-5-3-2-2	D29A	S31500	N	1.4424	N	—	—	—	—
4462-318-03-I	X2CrNiMoN22-5-3	D30A (52)	S32205	N	1.4462	I	SUS329J3L	W	S22053	N
4162-321-01-E	X2CrMnNiN21-5-1	D27F	S32101	N	1.4162	I	—	—	—	—
4062-322-02-U	X2CrNiN22-2	D24A	S32202	I	1.4062	N	—	—	—	—
4362-323-04-I	X2CrNiN23-4	D27B (51)	S32304	W	1.4362	I	—	—	S23043	W
4507-325-20-I	X2CrNiMoCuN25-6-3	D34A (53)	S32550	W	1.4507	I	—	—	S25554	—
4507-325-50-X	X3CrNiMoCuN26-6-3-2	D35F	S32550	I	1.4507	W	—	—	S25554	I
4658-327-07-U	X2CrNiMoCoN28-8-5-1	D42A	S32707	I	(1.4658)	I	—	—	—	—
4410-327-50-E	X2CrNiMoN25-7-4	D36A (54)	S32750	W	1.4410	I	—	—	S25073	W
4501-327-60-I	X2CrNiMoCuWN25-7-4	D36B (56)	S32760	I	1.4501	N	—	—	S27603	N
4480-329-00-U	X6CrNiMo26-4-2	D32F	S32900	I	(1.4480)	I	SUS329J1	W	—	—
4477-329-06-E	X2CrNiMoN29-7-2	D38A	S32906	N	1.4477	I	—	—	—	—
4485-332-07-U	X2CrNiMoN31-8-4	D43A	S33207	U	(1.4485)	I	—	—	—	—

Table A.2 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
c) Ferritic steels										
4523-182-35-I	X2CrMoTiS18-2	F20B (74)	S18235	W	1.4523	I	—	—	—	—
4002-405-00-I	X6CrAl13	F13H (66)	S40500	W	1.4002	N	SUS405	W	S11348	N
4724-405-77-I	X10CrAlSi13	F13L	—	—	1.4724	N	—	—	—	—
4720-409-00-I	X2CrTi12	F12B (62)	S40900	W	1.4720	N	SUH409L	W	S11163	—
4516-409-75-I	X6CrNiTi12	F13F (64)	S40975	W	1.4516	N	—	—	—	—
4003-410-77-I	X2CrNi12	F12C (61)	S41003	N	1.4003	N	—	—	S11213	N
4000-410-08-I	X6Cr13	F13G (65)	S41008	W	1.4000	N	SUS410S	N	S41008	N
4030-410-90-X	X2Cr12	F12A	—	—	(1.4030)	I	SUS410L	I	S11203	I
4012-429-00-X	X10Cr15	F15L	S42900	I	(1.4012)	I	SUS429	I	S11510	I
4589-429-70-E	X5CrNiMoTi15-2	F17H	—	—	1.4589	I	—	—	—	—
4595-429-71-I	X1CrNb15	F15A	—	—	1.4595	N	—	—	—	—
4016-430-00-I	X6Cr17	F17I (67)	S43000	W	1.4016	I	SUS430	W	S11710	W
4004-430-20-I	X7CrS17	F17L (68)	S43020	W	(1.4004)	I	SUS430F	W	S11717	W
4510-430-35-I	X3CrTi17	F17F (70)	S43035	W	1.4510	N	SUS430LX	W	S11863	W
4520-430-70-I	X2CrTi17	F17A	—	—	1.4520	N	SUS430LX	W	—	—
4511-430-71-I	X3CrNb17	F17G (73)	—	—	1.4511	N	SUS430LX	W	—	—
4664-430-75-J	X2CrCuTi18	F18A	—	—	(1.4664)	I	SUS430J1L	I	—	—
4742-430-77-I	X10CrAlSi18	F18N	—	—	1.4742	N	—	—	—	—
4017-430-91-E	X6CrNi17-1	F18H	—	—	1.4017	I	—	—	—	—
4113-434-00-I	X6CrMo17-1	F18I (69)	S43400	W	1.4113	N	SUS434	W	S11790	W
4526-436-00-I	X6CrMoNb17-1	F18J (71)	S43600	W	1.4526	N	—	—	S11770	W
4513-436-00-J	X2CrMoNbTi18-1	F19A	S43600	W	(1.4513)	N	SUS436L	I	S11862	W
4609-436-77-J	X2CrMo19	F19B	—	—	(1.4609)	N	SUS436J1L	I	—	—
4509-439-40-X	X2CrTiNb18	F18B	S43940	I	1.4509	N	SUS430LX	W	S11873	I
4764-442-72-J	X8CrAl19-3	F19N	—	—	(1.4764)	I	SUH21	I	—	—
4521-444-00-I	X2CrMoTi18-2	F20A (72)	S44400	W	1.4521	N	SUS444	W	S11972	W
4621-445-00-E	X2CrNbCu21	F21A	S44500	W	1.4621	I	—	—	—	—
4762-445-72-I	X10CrAlSi25	F25N	—	—	1.4762	N	—	—	—	—
4128-445-92-J	X2CrMo23-1	F24A	—	—	(1.4128)	I	SUS445J1	I	—	—
4129-445-92-J	X2CrMo23-2	F25A	—	—	(1.4129)	I	SUS445J2	I	—	—
4749-446-00-I	X15CrN26	F26R	S44600	W	1.4749	W	SUH446	W	S12550	W
4750-446-60-U	X2CrMoNi27-4-2	F33A	S44660	I	(1.4750)	I	—	—	—	—
4131-446-92-C	X1CrMo26-1	F27A	S44627	W	(1.4131)	I	SUSXM27	N	S12791	I
4135-447-92-C	X1CrMo30-2	F32A	S44700	N	(1.4135)	I	SUS447J1	N	S13091	I

Table A.2 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
d) Martensitic steels										
4006-410-00-I	X12Cr13	M13B (82)	S41000	W	1.4006	I	SUS410	W	S41010	W
4024-410-09-E	X15Cr13	M13F	—	—	1.4024	I	SUS410	W	—	—
4119-410-92-C	X13CrMo13	M13G	—	—	(1.4119)	I	SUS410J1	N	S45710	I
4313-415-00-I	X3CrNiMo13-4	M17A (81)	S41500	W	1.4313	N	SUSF6NM	W	S41595	W
4415-415-92-E	X2CrNiMoV13-5-2	M20A	—	—	1.4415	I	—	—	—	—
4005-416-00-I	X12CrS13	M13C (83)	S41600	W	1.4005	N	SUS416	W	S41617	N
4642-416-72-J	X13CrPb13	M13A	—	—	(1.4642)	I	SUS410F2	I	—	—
4021-420-00-I	X20Cr13	M13I (84)	S42000	W	1.4021	I	SUS420J1	N	S42020	N
4028-420-00-I	X30Cr13	M13M (85)	S42000	W	1.4028	I	SUS420J2	W	S42030	N
4031-420-00-I	X39Cr13	M13P (86)	S42000	W	1.4031	I	—	—	S42040	W
4034-420-00-I	X46Cr13	M13Q (87)	S42000	W	1.4034	I	—	—	S42040	W
4038-420-00-I	X52Cr13	M13U (88)	S42000	W	(1.4038)	I	—	—	—	—
4039-420-09-I	X60Cr13	M13V (89)	—	—	(1.4039)	I	—	—	—	—
4029-420-20-I	X33CrS13	M13N	S42020	W	1.4029	N	SUS420F	N	S42037	N
4110-420-69-E	X55CrMo14	M14U	—	—	1.4110	I	—	—	—	—
4643-420-72-J	X33CrPb13	M13O	—	—	(1.4643)	I	SUS420F2	I	—	—
4035-420-74-E	X46CrS13	M13R	—	—	1.4035	I	—	—	—	—
4116-420-77-E	X50CrMoV15	M15U	—	—	1.4116	I	—	—	—	—
4419-420-97-E	X38CrMo14	M14P	—	—	1.4419	I	—	—	S45830	W
4929-422-00-I	X23CrMoWMnNiV12-1-1	M13J	S42200	W	(1.4929)	I	SUH 616	N	S47220	N
4923-422-77-E	X30Cr13	M13H	—	—	1.4923	I	—	—	—	—
4058-429-99-J	X33Cr16	M16O	—	—	(1.4058)	I	SUS429J1	I	—	—
4019-430-20-I	X14CrS17	M17F (90)	S43020	W	1.4019	I	—	—	S11717	W
4057-431-00-X	X17CrNi16-2	M18G (91)	S43100	W	1.4057	I	SUS431	W	S43120	I
4123-431-77-E	X40CrMoVN16-2	M18T	—	—	1.4123	I	—	—	—	—
4418-431-77-E	X4CrNiMo16-5-1	M22A	—	—	1.4418	I	—	—	—	—
4122-434-09-I	X39CrMo17-1	M18R (92)	—	—	1.4122	I	—	—	—	—
4040-440-02-X	X68Cr17	M17U	S44002	W	(1.4040)	I	SUS440A	I	S44070	I
4041-440-03-X	X85Cr17	M17V	S44003	W	(1.4041)	I	SUS440B	I	S44080	I
4023-440-04-I	X110Cr17	M17W	S44004	W	(1.4023)	I	SUS440C	N	S44096	N
4025-440-74-X	X110CrS17	M17Z	—	—	(1.4025)	I	SUS440F	I	S44097	I
4766-440-77-X	X80CrSiNi20-2	M20U	—	—	(1.4766)	I	SUH4	I	S48380	I
4916-600-77-J	X18CrMnMoNbVN12	M12G	—	—	(1.4916)	I	SUH 600	I	S46250	N

Table A.2 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
e) Precipitation-hardening steels										
4534-138-00-X	X3CrNiMoAl13-8-3	P24H	S13800	I	1.4534	N	—	—	S51380	I
4594-155-92-E	X5CrNiMoCuNb14-5	P19I	—	—	1.4594	I	—	—	—	—
4532-157-00-I	X8CrNiMoAl15-7-2	P24M (103)	S15700	N	1.4532	N	—	—	S51570	N
4542-174-00-I	X5CrNiCuNb16-4	P20I (101)	S17400	W	1.4542	N	SUS630	W	S51740	W
4568-177-00-I	X7CrNiAl17-7	P24L (102)	S17700	N	1.4568	N	SUS631	W	S51770	N
4457-350-00-X	X9CrNiMoN17-5-3	P25M	(S35000)	I	(1.4457)	W	—	—	S51750	I
4530-455-77-E	X1CrNiMoAlTi12-9-2	P23A	—	—	1.4530	I	—	—	—	—
4596-455-77-E	X1CrNiMoAlTi12-10-2	P24A	—	—	1.4596	I	—	—	—	—
4645-469-10-U	X2CrNiMoCu AlTi12-9-4-3	P25A	(S46910)	I	(1.4645)	I	—	—	—	—
4644-662-20-U	X4NiCrMoTiMnSiB26-14-3-2	P43J	(S66220)	I	(1.4644)	I	—	—	—	—
4980-662-86-X	X6NiCrTiMoVB25-15-2	P42J	(S66286)	I	1.4980	N	SUH660	I	S51525	W
NOTE The grades given in this table are comparable to those given in Table 1. However, to compare similar grades, it is necessary to check each element before making a substitution.										
^a See the sources in the Bibliography.										
^b US steel listed in ASTM A959 and in UNS; if the steel number is given in brackets then the steel has only a UNS number.										
^c European steel listed in EN 10088-1:2005 and in the “Stahl-Eisen-Liste”; if the steel number is given in brackets then the steel is only listed in the “Stahl-Eisen-Liste”.										
^d Japanese Industrial Standard.										
^e Chinese steel of ISC number listed in GB/T20878.										
^f I = identical steel to ISO steel grade; N = steel grade with closer match of composition, but not identical; W = wider match.										

Table A.3 — Designations of the steels given in Table 1 and of comparable grades covered in various designation systems listed according to the European system

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
a) Austenitic steels										
4301-304-00-I	X5CrNi18-10	A28E (06)	S30400	W	1.4301	I	SUS304	W	S30408	W
4303-305-00-I	X6CrNi18-12	A30I (08)	S30500	W	1.4303	N	SUS305	W	S30510	W
4305-303-00-I	X10CrNiS18-9	A27M (14)	S30300	W	1.4305	W	SUS303	W	S30317	W
4306-304-03-I	X2CrNi19-11	A30A (02)	S30403	W	1.4306	N	SUS304L	W	S30403	N
4307-304-03-I	X2CrNi18-9	A27B (01)	S30403	W	1.4307	N	SUS304L	W	S30403	W
4310-301-00-I	X10CrNi18-8	A26L (11)	S30100	W	1.4310	N	—	—	S30110	W
4311-304-53-I	X2CrNi18-9	A27A (03)	S30453	W	1.4311	N	SUS304LN	W	S30453	W
4315-304-51-I	X5CrNiN19-9	A28F (10)	S30451	N	1.4315	W	SUS304N1	W	S30458	W
4318-301-53-I	X2CrNi18-7	A25A (04)	S30153	W	1.4318	N	SUS301L	W	S30153	W
4319-301-00-I	X5CrNi17-7	A24H (05)	S30100	W	1.4319	I	SUS301	W	S30110	W
4325-302-00-E	X9CrNi18-9	A27N	S30200	W	1.4325	I	SUS302	W	S30210	W
4326-302-15-I	X12CrNiSi18-9-3	A27P (46)	S30215	W	(1.4326)	I	SUS302B	I	S30240	N
4335-310-02-I	X1CrNi25-21	A46A (12)	S31002	W	1.4335	I	—	—	—	—
4369-202-91-I	X11CrNiMnN19-8-6	A33L (43)	—	—	1.4369	I	—	—	—	—
4371-201-53-I	X2CrMnNiN17-7-5	A29B	S20153	N	1.4371	N	—	—	—	—
4372-201-00-I	X12CrMnNiN17-7-5	A29O (13)	S20100	N	1.4372	N	SUS201	W	S35350	N
4373-202-00-I	X12CrMnNiN18-9-5	A32O	S20200	W	1.4373	N	SUS202	W	S35450	N
4389-384-00-I	X3NiCr18-16	A34F (09)	S38400	W	(1.4389)	I	SUS384	W	S38408	W
4401-316-00-I	X5CrNiMo17-12-2	A31I (30)	S31600	W	1.4401	N	SUS316	W	S31608	N
4404-316-03-I	X2CrNiMo17-12-2	A31A (21)	S31603	W	1.4404	N	SUS316L	W	S31603	N
4406-316-53-I	X2CrNiMoN17-11-2	A30B (25)	S31653	W	1.4406	N	SUS316LN	W	S31653	N
4429-316-53-I	X2CrNiMoN17-12-3	A32B (26)	S31653	W	1.4429	N	SUS316LN	W	S31653	N
4432-316-03-I	X2CrNiMo17-12-3	A32A (22)	S31603	W	1.4432	I	SUS316L	W	S31603	W
4434-317-53-I	X2CrNiMoN18-12-4	A34B (27)	S31753	W	1.4434	N	SUS317LN	W	S31753	W
4435-316-91-I	X2CrNiMo18-14-3	A35A (23)	—	—	1.4435	N	SUS316L	W	S31603	W
4436-316-00-I	X3CrNiMo17-12-3	A32F (31)	S31600	W	1.4436	I	SUS316	W	S31608	W
4438-317-03-I	X2CrNiMo19-14-4	A37A (24)	S31703	W	1.4438	W	SUS317L	W	S31703	W
4439-317-26-E	X2CrNiMoN17-13-5	A35B	S31726	N	1.4439	I	—	—	S31723	W
4445-317-00-U	X6CrNiMo19-13-4	A36I	S31700	I	(1.4445)	I	SUS317	W	S31708	N
4449-316-76-E	X3CrNiMo18-12-3	A33F	—	—	1.4449	I	—	—	—	—
4466-310-50-E	X1CrNiMoN25-22-2	A49A (29)	S31050	W	1.4466	I	—	—	S31053	W
4476-317-92-X	X3CrNiMo18-16-5	A39F	—	—	(1.4476)	I	SUS317J1	I	S31794	I
4478-083-67-U	X2NiCrMoN25-21-7	A53A	N08367	I	(1.4478)	I	SUS836L	W	—	—
4479-089-36-U	X1NiCrMoMnN34-27-6-5	A72A	N08936	I	(1.4479)	I	—	—	—	—
4483-317-26-I	X2CrNiMoN18-15-5	A38A (28)	S31726	W	(1.4483)	I	—	—	S31723	N
4494-316-74-J	X6CrNiMoS17-12-3	A32K	—	—	(1.4494)	I	SUS316F	I	—	—
4495-316-51-J	X6CrNiMoN17-12-3	A32H	S31651	N	(1.4495)	I	SUS316N	I	S31658	N
4496-309-51-J	X4CrNiMoN25-14-1	A40F	—	—	(1.4496)	—	SUS317J2	I	—	—

Table A.3 (continued)

Steel designations according to ^a											
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e		
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f	
a) Austenitic steels											
4529-089-26-I	X1NiCrMoCuN25-20-7	A52A (37)	N08926	W	1.4529	N	—	—	—	—	
4537-310-92-E	X1CrNiMoCuN25-25-5	A55A	—	—	1.4537	I	—	—	—	—	
4539-089-04-I	X1NiCrMoCu25-20-5	A50A (35)	N08904	W	1.4539	N	SUS890L	W	S39042	N	
4541-321-00-I	X6CrNiTi18-10	A28G (16)	S32100	W	1.4541	I	SUS321	W	S32168	W	
4547-312-54-I	X1CrNiMoCuN20-18-7	A45A (34)	S31254	W	1.4547	N	SUS312L	W	S31252	N	
4550-347-00-I	X6CrNiNb18-10	A28H (19)	S34700	I	1.4550	N	SUS347	W	S34778	N	
4563-080-28-I	X1NiCrMoCu31-27-4	A62A (36)	N08028	W	1.4563	I	—	—	—	—	
4565-345-65-I	X2CrNiMnMoN25-18-6-5	A54B (42)	S34565	W	1.4565	I	—	—	S34553	N	
4567-304-30-I	X3CrNiCu18-9-4	A27F (15)	S30430	W	1.4567	N	SUSXM7	W	S30488	W	
4567-304-76-I	X6CrNiCu17-8-2	A25J (45)	—	—	1.4567	W	SUS304J1	I	S30480	W	
4567-304-98-X	X6CrNiCu18-9-2	A27J	—	—	1.4567	W	SUS304J3	I	S30480	I	
4570-303-31-I	X6CrNiCuS18-9-2	A27I (44)	S30331	I	1.4570	N	—	—	—	—	
4571-316-35-I	X6CrNiMoTi17-12-2	A31F (32)	S31635	W	1.4571	N	SUS316Ti	W	S31668	W	
4578-316-76-E	X3CrNiCuMo17-11-3-2	A30F	—	—	1.4578	I	—	—	—	—	
4580-316-40-I	X6CrNiMoNb17-12-2	A31G (33)	S31640	W	1.4580	N	—	—	S31678	W	
4597-204-76-I	X8CrMnCuN17-8-3	A25L (40)	—	—	1.4597	N	—	—	—	—	
4615-201-75-E	X3CrMnNiCu15-8-5-3	A28C	—	—	1.4615	I	—	—	—	—	
4617-201-76-J	X6CrNiMnCu17-8-4-2	A29I	—	—	(1.4617)	I	SUS304J2	I	—	—	
4618-201-76-E	X9CrMnNiCu17-8-5-2	A30L	—	—	1.4618	I	—	—	—	—	
4625-303-23-X	X12CrNiSe18-9	A27O	S30323	I	(1.4625)	I	SUS303Se	I	S30327	I	
4647-316-75-X	X2CrNiMoCu18-14-2-2	A34A	—	—	(1.4647)	I	SUS316J1L	I	S31683	I	
4648-315-77-I	X6CrNiSiCuMo19-13-3-3-1	A33I	—	—	(1.4648)	I	SUS315J2	W	—	—	
4649-304-76-J	X6CrNiCu19-9-1	A28I	—	—	(1.4649)	I	SUS304Cu	I	S30488	W	
4650-304-75-E	X2CrNiCu19-10	A29A	—	—	1.4650	I	SUS304L	W	S30403	W	
4652-326-54-I	X1CrNiMoCuN24-22-8	A54A (38)	S32654	N	1.4652	I	—	—	S32652	N	
4656-089-04-I	X1NiCrMoCu22-20-5-2	A47A	N08904	N	(1.4656)	I	—	—	S39042	N	
4657-080-20-U	X4NiCrCuMo35-20-4-3	A58F	N08020	I	(1.4657)	I	—	—	—	—	
4659-312-66-I	X1CrNiMoCuNW24-22-6	A52B (41)	S31266	W	1.4659	I	—	—	—	—	
4660-315-77-I	X6CrNiCuSiMo19-10-3-2	A30J	—	—	(1.4660)	I	SUS315J1	N	—	—	
4665-316-76-J	X6CrNiMoCu18-12-2-2	A32I	—	—	(1.4665)	I	SUS316J1	I	—	—	
4667-303-76-J	X12CrNiCuS18-9-3	A27Q	—	—	(1.4667)	I	SUS303Cu	I	—	—	
4818-304-15-E	X6CrNiSiNCe19-10	A29J	S30415	W	1.4818	I	—	—	S30450	N	
4824-308-09-J	X20CrNiN22-11	A33Q	—	—	(1.4824)	I	SUH37	I	S30850	W	
4828-305-09-I	X15CrNiSi20-12	A32R	—	—	1.4828	N	—	—	—	—	
4833-309-08-I	X18CrNi23-13	A36R	S30908	W	1.4833	N	SUH309	W	S30908	W	
4835-308-15-U	X7CrNiSiNCe21-11	A32N	S30815	I	1.4835	N	—	—	—	—	
4841-314-00-E	X15CrNiSi25-21	A46R	S31400	N	1.4841	I	—	—	—	—	
4845-310-08-E	X8CrNi25-21	A46L	S31008	W	1.4845	I	SUS310S	W	S31008	N	
4845-310-09-X	X23CrNi25-21	A46O	S31008	W	1.4845	N	SUH310	I	S31020	I	

Table A.3 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
a) Austenitic steels										
4854-353-15-E	X6NiCrSiNc35-25	A60J	S35315	N	1.4854	I	—	—	—	—
4864-083-77-X	X13NiCr35-16	A51O	—	—	1.4864	N	SUH 330	I	S33010	I
4867-316-77-J	X40CrNiWSi15-14-3-2	A29P	—	—	(1.4867)	I	SUH31	I	—	—
4876-088-00-I	X8NiCrAlTi32-21	A53L	N08800	W	1.4876	N	NCF800	W	—	—
4879-317-77-J	X30CrNiMoPB20-11-2	A33R	—	—	(1.4879)	I	SUH38	I	—	—
4884-305-00-X	X6CrNiSi18-13-4	A31H	S30500	W	(1.4884)	I	SUSXM1501	I	S38148	I
4890-202-09-X	X53CrMnNiN21-9-4	A34V	—	—	(1.4890)	I	SUH35	I	S35650	I
4910-316-77-E	X3CrNiMoBN17-13-3	A33G	—	—	1.4910	I	—	—	—	—
4912-347-09-I	X7CrNiNb18-10	A28K (20)	S34709	W	1.4912	N	SUS347H	W	S34779	W
4940-321-09-I	X7CrNiTi18-10	A28O (17)	S32109	W	1.4940	N	SUS321H	W	S32169	N
4941-321-09-I	X6CrNiTiB18-10	A28J (18)	S32109	W	1.4941	W	—	—	S32169	W
4948-304-09-I	X7CrNi18-9	A27L (07)	S30409	W	1.4948	W	SUS304H	W	S30409	W
4950-309-08-E	X6CrNi23-13	A36J	S30908	W	1.4950	I	SUS309S	W	S30908	W
4951-310-08-I	X6CrNi25-20	A45L	S31008	W	1.4951	N	SUS310S	W	S31008	W
4958-088-77-E	X5NiCrAlTi31-20	A51J	—	—	1.4958	I	—	—	—	—
4959-088-10-U	X7NiCrAlTi33-21	A54L	N08810	I	1.4959	N	NCF800H	N	—	—
4959-088-11-U	X8NiCrAlTi33-21	A54M	N08811	I	1.4959	W	—	—	—	—
4959-088-77-E	X8NiCrAlTi32-20	A52L	—	—	1.4959	I	—	—	—	—
4961-347-77-E	X8CrNiNb16-13	A29L	—	—	1.4961	I	—	—	—	—
4971-314-79-I	X12CrNiCoMoWMnNNb21-20-20-3-3-2	A64R	—	—	1.4971	N	SUH661	W	—	—
4982-215-00-E	X10CrNiMoMnNbVB 15-10-1	A32P	S21500	N	1.4982	I	—	—	—	—
b) Austenitic-ferritic (duplex) steels										
4062-322-02-U	X2CrNiN22-2	D24A	S32202	I	1.4062	N	—	—	—	—
4162-321-01-E	X2CrMnNiN21-5-1	D27F	S32101	N	1.4162	I	—	—	—	—
4362-323-04-I	X2CrNiN23-4	D27B (51)	S32304	W	1.4362	I	—	—	S23043	W
4410-327-50-E	X2CrNiMoN25-7-4	D36A (54)	S32750	W	1.4410	I	—	—	S25073	W
4424-315-00-I	X2CrNiMoSiMnN19-5-3-2-2	D29A	S31500	N	1.4424	N	—	—	—	—
4460-312-00-I	X3CrNiMoN27-5-2	D34F (55)	S31200	W	1.4460	I	—	—	S22553	W
4462-318-03-I	X2CrNiMoN22-5-3	D30A (52)	S32205	N	1.4462	I	SUS329J3L	W	S22053	N
4477-329-06-E	X2CrNiMoN29-7-2	D38A	S32906	N	1.4477	I	—	—	—	—
4480-329-00-U	X6CrNiMo26-4-2	D32F	S32900	I	(1.4480)	I	SUS329J1	W	—	—
4481-312-60-J	X2CrNiMoN25-7-3	D35A	S31260	W	(1.4481)	I	SUS329J4L	I	S22583	W
4485-332-07-U	X2CrNiMoN31-8-4	D43A	S33207	U	(1.4485)	I	—	—	—	—
4501-327-60-I	X2CrNiMoCuWN25-7-4	D36B (56)	S32760	I	1.4501	N	—	—	S27603	N
4507-325-20-I	X2CrNiMoCuN25-6-3	D34A (53)	S32550	W	1.4507	I	—	—	S25554	—
4507-325-50-X	X3CrNiMoCuN26-6-3-2	D35F	S32550	I	1.4507	W	—	—	S25554	I
4658-327-07-U	X2CrNiMoCoN28-8-5-1	D42A	S32707	I	(1.4658)	I	—	—	—	—

Table A.3 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
c) Ferritic steels										
4000-410-08-I	X6Cr13	F13G (65)	S41008	W	1.4000	N	SUS410S	N	S41008	N
4002-405-00-I	X6CrAl13	F13H (66)	S40500	W	1.4002	N	SUS405	W	S11348	N
4003-410-77-I	X2CrNi12	F12C (61)	S41003	N	1.4003	N	—	—	S11213	N
4004-430-20-I	X7CrS17	F17L (68)	S43020	W	(1.4004)	I	SUS430F	W	S11717	W
4012-429-00-X	X10Cr15	F15L	S42900	I	(1.4012)	I	SUS429	I	S11510	I
4016-430-00-I	X6Cr17	F17I (67)	S43000	W	1.4016	I	SUS430	W	S11710	W
4017-430-91-E	X6CrNi17-1	F18H	—	—	1.4017	I	—	—	—	—
4030-410-90-X	X2Cr12	F12A	—	—	(1.4030)	I	SUS410L	I	S11203	I
4113-434-00-I	X6CrMo17-1	F18I (69)	S43400	W	1.4113	N	SUS434	W	S11790	W
4128-445-92-J	X2CrMo23-1	F24A	—	—	(1.4128)	I	SUS445J1	I	—	—
4129-445-92-J	X2CrMo23-2	F25A	—	—	(1.4129)	I	SUS445J2	I	—	—
4131-446-92-C	X1CrMo26-1	F27A	S44627	W	(1.4131)	I	SUSXM27	N	S12791	I
4135-447-92-C	X1CrMo30-2	F32A	S44700	N	(1.4135)	I	SUS447J1	N	S13091	I
4509-439-40-X	X2CrTiNb18	F18B	S43940	I	1.4509	N	SUS430LX	W	S11873	I
4510-430-35-I	X3CrTi17	F17F (70)	S43035	W	1.4510	N	SUS430LX	W	S11863	W
4511-430-71-I	X3CrNb17	F17G (73)	—	—	1.4511	N	SUS430LX	W	—	—
4513-436-00-J	X2CrMoNbTi18-1	F19A	S43600	W	(1.4513)	N	SUS436L	I	S11862	W
4516-409-75-I	X6CrNiTi12	F13F (64)	S40975	W	1.4516	N	—	—	—	—
4520-430-70-I	X2CrTi17	F17A	—	—	1.4520	N	SUS430LX	W	—	—
4521-444-00-I	X2CrMoTi18-2	F20A (72)	S44400	W	1.4521	N	SUS444	W	S11972	W
4523-182-35-I	X2CrMoTiS18-2	F20B (74)	S18235	W	1.4523	I	—	—	—	—
4526-436-00-I	X6CrMoNb17-1	F18J (71)	S43600	W	1.4526	N	—	—	S11770	W
4589-429-70-E	X5CrNiMoTi15-2	F17H	—	—	1.4589	I	—	—	—	—
4595-429-71-I	X1CrNb15	F15A	—	—	1.4595	N	—	—	—	—
4609-436-77-J	X2CrMo19	F19B	—	—	(1.4609)	I	SUS436J1L	I	—	—
4621-445-00-E	X2CrNbCu21	F21A	S44500	W	1.4621	I	—	—	—	—
4664-430-75-J	X2CrCuTi18	F18A	—	—	(1.4664)	I	SUS430J1L	I	—	—
4720-409-00-I	X2CrTi12	F12B (62)	S40900	W	1.4720	N	SUH409L	W	S11163	—
4724-405-77-I	X10CrAlSi13	F13L	—	—	1.4724	N	—	—	—	—
4742-430-77-I	X10CrAlSi18	F18N	—	—	1.4742	N	—	—	—	—
4749-446-00-I	X15CrN26	F26R	S44600	W	1.4749	W	SUH446	W	S12550	W
4750-446-60-U	X2CrMoNi27-4-2	F33A	S44660	I	(1.4750)	I	—	—	—	—
4762-445-72-I	X10CrAlSi25	F25N	—	—	1.4762	N	—	—	—	—
4764-442-72-J	X8CrAl19-3	F19N	—	—	(1.4764)	I	SUH21	I	—	—

Table A.3 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
d) Martensitic steels										
4005-416-00-I	X12CrS13	M13C (83)	S41600	W	1.4005	N	SUS416	W	S41617	N
4006-410-00-I	X12Cr13	M13B (82)	S41000	W	1.4006	I	SUS410	W	S41010	W
4019-430-20-I	X14CrS17	M17F (90)	S43020	W	1.4019	I	—	—	S11717	W
4021-420-00-I	X20Cr13	M13I (84)	S42000	W	1.4021	I	SUS420J1	N	S42020	N
4023-440-04-I	X110Cr17	M17W	S44004	W	(1.4023)	I	SUS440C	N	S44096	N
4024-410-09-E	X15Cr13	M13F	—	—	1.4024	I	SUS410	W	—	—
4025-440-74-X	X110CrS17	M17Z	—	—	(1.4025)	I	SUS440F	I	S44097	I
4028-420-00-I	X30Cr13	M13M (85)	S42000	W	1.4028	I	SUS420J2	W	S42030	N
4029-420-20-I	X33CrS13	M13N	S42020	W	1.4029	N	SUS420F	N	S42037	N
4031-420-00-I	X39Cr13	M13P (86)	S42000	W	1.4031	I	—	—	S42040	W
4034-420-00-I	X46Cr13	M13Q (87)	S42000	W	1.4034	I	—	—	S42040	W
4035-420-74-E	X46CrS13	M13R	—	—	1.4035	I	—	—	—	—
4038-420-00-I	X52Cr13	M13U (88)	S42000	W	(1.4038)	I	—	—	—	—
4039-420-09-I	X60Cr13	M13V (89)	—	—	(1.4039)	I	—	—	—	—
4040-440-02-X	X68Cr17	M17U	S44002	W	(1.4040)	I	SUS440A	I	S44070	I
4041-440-03-X	X85Cr17	M17V	S44003	W	(1.4041)	I	SUS440B	I	S44080	I
4057-431-00-X	X17CrNi16-2	M18G (91)	S43100	W	1.4057	I	SUS431	W	S43120	I
4058-429-99-J	X33Cr16	M16Q	—	—	(1.4058)	I	SUS429J1	I	—	—
4110-420-69-E	X55CrMo14	M14U	—	—	1.4110	I	—	—	—	—
4116-420-77-E	X50CrMoV15	M15U	—	—	1.4116	I	—	—	—	—
4119-410-92-C	X13CrMo13	M13G	—	—	(1.4119)	I	SUS410J1	N	S45710	I
4122-434-09-I	X39CrMo17-1	M18R (92)	—	—	1.4122	I	—	—	—	—
4123-431-77-E	X40CrMoVN16-2	M18T	—	—	1.4123	I	—	—	—	—
4313-415-00-I	X3CrNiMo13-4	M17A (81)	S41500	W	1.4313	N	SUSF6NM	W	S41595	W
4415-415-92-E	X2CrNiMoV13-5-2	M20A	—	—	1.4415	I	—	—	—	—
4418-431-77-E	X4CrNiMo16-5-1	M22A	—	—	1.4418	I	—	—	—	—
4419-420-97-E	X38CrMo14	M14P	—	—	1.4419	I	—	—	S45830	W
4642-416-72-J	X13CrPb13	M13A	—	—	(1.4642)	I	SUS410F2	I	—	—
4643-420-72-J	X33CrPb13	M13O	—	—	(1.4643)	I	SUS420F2	I	—	—
4766-440-77-X	X80CrSiNi20-2	M20U	—	—	(1.4766)	I	SUH4	I	S48380	I
4916-600-77-J	X18CrMnMoNbVN12	M12G	—	—	(1.4916)	I	SUH 600	I	S46250	N
4923-422-77-E	X30Cr13	M13H	—	—	1.4923	I	—	—	—	—
4929-422-00-I	X23CrMoWMnNiV12-1-1	M13J	S42200	W	(1.4929)	I	SUH 616	N	S47220	N

Table A.3 (continued)

Steel designations according to ^a										
ISO number	ISO name	Line (old)	ASTM A959/ UNS ^b		EN 10088-1:2005 Number ^c		JIS ^d		GB/T20878/ ISC ^e	
				I/N/W ^f		I/N/W ^f		I/N/W ^f		I/N/W ^f
e) Precipitation-hardening steels										
4457-350-00-X	X9CrNiMoN17-5-3	P25M	(S35000)	I	(1.4457)	W	—	—	S51750	I
4530-455-77-E	X1CrNiMoAlTi12-9-2	P23A	—	—	1.4530	I	—	—	—	—
4532-157-00-I	X8CrNiMoAl15-7-2	P24M (103)	S15700	N	1.4532	N	—	—	S51570	N
4534-138-00-X	X3CrNiMoAl13-8-3	P24H	S13800	I	1.4534	N	—	—	S51380	I
4542-174-00-I	X5CrNiCuNb16-4	P20I (101)	S17400	W	1.4542	N	SUS630	W	S51740	W
4568-177-00-I	X7CrNiAl17-7	P24L (102)	S17700	N	1.4568	N	SUS631	W	S51770	N
4594-155-92-E	X5CrNiMoCuNb14-5	P19I	—	—	1.4594	I	—	—	—	—
4596-455-77-E	X1CrNiMoAlTi12-10-2	P24A	—	—	1.4596	I	—	—	—	—
4644-662-20-U	X4NiCrMoTiMnSiB26-14-3-2	P43J	(S66220)	I	(1.4644)	I	—	—	—	—
4645-469-10-U	X2CrNiMoCu AlTi12-9-4-3	P25A	(S46910)	I	(1.4645)	I	—	—	—	—
4980-662-86-X	X6NiCrTiMoVB25-15-2	P42J	(S66286)	I	1.4980	N	SUH660	I	S51525	W
NOTE The grades given in this table are comparable to those given in Table 1. However, to compare similar grades, it is necessary to check each element before making a substitution.										
a See the sources in the Bibliography.										
b US steel listed in ASTM A959 and in UNS; if the steel number is given in brackets then the steel has only a UNS number.										
c European steel listed in EN 10088-1:2005 and in the “Stahl-Eisen-Liste”; if the steel number is given in brackets then the steel is only listed in the “Stahl-Eisen-Liste”.										
d Japanese Industrial Standard.										
e Chinese steel of ISC number listed in GB/T20878.										
f I = identical steel to ISO steel grade; N = steel grade with closer match of composition, but not identical; W = wider match.										

Annex B
(informative)

**Steels given in Table 1 and of comparable grades covered in various
International Standards**

STANDARDSISO.COM : Click to view the full PDF of ISO 15510:2010

Table B.1 — Steels given in Table 1 and of comparable grades covered in various International Standards

Steel designations according to ^{a,b}												
ISO number	ISO name	Line (old)	ISO 4954:1993	ISO 4955:2005	ISO 6931-1:1994	ISO 6931-2:2005	ISO 9327-5:1999	ISO 9328-7:2004	ISO 16143-1:2004	ISO 16143-2:2004	ISO 16143-3:2005	
a) Austenitic steels												
4318-301-53-I	X2CrNiN18-7	A25A (04)	—	—	—	—	—	X	—	—	—	
4319-301-00-I	X5CrNi17-7	A24H (05)	—	—	—	—	—	—	—	—	—	
4310-301-00-I	X10CrNi18-8	A26L (11)	X10CrNi18 9 E	—	X9CrNi18-8	X	—	—	X	X	X	
4325-302-00-E	X9CrNi18-9	A27N	—	—	—	—	—	—	X	—	—	
4326-302-15-I	X12CrNiSi18-9-3	A27P (46)	—	—	—	—	—	—	X	—	—	
4307-304-03-I	X2CrNi18-9	A27B (01)	X2CrNi18 10E	—	—	—	X2CrNi18-10	X	X	X	x	
4306-304-03-I	X2CrNi19-11	A30A (02)	—	—	—	—	—	X	X	X	X	
4311-304-53-I	X2CrNiN18-9	A27A (03)	—	—	—	—	X2CrNiN18-10	X2CrNiN18-10	X	X	—	
4301-304-00-I	X5CrNi18-10	A28E (06)	X5CrNi18 9E	—	—	X	X5CrNi18-9	X	X	X	X	
4315-304-51-I	X5CrNiN19-9	A28F (10)	—	—	—	—	—	—	—	X	X	
4948-304-09-I	X7CrNi18-9	A27L (07)	—	X	—	—	X	X6CrNi18-10	—	—	x	
4818-304-15-E	X6CrNiSiN18-9-10	A29J	—	X	—	—	—	—	—	—	—	
4650-304-75-E	X2CrNiCu19-10	A29A	—	—	—	—	—	—	—	—	—	
4649-304-76-J	X6CrNiCu19-9-1	A28I	—	—	—	—	—	—	—	—	—	
4305-303-00-I	X10CrNiSi18-9	A27M (14)	—	—	—	—	—	—	—	X	X	
4625-303-23-X	X12CrNiSe18-9	A27O	—	—	—	—	—	—	—	—	—	
4570-303-31-I	X6CrNiCuS18-9-2	A27I (44)	—	—	—	—	—	—	—	X	X	
4667-303-76-J	X12CrNiCuS18-9-3	A27Q	—	—	—	—	—	—	—	—	—	
4615-201-75-E	X3CrMnNiCu15-8-5-3	A28C	—	—	—	—	—	—	—	—	—	
4541-321-00-I	X6CrNiTi18-10	A28G (16)	X6CrNiTi18 10E	—	—	—	X	X	X	X	X	
4940-321-09-I	X7CrNiTi18-10	A28O (17)	—	X	—	—	X	—	—	—	—	
4941-321-09-I	X6CrNiTiB18-10	A28J (18)	—	—	—	—	—	X	—	—	—	
4550-347-00-I	X6CrNiN18-10	A28H (19)	—	X	—	—	X	X	X	X	—	
4912-347-09-I	X7CrNiN18-10	A28K (20)	—	—	—	—	X	—	—	—	—	
4961-347-77-E	X8CrNiN16-13	A29L	—	—	—	—	—	X	—	—	—	

Table B.1 (continued)

Steel designations according to ^{a,b}														
ISO number	ISO name	Line (old)	ISO 4954:1993	ISO 4955:2005	ISO 6931-1:1994	ISO 6931-2:2005	ISO 9327-5:1999	ISO 9328-7:2004	ISO 16143-1:2004	ISO 16143-2:2004	ISO 16143-3:2005			
a) Austenitic steels														
4567-304-30-I	X3CrNiCu18-9-4	A27E (15)	X3CrNiCu 18 9 3E	—	—	—	—	—	—	X	—			
4567-304-76-I	X6CrNiCu17-8-2	A25J (45)	—	—	—	—	—	—	X	—	—			
4567-304-98-X	X6CrNiCu18-9-2	A27J	—	—	—	—	—	—	—	—	—			
4660-315-77-I	X6CrNiCuSiMo19-10-3-2	A30J	—	—	—	—	—	—	—	—	—			
4867-316-77-J	X40CrNiWSi15-14-3-2	A29P	—	—	—	—	—	—	—	—	—			
4303-305-00-I	X6CrNi18-12	A30I (08)	X5CrNi18 12E	—	—	—	—	—	—	X	X			
4828-305-09-I	X15CrNiSi20-12	A32R	—	X	—	—	—	—	—	—	—			
4835-308-15-U	X7CrNiSiNCe21-11	A32N	—	X	—	—	—	—	—	—	X			
4884-305-00-X	X6CrNiSi18-13-4	A31H	—	—	—	—	—	—	—	—	—			
4389-384-00-I	X3NiCr18-16	A34F (09)	—	—	—	—	—	—	—	—	—			
4371-201-53-I	X2CrMnNiN17-7-5	A29B	—	—	—	—	—	—	—	—	—			
4372-201-00-I	X12CrMnNiN17-7-5	A29O (13)	—	—	—	X	—	—	X	—	—			
4597-204-76-I	X8CrMnCuN17-8-3	A25L (40)	—	—	—	—	—	—	X	X	X			
4617-201-76-J	X6CrNiMnCu17-8-4-2	A29I	—	—	—	—	—	—	—	—	—			
4618-201-76-E	X9CrMnNiCu17-8-5-2	A30L	—	—	—	—	—	—	—	—	—			
4373-202-00-I	X12CrMnNiN18-9-5	A32O	—	—	—	—	—	—	—	—	—			
4982-215-00-E	X10CrNiMoMnNbVB 15-10-1	A32P	—	—	—	—	—	—	—	—	—			
4369-202-91-I	X11CrNiMnN19-8-6	A33L (43)	—	—	—	—	—	—	X	X	x			
4890-202-09-X	X53CrMnNiN21-9-4	A34V	—	—	—	—	—	—	—	—	—			
4648-315-77-I	X6CrNiSiCuMo19-13-3-3-1	A33I	—	—	—	—	—	—	—	—	—			
4404-316-03-I	X2CrNiMo17-12-2	A31A (21)	—	—	—	—	X	X	X	X	X			
4432-316-03-I	X2CrNiMo17-12-3	A32A (22)	X2CrNiMo 17 13 3E	—	—	—	—	X	X	X	X			
4435-316-91-I	X2CrNiMo18-14-3	A35A (23)	—	—	—	—	—	X	X	X	X			
4406-316-53-I	X2CrNiMoN17-11-2	A30B (25)	—	—	—	—	—	X	—	—	—			
4665-316-76-J	X6CrNiMoCu18-12-2-2	A32I	—	—	—	—	—	—	—	—	—			

Table B.1 (continued)

Steel designations according to ^{a,b}												
ISO number	ISO name	Line (old)	ISO 4954:1993	ISO 4955:2005	ISO 6931-1:1994	ISO 6931-2:2005	ISO 9327-5:1999	ISO 9328-7:2004	ISO 16143-1:2004	ISO 16143-2:2004	ISO 16143-3:2005	
a) Austenitic steels												
4647-316-75-X	X2CrNiMoCu18-14-2-2	A34A	—	—	—	—	—	—	—	—	—	
4578-316-76-E	X3CrNiCuMo17-11-3-2	A30F	—	—	—	—	—	—	—	—	—	
4429-316-53-I	X2CrNiMoN17-12-3	A32B (26)	X2CrNiMoN 17 13 3E	—	—	—	—	X2CrNiMoN 17-13-3	X	X	—	
4401-316-00-I	X5CrNiMo17-12-2	A31I (30)	X5CrNiMo 17 12 2E	—	X5CrNiMo 17-12-2	X	X5CrNiMo 17-12	X	X	X	X	
4436-316-00-I	X3CrNiMo17-12-3	A32F (31)	—	—	—	—	—	X	X	X	X	
4449-316-76-E	X3CrNiMo18-12-3	A33F	—	—	—	—	—	—	—	—	—	
4910-316-77-E	X3CrNiMoBN17-13-3	A33G	—	—	—	—	—	X	—	—	—	
4494-316-74-J	X6CrNiMoS17-12-3	A32K	—	—	—	—	—	—	—	—	—	
4495-316-51-J	X6CrNiMoN17-12-3	A32H	—	—	—	—	—	—	—	—	—	
4571-316-35-I	X6CrNiMoTi17-12-2	A31F (32)	X6CrNiMoTi 17 12 2E	—	—	—	X6CrNiMoTi 17-12	X	X	X	X	
4580-316-40-I	X6CrNiMoNb17-12-2	A31G (33)	—	—	—	—	—	X	—	—	—	
4879-317-77-J	X30CrNiMoPB20-11-2	A33R	—	—	—	—	—	—	—	—	—	
4438-317-03-I	X2CrNiMo19-14-4	A37A (24)	—	—	—	—	—	—	—	—	—	
4439-317-26-E	X2CrNiMoN17-13-5	A35B	—	—	—	—	—	X	—	—	—	
4483-317-26-I	X2CrNiMoN18-15-5	A38A (28)	—	—	—	—	—	—	—	—	—	
4434-317-53-I	X2CrNiMoN18-12-4	A34B (27)	—	—	—	—	—	X	—	X	X	
4445-317-00-U	X6CrNiMo19-13-4	A36I	—	—	—	—	—	—	—	—	—	
4476-317-92-X	X3CrNiMo18-16-5	A39F	—	—	—	—	—	—	—	—	—	
4824-308-09-J	X20CrNiN22-11	A33Q	—	—	—	—	—	—	—	—	—	
4950-309-08-E	X6CrNi23-13	A36J	—	—	—	—	—	X	—	—	—	
4833-309-08-I	X18CrNi23-13	A36R	—	X	—	—	—	—	—	—	X	
4496-309-51-J	X4CrNiMoN25-14-1	A40F	—	—	—	—	—	—	—	—	—	
4335-310-02-I	X1CrNi25-21	A46A (12)	—	—	—	—	—	—	—	—	—	
4951-310-08-I	X6CrNi25-20	A45L	—	—	—	—	—	X	—	X	X	
4845-310-08-E	X8CrNi25-21	A46L	—	X	—	—	X6CrNi25-21	—	—	—	—	

Table B.1 (continued)

Steel designations according to ^{a,b}												
ISO number	ISO name	Line (old)	ISO 4954:1993	ISO 4955:2005	ISO 6931-1:1994	ISO 6931-2:2005	ISO 9327-5:1999	ISO 9328-7:2004	ISO 16143-1:2004	ISO 16143-2:2004	ISO 16143-3:2005	
a) Austenitic steels												
4845-310-09-X	X23CrNi25-21		—	—	—	—	—	—	—	—	—	
4841-314-00-E	X15CrNiSi25-21		—	—	—	—	—	—	—	—	—	
4466-310-50-E	X1CrNiMoN25-22-2	A49A (29)	—	—	—	—	—	X	X	X	X	
4547-312-54-I	X1CrNiMoCuN20-18-7	A45A (34)	—	—	—	—	—	X	—	X	X	
4659-312-66-I	X1CrNiMoCuNW24-22-6	A52B (41)	—	—	—	—	—	—	X	X	—	
4652-326-54-I	X1CrNiMoCuN24-22-8	A54A (38)	—	—	—	—	—	—	X	—	—	
4565-345-65-I	X2CrNiMnMoN25-18-6-5	A54B (42)	—	—	—	—	—	—	X	X	—	
4971-314-79-I	X12CrNiCoMoWMMnNb21-20-20-3-3-2	A64R	—	—	—	—	—	—	—	—	—	
4537-310-92-E	X1CrNiMoCuN25-25-5	A55A	—	—	—	—	—	X	—	—	—	
4656-089-04-I	X1NiCrMoCu22-20-5-2	A47A	—	—	—	—	—	—	—	—	—	
4539-089-04-I	X1NiCrMoCu25-20-5	A50A (35)	—	—	—	—	X2NiCrMoCu 25-20-5	X	X	X	X	
4529-089-26-I	X1NiCrMoCuN25-20-7	A52A (37)	—	—	—	—	—	X	—	X	—	
4478-083-67-U	X2NiCrMoN25-21-7	A53A	—	—	—	—	—	—	—	—	—	
4958-088-77-E	X5NiCrAlTi31-20	A51J	—	—	—	—	—	X	—	—	—	
4563-080-28-I	X1NiCrMoCu31-27-4	A62A (36)	—	—	—	—	—	X	X	X	X	
4876-088-00-I	X8NiCrAlTi32-21	A53L	—	X	—	—	—	X	—	—	X	
4959-088-77-E	X8NiCrAlTi32-20	A52L	—	—	—	—	—	X	—	—	—	
4959-088-10-U	X7NiCrAlTi33-21	A54L	—	—	—	—	—	—	—	—	—	
4959-088-11-U	X8NiCrAlTi33-21	A54M	—	—	—	—	—	—	—	—	—	
4864-083-77-X	X13NiCr35-16	A51O	—	—	—	—	—	—	—	—	—	
4657-080-20-U	X4NiCrCuMo35-20-4-3	A58F	—	—	—	—	—	—	—	—	—	
4854-353-15-E	X6NiCrSiNCe35-25	A60J	—	X	—	—	—	—	—	—	—	
4479-089-36-U	X1NiCrMoMnN34-27-6-5	A72A	—	—	—	—	—	—	—	—	—	

Table B.1 (continued)

Steel designations according to ^{a,b}												
ISO number	ISO name	Line (old)	ISO 4954:1993	ISO 4955:2005	ISO 6931-1:1994	ISO 6931-2:2005	ISO 9327-5:1999	ISO 9328-7:2004	ISO 16143-1:2004	ISO 16143-2:2004	ISO 16143-3:2005	
b) Austenitic-ferritic (duplex) steels												
4062-322-02-U	X2CrNiN22-2	D24A	—	—	—	—	—	—	—	—	—	—
4162-321-01-E	X2CrMnNiN21-5-1	D27F	—	—	—	—	—	—	—	—	—	—
4362-323-04-I	X2CrNiN23-4	D27B (51)	—	—	—	—	—	—	X	X	X	—
4424-315-00-I	X2CrNiMoSiMnN19-5-3-2-2	D29A	—	—	—	—	—	—	—	—	—	—
4462-318-03-I	X2CrNiMoN22-5-3	D30A (52)	—	—	—	—	—	—	X	X	X	—
4481-312-60-J	X2CrNiMoN25-7-3	D35A	—	—	—	—	—	—	—	X	—	—
4507-325-20-I	X2CrNiMoCuN25-6-3	D34A (53)	—	—	—	—	—	—	X	—	—	—
4507-325-50-X	X3CrNiMoCuN26-6-3-2	D35F	—	—	—	—	—	—	—	—	—	—
4410-327-50-E	X2CrNiMoN25-7-4	D36A (54)	—	—	—	—	—	—	X	X	X	—
4501-327-60-I	X2CrNiMoCuWN25-7-4	D36B (56)	—	—	—	—	—	—	X	X	—	—
4460-312-00-I	X3CrNiMoN27-5-2	D34F (55)	—	—	—	—	—	—	—	X	—	—
4480-329-00-U	X6CrNiMo26-4-2	D32F	—	—	—	—	—	—	—	—	—	—
4477-329-06-E	X2CrNiMoN29-7-2	D38A	—	—	—	—	—	—	—	—	—	—
4658-327-07-U	X2CrNiMoCoN28-8-5-1	D42A	—	—	—	—	—	—	—	—	—	—
4485-332-07-U	X2CrNiMoN31-8-4	D43A	—	—	—	—	—	—	—	—	—	—
c) Ferritic steels												
4030-410-90-X	X2Cr12	F12A	—	—	—	—	—	—	—	—	—	—
4003-410-77-I	X2CrNi12	F12C (61)	—	—	—	—	—	X	X	—	—	—
4720-409-00-I	X2CrTi12	F12B (62)	—	X	—	—	—	—	X	—	—	—
4516-409-75-I	X6CrNiTi12	F13F (64)	—	—	—	—	—	X	—	—	—	—
4000-410-08-I	X6Cr13	F13G (65)	—	X	—	—	—	—	—	—	—	—
4002-405-00-I	X6CrAl13	F13H (66)	—	—	—	—	—	—	—	—	—	—
4724-405-77-I	X10CrAlSi13	F13L	—	X	—	—	—	—	—	—	—	—
4012-429-00-X	X10Cr15	F15L	—	—	—	—	—	—	—	—	—	—
4595-429-71-I	X1CrNb15	F15A	—	—	—	—	—	—	—	—	—	—
4589-429-70-E	X5CrNiMoTi15-2	F17H	—	—	—	—	—	—	—	—	—	—

Table B.1 (continued)

Steel designations according to ^{a,b}														
ISO number	ISO name	Line (old)	ISO 4954:1993	ISO 4955:2005	ISO 6931-1:1994	ISO 6931-2:2005	ISO 9327-5:1999	ISO 9328-7:2004	ISO 16143-1:2004	ISO 16143-2:2004	ISO 16143-3:2005			
c) Ferritic steels														
4016-430-00-I	X6Cr17	F17I (67)	X6Cr17E	X	—	X	—	—	X	X	X			
4004-430-20-I	X7CrS17	F17L (68)	—	—	—	—	—	—	—	—	—			
4520-430-70-I	X2CrTi17	F17A	—	—	—	—	—	X	—	—	—			
4664-430-75-J	X2CrCuTi18	F18A	—	—	—	—	—	—	—	—	—			
4509-439-40-X	X2CrTiNb18	F18B	—	X	—	—	—	X	—	—	—			
4510-430-35-I	X3CrTi17	F17F (70)	—	X	—	—	—	X	X	—	—			
4511-430-71-I	X3CrNb17	F17G (73)	—	—	—	—	—	—	X	X	X			
4742-430-77-I	X10CrAlSi18	F18N	—	X	—	—	—	—	—	—	—			
4017-430-91-E	X6CrNi17-1	F18H	—	—	—	—	—	—	—	—	—			
4113-434-00-I	X6CrMo17-1	F18I (69)	X6CrMo17 1E	—	—	—	—	—	—	X	X			
4513-436-00-J	X2CrMoNbTi18-1	F19A	—	—	—	—	—	—	—	—	—			
4609-436-77-J	X2CrMo19	F19B	—	—	—	—	—	—	—	—	—			
4526-436-00-I	X6CrMoNb17-1	F18J (71)	—	—	—	—	—	—	—	—	—			
4521-444-00-I	X2CrMoTi18-2	F20A (72)	—	—	—	—	—	X	—	—	—			
4523-182-35-I	X2CrMoTiS18-2	F20B (74)	—	—	—	—	—	—	—	—	X			
4621-445-00-E	X2CrNbCu21	F21A	—	—	—	—	—	—	—	—	—			
4764-442-72-J	X8CrAl19-3	F19N	—	—	—	—	—	—	—	—	—			
4128-445-92-J	X2CrMo23-1	F24A	—	—	—	—	—	—	—	—	—			
4129-445-92-J	X2CrMo23-2	F25A	—	—	—	—	—	—	—	—	—			
4762-445-72-I	X10CrAlSi25	F25N	—	X	—	—	—	—	—	—	—			
4749-446-00-I	X15CrN26	F26R	—	X	—	—	—	—	—	—	X			
4131-446-92-C	X1CrMo26-1	F27A	—	—	—	—	—	—	—	—	—			
4750-446-60-U	X2CrMoNi27-4-2	F33A	—	—	—	—	—	—	—	—	—			
4135-447-92-C	X1CrMo30-2	F32A	—	—	—	—	—	—	—	—	—			

Table B.1 (continued)

Steel designations according to ^{a,b}												
ISO number	ISO name	Line (old)	ISO 4954:1993	ISO 4955:2005	ISO 6931-1:1994	ISO 6931-2:2005	ISO 9327-5:1999	ISO 9328-7:2004	ISO 16143-1:2004	ISO 16143-2:2004	ISO 16143-3:2005	
d) Martensitic steels												
4006-410-00-I	X12Cr13	M13B (82)	X12Cr13E	—	—	—	—	—	X	X	X	
4024-410-09-E	X15Cr13	M13F	—	—	—	—	—	—	—	—	—	
4119-410-92-C	X13CrMo13	M13G	—	—	—	—	—	—	—	—	—	
4642-416-72-J	X13CrPb13	M13A	—	—	—	—	—	—	—	—	—	
4005-416-00-I	X12CrS13	M13C (83)	—	—	—	—	—	—	—	X	X	
4021-420-00-I	X20Cr13	M13I (84)	—	—	—	X	—	—	X	X	X	
4916-600-77-J	X18CrMnMoNbVN12	M12G	—	—	—	—	—	—	—	—	—	
4929-422-00-I	X23CrMoWmMnNiV12-1-1	M13J	—	—	—	—	—	—	—	—	—	
4923-422-77-E	X30Cr13	M13H	—	—	—	—	—	—	—	—	—	
4028-420-00-I	X30Cr13	M13M (85)	—	—	—	X	—	—	X	X	X	
4029-420-20-I	X33CrS13	M13N	—	—	—	—	—	—	—	—	—	
4643-420-72-J	X33CrPb13	M13O	—	—	—	—	—	—	—	—	—	
4031-420-00-I	X39Cr13	M13P (86)	—	—	—	X	—	—	—	—	—	
4419-420-97-E	X38CrMo14	M14P	—	—	—	—	—	—	—	—	—	
4123-431-77-E	X40CrMoVN16-2	M18T	—	—	—	—	—	—	—	—	—	
4034-420-00-I	X46Cr13	M13Q (87)	—	—	—	—	—	—	—	—	—	
4035-420-74-E	X46CrS13	M13R	—	—	—	—	—	—	—	—	—	
4038-420-00-I	X52Cr13	M13U (88)	—	—	—	—	—	—	—	—	—	
4110-420-69-E	X55CrMo14	M14U	—	—	—	—	—	—	—	—	—	
4039-420-09-I	X60Cr13	M13V (89)	—	—	—	—	—	—	—	—	—	
4313-415-00-I	X3CrNiMo13-4	M17A (81)	—	—	—	—	—	X	—	X	—	
4415-415-92-E	X2CrNiMoV13-5-2	M20A	—	—	—	—	—	—	—	—	—	
4116-420-77-E	X50CrMoV15	M15U	—	—	—	—	—	—	—	—	—	
4057-431-00-X	X17CrNi16-2	M18G (91)	X19CrNi16 2E	—	—	—	—	—	—	—	X	
4058-429-99-J	X33Cr16	M16O	—	—	—	—	—	—	—	X	—	
4418-431-77-E	X4CrNiMo16-5-1	M22A	—	—	—	—	—	X	—	—	—	