
**Specification and qualification of welding
procedures for metallic materials —
Qualification based on pre-production
welding test**

*Descriptif et qualification d'un mode opératoire de soudage pour les
matériaux métalliques — Qualification sur la base d'un assemblage
soudé de préproduction*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 15613:2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15613 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Unification of requirements in the field of metal welding*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Throughout the text of this document, read "...this European Standard..." to mean "...this International Standard...".

For the purposes of this International Standard, the CEN annex regarding fulfilment of European Council Directives has been removed.

Contents

	page
Foreword.....	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Preliminary welding procedure specifications (pWPS)	2
5 Qualification of the welding procedure	2
6 Welding of test pieces	2
7 Testing	2
7.1 Fusion welding.....	2
7.2 Resistance welding.....	3
7.2.1 General.....	3
7.2.2 Overlap welding	3
7.2.3 Butt welding	3
8 Range of qualification	3
9 Validity	3
10 Welding procedure qualification record (WPQR)	4

Foreword

This document (EN ISO 15613:2004) has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DS, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard EN ISO 15613:2004 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2004, and conflicting national standards shall be withdrawn at the latest by December 2004.

This document supersedes EN 288-8:1995.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

In EN ISO 15607, one of the methods of welding procedure qualification is based on pre-production welding test.

Qualification based on a pre-production welding test can be used where the shape and dimensions of the standard test pieces (e.g. those of prEN ISO 15614) do not adequately represent the joint to be welded.

In such cases, one or more special test pieces can be made to simulate the production joint in all essential features, e.g. dimensions, restraint, heat sink effects, limited access. In the case of resistance welding, actual components have to be used for the pre-production test.

STANDARDSISO.COM : Click to view the full PDF of ISO 15613:2004

1 Scope

This European Standard is a part of a series of standards, details of this series are given in EN ISO 15607:2003, annex A.

This standard specifies how a preliminary welding procedure specification is qualified based on pre-production welding tests.

This standard is applicable to arc welding, gas welding, beam welding, resistance welding, stud welding and friction welding of metallic materials. The principles of this standard may be applied to other welding processes.

The use of this standard can be restricted by an application standard or specification.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO 15607:2003, *Specification and qualification of welding procedures for metallic materials - General rules (ISO 15607:2003)*.

CR ISO 15608:2000, *Welding - Guidelines for a metallic material grouping system (ISO/TR 15608:2000)*.

prEN ISO 15609-1, *Specification and approval of welding procedures for metallic materials - Welding procedure specification - Part 1: Arc welding (ISO/DIS 15609-1:2000)*.

EN ISO 15609-2, *Specification and qualification of welding procedures for metallic materials - Welding procedure specification - Part 2: Gas welding (ISO 15609-2:2001)*.

prEN ISO 15609-3, *Specification and qualification of welding procedures for metallic materials - Welding procedure specification - Part 3: Electron beam welding (ISO/DIS 15609-3:2000)*.

prEN ISO 15609-4, *Specification and qualification of welding procedures for metallic materials - Welding procedure specification - Part 4: Laser beam welding (ISO/DIS 15609-4:2000)*.

prEN ISO 15609-5, *Specification and approval of welding procedures for metallic materials - Welding procedure specification - Part 5: Resistance welding (ISO/DIS 15609-5:2000)*.

EN ISO 15614-1, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1:2003)*.

prEN ISO 15614-2, *Specification and approval of welding procedures for metallic materials - Welding procedure tests - Part 2: Arc welding of aluminium and its alloys (ISO/DIS 15614-2:2000)*.

prEN ISO 15614-3, *Specification and qualification of welding procedures for metallic materials - Welding procedure tests - Part 3: Welding procedure tests for the arc welding of cast iron (was submitted to CEN Enquiry as prEN 288-12)*.

prEN ISO 15614-4, *Specification and qualification of welding procedures for metallic materials - Welding procedure tests - Part 4: Finishing welding of aluminium castings (was submitted to CEN Enquiry as prEN 288-13)*.

prEN ISO 15614-5, *Specification and approval of welding procedures for metallic materials - Welding procedure tests - Part 5: Arc welding of titanium, zirconium and their alloys (ISO/DIS 15614-5:2000)*.

ISO 15613:2004(E)

prEN ISO 15614-6, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 6: Copper and copper alloys*.

EN ISO 15614-8, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 8: Welding of tubes to tube-plate joints (ISO 15614-8:2002)*.

prEN ISO 15614-9, *Specification and qualification of welding procedures for metallic materials - Welding procedure tests - Part 9: Underwater hyperbaric wet welding (ISO/DIS 15614-9:2000)*.

prEN ISO 15614-10, *Specification and approval of welding procedures for metallic materials - Welding procedure test - Part 10: Hyperbaric dry welding (ISO/DIS 15614-10:2000)*.

EN ISO 15614-11, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 11: Electron and laser beam welding (ISO 15614-11:2002)*.

prEN ISO 15614-12:2002, *Specification and approval of welding procedures for metallic materials - Welding procedure tests - Part 12: Spot, seam and projection welding (ISO/DIS 15614-12:2000)*.

prEN ISO 15614-13:2002, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 13: Resistance butt and flash welding (ISO/DIS 15614-13:2002)*.

ISO 10447, *Welding - Peel and chisel testing of resistance spot, projection and seam welds*.

3 Terms and definitions

For the purposes of this European Standard, the terms and definitions given in EN ISO 15607:2003 apply.

4 Preliminary welding procedure specifications (pWPS)

The preliminary welding procedure specification shall be prepared in accordance with prEN ISO 15609-1 or EN ISO 15609-2.

5 Qualification of the welding procedure

The qualification of the welding procedure shall be carried out by an examiner or examining body in accordance with the relevant part of prEN ISO 15614 as modified by this standard.

6 Welding of test pieces

Preparation and welding of the test pieces shall be carried out under the general conditions of production welding which they shall represent with shapes and dimensions of the test piece simulating the actual welding conditions of the structure. This includes welding positions and other essential items, e.g. stress conditions, heating effects, limited access, edge condition.

When actual components are used, jigs and fixtures shall be those which will be used in production.

If tack welds are to be fused into the final joint they shall be included in the test piece.

7 Testing

7.1 Fusion welding

The testing of the test pieces shall as far as possible be carried out in accordance with the relevant part of prEN ISO 15614.

In general, the following tests are to be performed at least:

- a) visual inspection (100 %);
- b) surface crack detection (for non-magnetic materials, penetrant testing only);
- c) hardness tests (not required for parent metals of ferritic steels with $R_m < 420 \text{ N/mm}^2$ or $R_e < 275 \text{ N/mm}^2$ or for steels according to group 8 or aluminium alloys in accordance with groups 21 and 22 of CR ISO 15608:2000);
- d) macroscopic examination (number depends on the geometry of the structure).

7.2 Resistance welding

7.2.1 General

If available, the results of other WPS could be taken into consideration if all conditions are sufficiently comparable, e.g. equipment, electrodes, material (type, surface, thickness) and weld data.

7.2.2 Overlap welding

If a pre-production weld test of overlap welds relates to prEN ISO 15614-12:2002, all types of tests according to Table 1 of that standard shall be carried out as far as necessary. In general, the following tests shall be performed at least:

- a) visual inspection;
- b) work shop test to determine weld size and fracture type;
- c) macroscopic examination to determine at least nugget diameter and indentation respectively minimum width of a resistance seam weld (number depends on the geometry of the structure);
- d) chisel tests according to ISO 10447 of pre-production test piece.

7.2.3 Butt welding

If a pre-production weld test of butt welds relates to prEN ISO 15614-13:2002, all types of test related to Table 1 of that standard shall be carried out as far as possible. In general, the following tests shall be performed at least:

- a) visual inspection (penetrant testing);
- b) destructive tests, especially bend tests or tests by deformation of the whole pre-production test piece.

8 Range of qualification

Any qualification issued under this standard is limited to the type of joint used in the pre-production test.

The range of qualification is generally in accordance with the relevant parts of prEN ISO 15614 for welding procedure tests. However the range of qualification for thickness can be applied to each component in the joint, as well as weld thickness.

In the case of resistance welding, the qualification range is limited to the pre-production test piece which was tested.

9 Validity

The qualified welding procedure based on pre-production welding test is valid as far as the welding production is carried out in the specified range, see clause 8.