
**Thermoplastic elastomers —
Nomenclature and abbreviated terms**

Élastomères thermoplastiques — Nomenclature et termes abrégés

STANDARDSISO.COM : Click to view the full PDF of ISO 18064:2022



STANDARDSISO.COM : Click to view the full PDF of ISO 18064:2022



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Nomenclature system.....	1
5 Categories of thermoplastic elastomer.....	2
5.1 TPA.....	2
5.2 TPC.....	2
5.3 TPO.....	2
5.4 TPS.....	2
5.5 TPU.....	2
5.6 TPV.....	2
5.7 TPZ.....	2
6 Materials in each TPE category.....	3
6.1 TPA.....	3
6.2 TPC.....	3
6.3 TPO.....	3
6.4 TPS.....	3
6.5 TPU.....	4
6.6 TPV.....	4
6.7 Miscellaneous material (TPZ).....	4
Annex A (informative) Formerly used abbreviated terms.....	5
Bibliography.....	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 18064:2014), which has been technically revised.

The main changes are as follows:

- inclusion of TPO co-polymers;
- differentiation between single polymers and compounds;
- unification of expressions.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Thermoplastic elastomers combine many of the attributes and features of both vulcanized thermoset rubber and thermoplastic materials. It is, therefore, important that any system of classification and nomenclature for this rapidly expanding polymer sector be acceptable to both the rubber and plastics industries. Neither of the existing International Standards for the nomenclature and abbreviated terms for rubber (ISO 1629) and for plastics (ISO 1043-1) is suitable for this purpose. The system in this document has been devised to avoid any conflict or ambiguity, permit the use of existing terms in the construction of abbreviated terms for thermoplastic elastomers, and allow for future developments or expansion.

This document uses established abbreviated terms. Its aim is both to prevent the occurrence of more than one abbreviated term for a given thermoplastic elastomer term, and to prevent the interpretation of more than one meaning for a given abbreviated term. For this reason, this document makes appropriate use of the terms and symbols listed in ISO 1043-1 and ISO 1629.

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 18064:2022

Thermoplastic elastomers — Nomenclature and abbreviated terms

1 Scope

This document establishes a nomenclature system for thermoplastic elastomers based on the chemical composition of the polymer or polymers involved. It specifies symbols and abbreviated terms used to identify thermoplastic elastomers in industry, commerce, and government. It is not intended to conflict with, but to supplement, existing trade names and trademarks.

NOTE 1 The name of the thermoplastic elastomer is intended to be used in technical papers and presentations followed by the abbreviated term used to designate the elastomer in this document.

NOTE 2 [Annex A](#) gives thermoplastic-elastomer abbreviated terms that have been used in the past in materials standards, technical bulletins, textbooks, patents, and trade literature.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 1629, *Rubber and latices — Nomenclature*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

thermoplastic elastomer

TPE

polymer or blend of polymers that has properties at its service temperature similar to those of vulcanized rubber but can be processed and reprocessed at elevated temperature like a thermoplastic

Note 1 to entry: TPE are elastomers as specified in ISO 1382 and ISO 472. An elastomer shows recovery after elongation.

4 Nomenclature system

4.1 The prefix TP is used to indicate that the abbreviated term is for a thermoplastic elastomer and shall be followed by a letter representing each category of thermoplastic elastomer, as detailed in [Clause 5](#).

4.2 The abbreviated term for each category of thermoplastic elastomer shall be followed, after a hyphen, by a combination of symbols to describe a specific member of each category, as detailed in [Clause 6](#).

4.3 If the TPO and TPS are compounded with other polymers, “-M” is added after the letters describing the main polymer.

5 Categories of thermoplastic elastomer

5.1 TPA

Thermoplastic polyamide elastomer, consisting of a block copolymer of alternating hard and soft segments with amide chemical linkages in the hard segments and ester, ether or carbonate chemical linkages or mixtures of them in the soft segments.

5.2 TPC

Thermoplastic copolyester elastomer, consisting of a block copolymer of alternating hard segments and soft segments with ester linkages in the hard segments and ester, ether or carbonate chemical linkages or mixtures of them in the soft segments.

5.3 TPO

This category comprises the following two definitions:

Thermoplastic polyolefin elastomer, consisting of a block copolymer of alternating hard segments and soft segments where all segments have an olefinic or aliphatic structure.

Thermoplastic polyolefin elastomer mixture, consisting of a blend of a polyolefin and a conventional non-vulcanized rubber and the rubber phase in the blend having little or no crosslinking.

5.4 TPS

Thermoplastic polystyrene elastomer, consisting of at least a triblock copolymer of styrene and a specific diene, where the two end segments, i.e. the hard segments, are polystyrene and the internal soft segment is a polydiene or hydrogenated polydiene.

5.5 TPU

Thermoplastic polyurethane elastomer, consisting of a block copolymer of alternating hard and soft segments with urethane chemical linkages in the hard segments and ether, ester or carbonate chemical linkages or mixtures of them in the soft segments.

5.6 TPV

Thermoplastic elastomer vulcanizate, consisting of a blend of a thermoplastic material and a conventional rubber in which the rubber has been crosslinked by the process of dynamic vulcanization during the blending and mixing step.

5.7 TPZ

Unclassified thermoplastic elastomer, comprising a polymer compound by any composition or structure other than those grouped in TPA, TPC, TPO, TPS, TPU, and TPV.

6 Materials in each TPE category

6.1 TPA

The category of TPA is sub-categorized into groups according to the linkages in the soft segments. The following symbols are used:

TPA-EE soft segment with both ether and ester linkages;

TPA-ES polyester soft segment;

TPA-ET polyether soft segment;

TPA-CE polycarbonate soft segment.

6.2 TPC

The category of TPC is sub-categorized into groups according to the linkages in the soft segments. The following symbols are used:

TPC-EE soft segment with ester and ether linkages;

TPC-ES polyester soft segment;

TPC-ET polyether soft segment;

TPC-CE polycarbonate soft segment.

6.3 TPO

The category of TPO is sub-categorized into groups as follows:

A TPO block copolymer is represented by the suffix -C for “copolymer”.

A specific blended TPO (i.e. not a copolymer) is identified by a bracketed term comprising the standard abbreviated term for the thermoplastic type according to ISO 1043-1, a “+” sign and the standard abbreviated term for the rubber type according to ISO 1629.

Examples for TPO symbols are as follows:

TPO-C block copolymer;

TPO-M (PP+EPDM) polymer mixture, equivalent to blend, of polypropylene with ethylene-propylene-diene terpolymer, with no or little crosslinking of the EPDM phase.

6.4 TPS

This category is sub-categorized into fully-hydrogenated “TPS-H” or only partially and non-hydrogenated “-N”. The following symbols are used:

TPS-H fully-hydrogenated soft segment;

TPS-N partially or non-hydrogenated soft segment.

NOTE For the user it is not relevant to know which kind of copolymer is taken for the application. The highest impact on properties comes from the amount of unsaturated linkages.

6.5 TPU

The category of TPU is sub-categorized into types according to the aromatic or aliphatic nature of the urethane linkages of the hard segments, and according to the chemical linkages (ether, ester, carbonate) in the soft segments. The following symbols are used:

TPU-ARES	aromatic hard segment, polyester soft segment;
TPU-ARET	aromatic hard segment, polyether soft segment;
TPU-AREE	aromatic hard segment, soft segment with ester and ether linkages;
TPU-ARCE	aromatic hard segment, polycarbonate soft segment;
TPU-ALES	aliphatic hard segment, polyester soft segment;
TPU-ALET	aliphatic hard segment, polyether soft segment;
TPU-ALEE	aliphatic hard segment, soft segment with ester and ether linkages;
TPU-ALCE	aliphatic hard segment, polycarbonate soft segment.

NOTE The previous version of this document contained TPU-ARCL for caprolactone soft segment. This is incorporated into the ester TPU-ARES and ALES.

6.6 TPV

The category of TPV varies depending on the nature of the thermoplastic as continuous phase and the dispersed rubber component in the system.

A specific TPV is identified by a bracketed term comprising the standard abbreviated term for the thermoplastic type according to ISO 1043-1, followed by a "+" sign and the standard abbreviated term for the rubber according to ISO 1629.

Examples, for TPV type symbols are as follows:

TPV-(PP+ EPDM)	combination of EPDM and polypropylene in which the EPDM phase is highly crosslinked and finely dispersed in a continuous PP phase;
TPV-(PP+NBR)	combination of acrylonitrile-butadiene rubber and polypropylene in which the NBR phase is highly crosslinked and finely dispersed in a continuous PP phase;
TPV-(PA+ACM)	combination of acrylate rubber and polyamide in which the ACM phase is highly crosslinked and finely dispersed in a continuous PA phase;
TPV-(TPU+QR)	combination of silicone rubber and thermoplastic polyurethane in which the QR phase is highly cross-linked and finely dispersed in a continuous TPU phase.

NOTE The thermoplastic is put first to indicate that it has the main effect on the mechanical properties.

6.7 Miscellaneous material (TPZ)

These thermoplastic elastomers do not fit into any of the classes named above and are identified by the prefix TPZ, followed by the abbreviated term of the main polymer partners. The continuous phase is put first.

An example for a TPZ symbol is as follows:

TPZ-(PVC+NBR)	blend of polyvinyl chloride and acrylonitrile-butadiene rubber.
----------------------	---

Annex A (informative)

Formerly used abbreviated terms

Over the years, many different types of thermoplastic material have been developed and (partially) commercialized. In the past, different ways were used to describe the representatives of the different classes of these materials. Some of the terms used to describe the materials have been used in the literature and in patents. This has led to the situation in which today, the same material is known under different terms. In order to permit a smooth transition to the newly developed standardized way of describing thermoplastic materials and maintain the link with already existing literature, a number of formerly used terms and abbreviated terms are given in [Table A.1](#).

Table A.1 — Formerly used and corresponding new abbreviated terms

New terms used in this document		Terms still used in patents, literature and market	
Abbreviated term	Description	Abbreviated term	Description
TPA	Thermoplastic polyamide elastomer	TPE-A	Thermoplastic polyamide elastomer
TPC	Thermoplastic copolyester elastomer	TPE-E	Thermoplastic copolyester elastomer
TPO	Thermoplastic polyolefin elastomer	TPE-O	Thermoplastic polyolefin elastomer
TPS	Thermoplastic polystyrene elastomer	TPE-S	Thermoplastic polystyrene elastomer
TPU	Thermoplastic polyurethane elastomer	TPE-U	Thermoplastic polyurethane elastomer
TPV	Thermoplastic elastomer vulcanizate	TPE-V	Thermoplastic elastomer vulcanizate
		FCEA	Fully crosslinked elastomeric alloy
		HCTPV	Highly crosslinked thermoplastic vulcanizate
TPZ-(PVC+NBR)	Blend of NBR and PVC	NPV	NBR/PVC blend (old abbreviated term mainly used in India)
TPA	Thermoplastic polyamide elastomer	PEBA	Thermoplastic elastomer, polyether block amide
TPS-N	Thermoplastic polystyrene elastomer, non-hydrogenated	TPS-SBS	Styrene butadiene styrene block copolymer
		TPS-SIS	Styrene isoprene styrene block copolymer
TPS-H	Thermoplastic polystyrene elastomer, hydrogenated	TPS-SEBS	Styrene ethylene/butylene styrene block copolymer
		TPS-SEPS	Styrene ethylene/propylene styrene block copolymer
TPC	Thermoplastic copolyester elastomer	TEEE	Thermoplastic elastomer, ether-ester