

INTERNATIONAL
STANDARD

ISO
20932-1

First edition
2018-11

AMENDMENT 1

2021-10

**Textiles — Determination of the
elasticity of fabrics —**

**Part 1:
Strip tests**

AMENDMENT 1

Textiles — Détermination de l'élasticité des étoffes —

Partie 1: Essais sur bande

AMENDEMENT 1

STANDARDSISO.COM : Click to view the full PDF of ISO 20932-1:2018/Amd 1:2021



Reference number
ISO 20932-1:2018/Amd.1:2021(E)

© ISO 2021

STANDARDSISO.COM : Click to view the full PDF of ISO 20932-1:2018/Amd 1:2021



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 24, *Conditioning atmospheres and physical tests for textile fabrics*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 248, *Textiles and textile products*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 20932 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

STANDARDSISO.COM : Click to view the full PDF of ISO 20932-1:2018/Amd 1:2021

Textiles — Determination of the elasticity of fabrics —

Part 1: Strip tests

AMENDMENT 1

3.19

Replace the definition and note to entry with the following:

ratio of recovered extension of the test specimen after cycling (to a specified force or specified extension) to its initial length

Note 1 to entry The recovered elongation is the complement of the *permanent deformation* (3.18) to the *elongation* (3.11).

Note 2 to entry Recovered elongation is expressed as a percentage.

9.1.12

Replace the sentence with the following:

Set the extension and retraction rate of the specimen at 100 % of the initial length per minute. It means that, for examples, if the initial length is 100 mm, set up the rate at 100 mm/min; if the initial length is 200 mm, set up the rate at 200 mm/min.

Clause 11, a)

Replace item a) with the following:

a) Elongation, $S_{\%}$ expressed as a percentage, as shown in Formula (1):

$$S_{\%} = 100 \times \frac{E}{P} \quad (1)$$

where

E is the extension (mm), increase in length of the initial distance (mm) between applied reference marks at maximum force on the fifth cycle; or, in case a pretension is used, increase in length of the clamp distance (mm) from the initial length (mm) at maximum force on the fifth cycle;

P is the initial distance (mm) between applied reference marks; or, in case a pretension is used, the initial length (mm).

Clause 11, d)

Replace item d) with the following:

- d) Permanent deformation, C , expressed as a distance, and permanent deformation $C_{\%}$, expressed as a percentage, as shown in Formula (4) and in Formula (5), respectively:

$$C = Q - P \quad (4)$$

$$C_{\%} = 100 \times \frac{Q - P}{P} \quad (5)$$

where

Q is the distance (mm) between applied reference marks after the measurement and specified recovery period; or, in case a pretension is used, the final clamp distance (mm) at pretension after a specified recovery period;

P is the initial distance (mm) between applied reference marks; or, in case a pretension is used, the initial length (mm)."

Clause 11, e)

Replace item e) with the following:

- e) Recovered extension, D , expressed as a distance, and recovered elongation $D_{\%}$, expressed as a percentage, as shown in Formula (6) and in Formula (7), respectively:

$$D = E - C \quad (6)$$

$$D_{\%} = 100 \times \frac{E - C}{P} \quad (7)$$

where

E is the extension (mm) as measured in 11, a);

C is the permanent deformation (mm) as calculated in 11, d);

P is the initial distance (mm) between applied reference marks; or, in case a pretension is used, the initial length (mm).