

NFPA[®]

290

**Standard for Fire Testing of
Passive Protection Materials
for Use on LP-Gas Containers**

2018



IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA® STANDARDS

NOTICE AND DISCLAIMER OF LIABILITY CONCERNING THE USE OF NFPA STANDARDS

NFPA® codes, standards, recommended practices, and guides (“NFPA Standards”), of which the document contained herein is one, are developed through a consensus standards development process approved by the American National Standards Institute. This process brings together volunteers representing varied viewpoints and interests to achieve consensus on fire and other safety issues. While the NFPA administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in NFPA Standards.

The NFPA disclaims liability for any personal injury, property, or other damages of any nature whatsoever, whether special, indirect, consequential or compensatory, directly or indirectly resulting from the publication, use of, or reliance on NFPA Standards. The NFPA also makes no guaranty or warranty as to the accuracy or completeness of any information published herein.

In issuing and making NFPA Standards available, the NFPA is not undertaking to render professional or other services for or on behalf of any person or entity. Nor is the NFPA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

The NFPA has no power, nor does it undertake, to police or enforce compliance with the contents of NFPA Standards. Nor does the NFPA list, certify, test, or inspect products, designs, or installations for compliance with this document. Any certification or other statement of compliance with the requirements of this document shall not be attributable to the NFPA and is solely the responsibility of the certifier or maker of the statement.

REVISION SYMBOLS IDENTIFYING CHANGES FROM THE PREVIOUS EDITION

Text revisions are shaded. A **Δ** before a section number indicates that words within that section were deleted and a **Δ** to the left of a table or figure number indicates a revision to an existing table or figure. When a chapter was heavily revised, the entire chapter is marked throughout with the **Δ** symbol. Where one or more sections were deleted, a **•** is placed between the remaining sections. Chapters, annexes, sections, figures, and tables that are new are indicated with an **N**.

Note that these indicators are a guide. Rearrangement of sections may not be captured in the markup, but users can view complete revision details in the First and Second Draft Reports located in the archived revision information section of each code at www.nfpa.org/docinfo. Any subsequent changes from the NFPA Technical Meeting, Tentative Interim Amendments, and Errata are also located there.

REMINDER: UPDATING OF NFPA STANDARDS

Users of NFPA codes, standards, recommended practices, and guides (“NFPA Standards”) should be aware that NFPA Standards may be amended from time to time through the issuance of a Tentative Interim Amendment (TIA) or corrected by Errata. An official NFPA Standard at any point in time consists of the current edition of the document together with any TIAs and Errata then in effect.

To determine whether an NFPA Standard has been amended through the issuance of Tentative Interim Amendments or corrected by Errata, go to www.nfpa.org/docinfo to choose from the list of NFPA Standards or use the search feature to select the NFPA Standard number (e.g., NFPA 13). The document information page provides up-to-date document-specific information as well as postings of all existing TIAs and Errata. It also includes the option to register for an “Alert” feature to receive an automatic email notification when new updates and other information are posted regarding the document.

IMPORTANT NOTICES AND DISCLAIMERS CONCERNING NFPA® STANDARDS

ADDITIONAL NOTICES AND DISCLAIMERS

Updating of NFPA Standards

Users of NFPA codes, standards, recommended practices, and guides (“NFPA Standards”) should be aware that these documents may be superseded at any time by the issuance of new editions or may be amended from time to time through the issuance of Tentative Interim Amendments or corrected by Errata. An official NFPA Standard at any point in time consists of the current edition of the document together with any Tentative Interim Amendments and any Errata then in effect. In order to determine whether a given document is the current edition and whether it has been amended through the issuance of Tentative Interim Amendments or corrected through the issuance of Errata, consult appropriate NFPA publications such as the National Fire Codes® Subscription Service, visit the NFPA website at www.nfpa.org, or contact the NFPA at the address listed below.

Interpretations of NFPA Standards

A statement, written or oral, that is not processed in accordance with Section 6 of the Regulations Governing the Development of NFPA Standards shall not be considered the official position of NFPA or any of its Committees and shall not be considered to be, nor be relied upon as, a Formal Interpretation.

Patents

The NFPA does not take any position with respect to the validity of any patent rights referenced in, related to, or asserted in connection with an NFPA Standard. The users of NFPA Standards bear the sole responsibility for determining the validity of any such patent rights, as well as the risk of infringement of such rights, and the NFPA disclaims liability for the infringement of any patent resulting from the use of or reliance on NFPA Standards.

NFPA adheres to the policy of the American National Standards Institute (ANSI) regarding the inclusion of patents in American National Standards (“the ANSI Patent Policy”), and hereby gives the following notice pursuant to that policy:

NOTICE: The user’s attention is called to the possibility that compliance with an NFPA Standard may require use of an invention covered by patent rights. NFPA takes no position as to the validity of any such patent rights or as to whether such patent rights constitute or include essential patent claims under the ANSI Patent Policy. If, in connection with the ANSI Patent Policy, a patent holder has filed a statement of willingness to grant licenses under these rights on reasonable and nondiscriminatory terms and conditions to applicants desiring to obtain such a license, copies of such filed statements can be obtained, on request, from NFPA. For further information, contact the NFPA at the address listed below.

Law and Regulations

Users of NFPA Standards should consult applicable federal, state, and local laws and regulations. NFPA does not, by the publication of its codes, standards, recommended practices, and guides, intend to urge action that is not in compliance with applicable laws, and these documents may not be construed as doing so.

Copyrights

NFPA Standards are copyrighted. They are made available for a wide variety of both public and private uses. These include both use, by reference, in laws and regulations, and use in private self-regulation, standardization, and the promotion of safe practices and methods. By making these documents available for use and adoption by public authorities and private users, the NFPA does not waive any rights in copyright to these documents.

Use of NFPA Standards for regulatory purposes should be accomplished through adoption by reference. The term “adoption by reference” means the citing of title, edition, and publishing information only. Any deletions, additions, and changes desired by the adopting authority should be noted separately in the adopting instrument. In order to assist NFPA in following the uses made of its documents, adopting authorities are requested to notify the NFPA (Attention: Secretary, Standards Council) in writing of such use. For technical assistance and questions concerning adoption of NFPA Standards, contact NFPA at the address below.

For Further Information

All questions or other communications relating to NFPA Standards and all requests for information on NFPA procedures governing its codes and standards development process, including information on the procedures for requesting Formal Interpretations, for proposing Tentative Interim Amendments, and for proposing revisions to NFPA standards during regular revision cycles, should be sent to NFPA headquarters, addressed to the attention of the Secretary, Standards Council, NFPA, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101; email: stds_admin@nfpa.org.

For more information about NFPA, visit the NFPA website at www.nfpa.org. All NFPA codes and standards can be viewed at no cost at www.nfpa.org/docinfo.

Copyright © 2017 National Fire Protection Association®. All Rights Reserved.

NFPA® 290

Standard for

Fire Testing of Passive Protection Materials for Use on LP-Gas Containers

2018 Edition

This edition of NFPA 290, *Standard for Fire Testing of Passive Protection Materials for Use on LP-Gas Containers*, was prepared by the Technical Committee on Fire Tests. It was issued by the Standards Council on July 28, 2017, with an effective date of August 18, 2017, and supersedes all previous editions.

This edition of NFPA 290 was approved as an American National Standard on August 18, 2017.

Origin and Development of NFPA 290

Although the 2003 edition was the first edition of NFPA 290, *Fire Testing of Passive Protection Materials for Use on LP-Gas Containers*, a test procedure for torch fire and hose stream testing of thermal insulating systems for LP-Gas containers has been included as an annex to NFPA 58, *Liquefied Petroleum Gas Code*, since the 1986 edition of that code. That test method was developed by the Technical Committee on Fire Tests at the request of the Technical Committee on Liquefied Petroleum Gases as a result of numerous BLEVE incidents that had occurred in previous years. In the mid-1990s, the test procedure saw greater use, particularly outside the United States, and the two technical committees agreed that it should be developed and maintained as a fire test standard under the scope of the Fire Test Committee rather than as an annex to NFPA 58.

The 2003 edition of NFPA 290 represented a refinement of the test procedure that previously appeared as an appendix to NFPA 58, and it reorganized the procedure as a stand-alone fire test standard using mandatory language in accordance with the *Manual of Style for NFPA Technical Committee Documents*.

The 2009 edition contained revisions to clarify its scope and purpose and a revised definition of the term *passive fire protection material*.

No major changes were made in 2013.

The 2018 edition has been updated to reference the most up-to-date standards and terminology.

Technical Committee on Fire Tests

Barry L. Badders, Jr., *Chair*
Intertek Testing Services, TX [RT]

Scott W. Adams, Park City Fire Service District, UT [E]
Farid Alfawakhiri, American Iron and Steel Institute, IL [M]
James A. Burns, New York State Department, NY [E]
 Rep. Firemen's Association of the State of New York
Karen C. Carpenter, Southwest Research Institute, TX [RT]
Gordon H. Damant, Inter-City Testing & Consulting Corp. of California, CA [SE]
Rick D. Davis, National Institute of Standards & Technology, MD [RT]
Scott E. Dillon, Crane Engineering, MN [SE]
William E. Fitch, Phyrefish.com, FL [SE]
Richard G. Gann, Gaithersburg, MD [SE]
Marcelo M. Hirschler, GBH International, CA [SE]
Paul A. Hough, Armstrong World Industries, Inc., PA [M]
William E. Koffel, Koffel Associates, Inc., MD [SE]
Sergei V. Levchik, Israel Chemicals Ltd. (ICL-IP), NY [M]
 Rep. ACC-North American Flame Retardant Alliance

James Andrew Lynch, The Fire Solutions Group, PA [SE]
John Martell, Professional Fire Fighters of Maine/IAFF, ME [L]
 Rep. International Association of Fire Fighters
Rodney A. McPhee, Canadian Wood Council, Canada [M]
Kathleen A. Newman, Firetect, CA [M]
Arthur J. Parker, JENSEN HUGHES, MD [SE]
Michael L. Savage, Sr., City of Rio Rancho, NM [E]
Michael Schmeida, Gypsum Association, OH [M]
David T. Sheppard, U.S. Bureau of Alcohol, Tobacco, Firearms & Explosives, MD [RT]
Dwayne E. Sloan, UL LLC, NC [RT]
Stanislav I. Stoliarov, University of Maryland, MD [SE]
Kuma Sumathipala, American Wood Council, VA [M]
Dong Zeng, FM Global, MA [I]
 Rep. FM Global

Alternates

Erik H. Anderson, Koffel Associates, Inc., MD [SE]
 (Alt. to William E. Koffel)
Jesse J. Beitel, JENSEN HUGHES, MD [SE]
 (Alt. to Arthur J. Parker)
Richard J. Davis, FM Global, MA [I]
 (Alt. to Dong Zeng)
Timothy Earl, GBH International, MI [SE]
 (Alt. to Marcelo M. Hirschler)
Sam W. Francis, American Wood Council, PA [M]
 (Alt. to Kuma Sumathipala)
Stephen Paul Fuss, U.S. Bureau of Alcohol, Tobacco, Firearms & Explosives, MD [RT]
 (Alt. to David T. Sheppard)
Justin A. Geiman, Fire and Risk Alliance LLC, MD [SE]
 (Alt. to James Andrew Lynch)

Karl Dana Houser, Intertek, PA [RT]
 (Alt. to Barry L. Badders, Jr.)
Marc L. Janssens, Southwest Research Institute, TX [RT]
 (Alt. to Karen C. Carpenter)
Ineke Van Zeeland, Canadian Wood Council, Canada [M]
 (Alt. to Rodney A. McPhee)
Matthew T. Vinci, International Association of Fire Fighters, DC [L]
 (Alt. to John Martell)
Robert J. Wills, American Iron and Steel Institute, AL [M]
 (Alt. to Farid Alfawakhiri)
Luke C. Woods, UL LLC, MA [RT]
 (Alt. to Dwayne E. Sloan)
Joe Ziolkowski, American Furniture Manufacturers Association, NC [M]
 Voting Alternate

Nonvoting

Robert H. Barker, American Fiber Manufacturers Association, VA [M]
 Rep. American Fiber Manufacturers Association
Rohit Khanna, U.S. Consumer Product Safety Commission, MD [C]
 Rep. U.S. Consumer Product Safety Commission

Andrew Lock, U.S. Consumer Product Safety Commission, MD [C]
 Rep. US Consumer Product Safety Commission

Tracy L. Vecchiarelli, NFPA Staff Liaison

This list represents the membership at the time the Committee was balloted on the final text of this edition. Since that time, changes in the membership may have occurred. A key to classifications is found at the back of the document.

NOTE: Membership on a committee shall not in and of itself constitute an endorsement of the Association or any document developed by the committee on which the member serves.

Committee Scope: This Committee shall have primary responsibility for documents on fire testing procedures, for reviewing existing fire test standards and recommending appropriate action to NFPA, for recommending the application of and advising on the interpretation of acceptable test standards for fire problems of concern to NFPA technical committees and members, and for acting in a liaison capacity between NFPA and the committees of other organizations writing fire test standards. This Committee does not cover fire tests that are used to evaluate extinguishing agents, devices, or systems.

Contents

Chapter 1 Administration	290- 4	Chapter 6 Test Location	290- 6
1.1 Scope.	290- 4	6.1 Environmental Effects.	290- 6
1.2 Purpose.	290- 4	6.2 Air Temperature.	290- 6
1.3 Application.	290- 4	6.3 Wind Limitations.	290- 6
1.4 Units and Formulas.	290- 4	6.4 Adverse Weather.	290- 6
Chapter 2 Referenced Publications	290- 4	Chapter 7 Conduct of Tests	290- 6
2.1 General.	290- 4	7.1 Test Assembly.	290- 6
2.2 NFPA Publications. (Reserved)	290- 4	7.2 Calibration Test.	290- 6
2.3 Other Publications.	290- 5	7.3 Conduct of Torch Test.	290- 6
2.4 References for Extracts in Mandatory Sections. (Reserved)	290- 5	7.4 Hose Stream Test.	290- 6
Chapter 3 Definitions	290- 5	7.5 Conditions of Acceptance.	290- 7
3.1 General.	290- 5	7.6 Environmental Conditions.	290- 7
3.2 NFPA Official Definitions.	290- 5	7.7 Measurements.	290- 7
3.3 General Definitions.	290- 5	7.8 Observations.	290- 7
Chapter 4 Test Specimens	290- 5	7.9 Photographs.	290- 7
4.1 Construction of Test Specimen.	290- 5	7.10 Video.	290- 7
4.2 Construction of Rear Box.	290- 5	Chapter 8 Presentation of Results	290- 7
4.3 Passive Fire Protection (PFP) Material.	290- 5	8.1 Test Report.	290- 7
Chapter 5 Torch Fire	290- 6	Annex A Explanatory Material	290- 8
5.1 Torch Fire Nozzle.	290- 6	Annex B Informational References	290- 8
5.2 Torch Fire Exposure.	290- 6	Index	290- 9
5.3 Fuel.	290- 6		

NFPA 290

Standard for

Fire Testing of Passive Protection Materials for
Use on LP-Gas Containers

2018 Edition

IMPORTANT NOTE: This NFPA document is made available for use subject to important notices and legal disclaimers. These notices and disclaimers appear in all publications containing this document and may be found under the heading "Important Notices and Disclaimers Concerning NFPA Standards." They can also be viewed at www.nfpa.org/disclaimers or obtained on request from NFPA.

UPDATES, ALERTS, AND FUTURE EDITIONS: New editions of NFPA codes, standards, recommended practices, and guides (i.e., NFPA Standards) are released on scheduled revision cycles. This edition may be superseded by a later one, or it may be amended outside of its scheduled revision cycle through the issuance of Tentative Interim Amendments (TIAs). An official NFPA Standard at any point in time consists of the current edition of the document, together with all TIAs and Errata in effect. To verify that this document is the current edition or to determine if it has been amended by TIAs or Errata, please consult the National Fire Codes® Subscription Service or the "List of NFPA Codes & Standards" at www.nfpa.org/docinfo. In addition to TIAs and Errata, the document information pages also include the option to sign up for alerts for individual documents and to be involved in the development of the next edition.

NOTICE: An asterisk (*) following the number or letter designating a paragraph indicates that explanatory material on the paragraph can be found in Annex A.

A reference in brackets [] following a section or paragraph indicates material that has been extracted from another NFPA document. As an aid to the user, the complete title and edition of the source documents for extracts in mandatory sections of the document are given in Chapter 2 and those for extracts in informational sections are given in Annex B. Extracted text may be edited for consistency and style and may include the revision of internal paragraph references and other references as appropriate. Requests for interpretations or revisions of extracted text shall be sent to the technical committee responsible for the source document.

Information on referenced publications can be found in Chapter 2 and Annex B.

Chapter 1 Administration

1.1* Scope. The test described in this procedure shall be used to determine the fire resistance of passive fire protection (PFP) materials applied to the exterior of LP-Gas containers.

1.2 Purpose. This test is designed to evaluate the fire resistance of passive fire protection (PFP) materials in a torch fire environment created by the rupture of a nearby storage vessel.

1.2.1* This test procedure subjects an insulated steel plate, simulating an LP-Gas storage vessel, to a torch fire exposure for 50 minutes. After 20 minutes of the torch fire exposure, the insulated steel plate is subjected simultaneously to the torch fire exposure and a hose stream for 10 minutes.

1.3 Application.

1.3.1 This procedure shall be a test of materials and not a test of assemblies. If necessary, additional testing shall be performed to determine the effectiveness of the material protecting a particular assembly or fabrication.

1.3.2* Although the test has been designed to reproduce conditions similar to those found in fires resulting from realistic releases of hydrocarbons, this test does not guarantee a specific degree of protection from the myriad of possible fires involving LP-Gas storage vessels or containers.

1.3.3 The test involves hazardous materials and operations.

1.3.3.1 The procedure does not address all of the safety problems associated with its use.

1.3.3.2 It shall be the responsibility of the user of the procedure to establish the safety and health practices and determine the applicability of regulatory limitations before use.

1.3.3.3 It shall be the responsibility of the supplier to inform the testing laboratory of any dangerous properties of the material to be tested, fumes given off during testing, and the residues after testing.

1.3.4 Although the test specified has been designed to simulate some of the conditions that occur in an actual LP-Gas-fueled torch fire, it does not reproduce them all exactly.

1.3.4.1 The results of this test do not guarantee safety but can be used as elements of a fire hazard or fire risk assessment for structures or plants.

1.3.4.2 The fire hazard or fire risk assessment shall also take into account all the other factors that are pertinent to an assessment of the fire hazard for a particular end use.

1.3.5 This test does not offer an assessment of other properties of the passive fire protection material such as weathering, aging, shock resistance, impact or explosion resistance, flame spread, or smoke production.

1.4 Units and Formulas.

1.4.1 SI Units. Metric units of measurement in this standard are in accordance with the modernized metric system known as the International System of Units (SI).

1.4.2 Primary Values. The SI value for a measurement and the equivalent inch-pound value given in parentheses shall each be acceptable for use as primary units for satisfying the requirements of this standard.

Chapter 2 Referenced Publications

2.1 General. The documents or portions thereof listed in this chapter are referenced within this standard and shall be considered part of the requirements of this document.

2.2 NFPA Publications. (Reserved)

2.3 Other Publications.

2.3.1 ANSI/UL Publications. Underwriters Laboratories Inc., 333 Pfingsten Road, Northbrook, IL 60062-2096.

ANSI/UL 385, *Standard for Safety Play Pipes for Water Supply Testing in Fire Protection Service*, 2005, revised 2015.

2.3.2 Other Publications.

Merriam-Webster's Collegiate Dictionary, 11th edition, Merriam-Webster, Inc., Springfield, MA, 2003.

2.4 References for Extracts in Mandatory Sections. (Reserved)

Chapter 3 Definitions

3.1 General. The definitions contained in this chapter shall apply to the terms used in this standard. Where terms are not defined in this chapter or within another chapter, they shall be defined using their ordinarily accepted meanings within the context in which they are used. *Merriam-Webster's Collegiate Dictionary*, 11th edition, shall be the source for the ordinarily accepted meaning.

3.2 NFPA Official Definitions.

3.2.1 Shall. Indicates a mandatory requirement.

3.2.2 Should. Indicates a recommendation or that which is advised but not required.

3.2.3 Standard. An NFPA Standard, the main text of which contains only mandatory provisions using the word “shall” to indicate requirements and which is in a form generally suitable for mandatory reference by another standard or code or for adoption into law. Nonmandatory provisions are not to be considered a part of the requirements of a standard and shall be located in an appendix, annex, footnote, informational note, or other means as permitted in the NFPA Manuals of Style. When used in a generic sense, such as in the phrase “standards development process” or “standards development activities,” the term “standards” includes all NFPA Standards, including Codes, Standards, Recommended Practices, and Guides.

3.3 General Definitions.

3.3.1 Fire Resistance. The measure of the ability of a material, product, or assembly to withstand fire or give protection from it.

3.3.2* Passive Fire Protection (PFP) Material. A material that is applied to a substrate and designed to protect it from the thermal effects of a fire.

3.3.2.1 Passive Fire Protection — Coating Material. A material that is applied to a substrate and is designed to protect it from thermal effects.

3.3.2.2 Passive Fire Protection — Panel Material. A material in the form of a panel or sheet, including pre-formed components, that is designed to stand alone prior to application to a steel substrate.

3.3.3 Rear Box. A mild steel box, open at the front and back, that is designed to be attached to the rear of the test specimen to shield it from environmental influences.

3.3.4 Torch Fire. An ignited discharge of propane vapors under pressure.

Chapter 4 Test Specimens

4.1 Construction of Test Specimen.

4.1.1 Two test specimens shall be required to conduct this test.

4.1.2 One test specimen shall be an uninsulated steel plate used for calibration of the propane torch fire exposure.

4.1.3 A second test specimen shall be a steel plate thermally protected with the insulation material at the thickness, density, and installation techniques being evaluated.

4.1.4 The test specimen dimensions shall not be less than 1.2 m × 1.2 m (4 ft × 4 ft) by nominal 16 mm ($\frac{5}{8}$ in.) thick.

4.1.5 The test specimens shall be constructed using a steel plate with thermal properties equivalent to ASME pressure vessel steel.

4.1.6 Multiple insulated test specimens shall be permitted to be evaluated in a single test program, provided the test specimens are tested consecutively.

4.1.7 The test specimen shall be mounted on a steel-plate holder such that the exposed face of the test specimen is not shielded in any way by the test specimen fixture.

4.1.8 The steel-plate holder shall be constructed in such a manner that the only heat transfer to the backside of the plate is by heat conduction through the plate and not by any other heat paths.

4.1.9 The test specimen shall be mounted vertically.

4.1.10 The rear box shall be installed to the unexposed face of the test specimen in a manner such that all joints are gastight.

4.2 Construction of Rear Box.

4.2.1 All tests require fitting the rear box to the unexposed side of the test specimen to shield the unexposed face from environmental influences.

4.2.2 The rear box shall be constructed from mild steel a minimum of 10 mm ($\frac{3}{8}$ in.) thick.

4.2.3 The rear box shall be open at the front and back and flanged at the front to allow fitting to the rear of the test specimen with no significant air gaps.

4.2.4 The internal dimensions of the rear box shall match the dimensions of the test specimen and be a minimum of 1 m (3 ft) deep.

4.3 Passive Fire Protection (PFP) Material.

4.3.1 Documentation of the method of preparation of the test specimen and the application details of the PFP material shall be provided to the test laboratory in advance of the test.

4.3.2 The test laboratory shall include this information in the test report.

Chapter 5 Torch Fire

5.1 Torch Fire Nozzle. The propane vapor shall be issued from a nozzle capable of meeting the requirements of this test standard.

5.2 Torch Fire Exposure.

5.2.1 The flame temperature from the torch fire shall be $1200^{\circ}\text{C} \pm 60^{\circ}\text{C}$ ($2200^{\circ}\text{F} \pm 140^{\circ}\text{F}$) for the duration of the test.

5.2.2 The velocity of the torch fire at the exposed face of the test specimen shall be $64 \text{ km/hr} \pm 16 \text{ km/hr}$ ($40 \text{ mph} \pm 10 \text{ mph}$) for the duration of the test.

5.2.3 The tip of the discharge nozzle shall be aimed horizontally perpendicular and centered such that the apex of the flame shall be directed to impinge on the geometric center of the test specimen.

5.2.4 The tip of the discharge nozzle shall be positioned at a distance from the exposed face of the test specimen to achieve the temperature and velocity requirements specified in 5.2.1 and 5.2.2.

5.3 Fuel.

5.3.1 The fuel shall be a propane fuel delivered as a vapor, without a liquid fraction, at a steady flow rate such that the requirements of 5.2.1 and 5.2.2 are met.

5.3.2 There shall be a means of controlling and monitoring the fuel flow of the propane fuel during the torch test.

Chapter 6 Test Location

6.1 Environmental Effects. The test shall be carried out in a test location such that environmental effects are minimized.

6.2 Air Temperature. The ambient air temperature at the start of the test shall be between -10°C and 41°C (14°F and 105°F).

6.3 Wind Limitations. The wind conditions for tests conducted outdoors shall be less than 16 km/hr (10 mph) for the duration of the test.

6.4 Adverse Weather. Tests shall not be conducted outdoors during periods of rain or fog or other adverse weather conditions that could affect the outcome of the test.

Chapter 7 Conduct of Tests

7.1 Test Assembly.

7.1.1 The test specimen shall be adequately restrained in the test specimen fixture throughout the torch and hose stream tests.

7.1.2 The test duration shall be a minimum of 50 minutes.

7.2 Calibration Test.

7.2.1 Prior to evaluating the performance of the thermal insulation system, the torch impingement shall be calibrated as described in 7.2.2 through 7.2.7.

7.2.2 An uninsulated steel plate, as described in Section 4.1, shall be installed in the steel-plate holder.

7.2.3* The unexposed face of the uninsulated steel plate shall be instrumented with not fewer than nine thermocouples.

7.2.4 The thermocouples attached to the unexposed face of the test specimen shall be divided into nine equal squares with a thermocouple affixed to the center of each square.

7.2.5 Before exposure to the torch fire, none of the thermocouple readings on the unexposed side of the steel plate shall indicate a plate temperature in excess of 38°C (100°F) or less than 0°C (32°F).

7.2.6 Temperature measurements shall be monitored during the course of the calibration test and recorded at intervals not exceeding 30 seconds.

7.2.7 A calibration test shall be deemed successful when two of the nine thermocouples record unexposed face temperatures of 427°C (800°F) within $4 \text{ minutes} \pm 0.5 \text{ minute}$ from the start of the test.

7.3 Conduct of Torch Test.

7.3.1 A thermal insulation system shall be tested in the torch environment described in Section 7.2 in the manner described in 7.3.1.1 through 7.3.1.8.

7.3.1.1 The thermal insulation system shall be applied to the exposed side of a steel plate identical to that used during the calibration test described in Section 7.2.

7.3.1.2 The unexposed side of the steel plate shall be instrumented with a minimum of nine thermocouples placed as described in 7.2.3 to record the thermal response of the steel plate.

7.3.1.3 Before exposure to the torch fire, none of the thermocouple readings on the unexposed side of the insulated steel plate shall indicate a plate temperature in excess of 38°C (100°F) or less than 0°C (32°F).

7.3.1.4 The entire surface of the thermal insulation system shall be exposed to the torch fire environment.

7.3.1.5 The test specimen shall be exposed to the torch fire environment described in Section 7.2.

7.3.1.6 The insulated test specimen shall be exposed to the torch fire for 50 minutes.

7.3.1.7 Twenty minutes into the torch test, a hose stream test shall be conducted concurrently, as described in Section 7.4, for 10 minutes.

7.3.1.8 Subsequent to the application of the hose stream, the torch test shall continue until any thermocouple on the unexposed face of the steel plate indicates a plate temperature in excess of 427°C (800°F) or until a total test time of 50 minutes has elapsed.

7.4 Hose Stream Test.

7.4.1 During the torch test, the insulated test specimen shall be exposed to a hose stream test.

7.4.2 After 20 minutes of exposure to the torch test, the test specimen shall be exposed to a hose stream test.

7.4.3 The hose stream test shall be conducted concurrently with the torch test for a period of 10 minutes.

7.4.4 The hose stream shall be delivered through a 64 mm (2 in.) diameter hose discharging through a National Standard play pipe as specified in ANSI/UL 385, *Standard for Safety Play Pipes for Water Supply Testing in Fire Protection Service*.

7.4.4.1 The play pipe shall have an overall length of 762 mm (30 in.) and shall be equipped with a 28 mm (1 $\frac{1}{8}$ in.) diameter discharge tip of the standard-taper, smooth bore pattern without shoulder at the orifice.

7.4.4.2 The play pipe shall be fitted with a 64 mm (2 in.) inside diameter by 152 mm (6 in.) long nipple mounted between the hose and the base of the play pipe.

7.4.4.3 The pressure tap for measuring the water pressure at the base of the nozzle shall be normal to the surface of the nipple, centered in its length.

7.4.4.4 The pressure tap shall not protrude into the water stream.

7.4.4.5 The water pressure shall be measured with a pressure gauge [as a minimum 0 kPa to 345 kPa (0 psi to 50 psi)] graduated in no more than 13.8 kPa (2 psi) increments.

7.4.5 The gauge water pressure at the base of the nozzle and for the duration of the hose stream test shall be 207 kPa (30 psi).

7.4.5.1 The estimated delivery rate of water shall be 776 L/min (205 gpm) or 7760 L (2050 gal) over the 10-minute hose stream test.

7.4.6 Nozzle Distance. The nozzle orifice shall be located 6 m (20 ft) from and on a line normal to the center of the exposed surface of the test specimen.

7.4.6.1 If the nozzle cannot be located normal to the surface of the test specimen, the nozzle shall be on a line deviating not to exceed 30 degrees from the line normal to the center of the test specimen.

7.4.6.2 When so located, the distance from the center of the test specimen shall be less than 6 m (20 ft) by an amount equal to 0.3 m (1 ft) for each 10 degrees of deviation from the normal.

7.4.7 The hose stream shall be directed first at the middle of the test specimen and then at all parts of the exposed surface, making changes in direction slowly.

7.5 Conditions of Acceptance. None of the thermocouples on the unexposed side of the steel plate shall indicate a temperature in excess of 427°C (800°F) for a period of 50 minutes.

7.6 Environmental Conditions.

7.6.1 Environmental conditions shall be measured immediately before the test, and any significant changes during the test shall be noted.

7.6.2 The ambient temperature shall be measured. For tests conducted outdoors, wind speed and direction shall also be measured. Observations shall also be made of the weather, to indicate whether it is sunny or cloudy or whether there is any precipitation.

7.7 Measurements. A steady flow rate of propane vapor shall be required.

7.7.1 When the torch fire first impinges on the test specimen, a timer shall be started and the flow rate, temperatures, and pressures shall be monitored.

7.7.2 Readings of the instruments shall be taken at least once every 30 seconds.

7.7.3 The tests shall continue until either the time or temperature selected prior to the test is reached.

7.8 Observations.

7.8.1 Observations of significant details of the behavior and appearance of the test specimen during the test and after the torch fire is extinguished shall be recorded.

7.8.2 Information on deformation, spalling, cracking, and burning of the PFP material and continuance of flaming shall be noted.

7.9 Photographs.

7.9.1 Photographs of the test specimen shall be taken prior to and as soon as is practicable after the torch test has been extinguished.

7.9.2 The photographs described in 7.9.1 shall be included in the test report.

7.10 Video. A video record shall be made of the test.

Chapter 8 Presentation of Results

8.1 Test Report. A test report shall be produced and shall include the following information:

- (1) Name of the testing laboratory and the test date.
- (2) Names of the sponsor/customer, the manufacturer, and the product.
- (3) Documentation of how and when the test specimen was prepared, details of the application of the PFP material, and the name of the applicator company.
- (4) A description of the test specimen, including measurements of the thickness of passive fire protection material and the hardness, if measured. The mean, standard deviation, and range of measurements of thickness shall be given.
- (5) Record of test details, as follows:
 - (a) Ambient conditions.
 - (b) Record of the fuel pressure and temperature at least every 30 seconds throughout the test, where these are used to calculate mass flow rate, and the method of control and calculation.
 - (c) Record of fuel mass flow rate at least every 30 seconds throughout the test and total mass of fuel used.
 - (d) For reacting materials, the thickness of unreacted or partially reacted material left at the end of the test and the char thickness at the positions where the initial thickness was measured. The condition of the char and the strength of bonding to the underlying material shall be recorded.
 - (e) For materials restrained/supported by a reinforcing mesh, the condition of the mesh at the end of the test.

- (6) The test result, in the following format:
- (a) The behavior and appearance of the test specimen during and after the test and photographs, as detailed in Section 7.8 and Section 7.9.
 - (b) Temperature/time plots and tables of temperatures at least every 30 seconds for each thermocouple.
 - (c) Record of the maximum temperature and the time it occurs for each thermocouple.
 - (d) Statement as to the material's performance with respect to the conditions of acceptance.

Annex A Explanatory Material

Annex A is not a part of the requirements of this NFPA document but is included for informational purposes only. This annex contains explanatory material, numbered to correspond with the applicable text paragraphs.

- Δ A.1.1** Thermal protection insulating systems are allowed for use on LP-Gas containers as a means of “Special Protection” in NFPA 58 and NFPA 59. These standards have required that these materials undergo thermal performance testing as a precondition for acceptance. The intent of this testing procedure is to identify insulation systems that retard or prevent the release of the container's contents in a fire environment of 50 minutes' duration and that will resist a concurrent hose stream of 10 minutes' duration.

This test method provides a replacement for the test as described in Annex H of NFPA 58 and referenced in NFPA 59.

A.1.2.1 The torch exposure simulates the high temperature and erosive effects of a high-pressure jet of burning fuel vapor issuing from a nearby ruptured LP-Gas storage vessel. The hose stream simulates a fire fighter hose stream impingement on the insulated steel tank.

A.1.3.2 This test is an evaluation based on a “torching” type fire exposure. Other fire exposures such as a pool fire are a potential concern. It is believed, however, that the “torching”

test is a worst-case fire scenario because of the high-temperature exposure coupled with the erosive effects of the high-velocity flame.

A.3.3.2 Passive Fire Protection (PFP) Material. Passive fire protection materials can be in the form of coatings or in the form of panels or sheets, including preformed components, that are designed to stand alone prior to application to a substrate.

A.7.2.3 Thermocouples can be attached to the steel plate via several methods. One such method is to weld the individual thermocouple leads directly to the steel plate, with the individual leads separated by 6 mm (¼ in.) or less. Another method is to “peen” the thermocouples in place. This entails drilling a small diameter indentation into the steel plate. This indentation is less than the diameter of the thermocouple bead. The thermocouple bead is placed in the indentation, and the surrounding metal is “peened” over the thermocouple bead to secure it in place.

Annex B Informational References

B.1 Referenced Publications. The documents or portions thereof listed in this annex are referenced within the informational sections of this standard and are not part of the requirements of this document unless also listed in Chapter 2 for other reasons.

B.1.1 NFPA Publications. National Fire Protection Association, 1 Batterymarch Park, Quincy, MA 02169-7471.

NFPA 58, *Liquefied Petroleum Gas Code*, 2017 edition.

NFPA 59, *Utility LP-Gas Plant Code*, 2018 edition.

B.1.2 Other Publications. (Reserved)

B.2 Informational References. (Reserved)

B.3 References for Extracts in Informational Sections. (Reserved)

Index

Copyright © 2017 National Fire Protection Association. All Rights Reserved.

The copyright in this index is separate and distinct from the copyright in the document that it indexes. The licensing provisions set forth for the document are not applicable to this index. This index may not be reproduced in whole or in part by any means without the express written permission of NFPA.

- A-**
- Administration**, Chap. 1
 - Application, 1.3
 - Purpose, 1.2
 - Scope, 1.1, A.1.1
 - Units and Formulas, 1.4
 - Primary Values, 1.4.2
 - SI Units, 1.4.1
- C-**
- Conduct of Tests**, Chap. 7
 - Calibration Test, 7.2
 - Conditions of Acceptance, 7.5
 - Conduct of Torch Test, 7.3
 - Environmental Conditions, 7.6
 - Hose Stream Test, 7.4
 - Nozzle Distance, 7.4.6
 - Measurements, 7.7
 - Observations, 7.8
 - Photographs, 7.9
 - Test Assembly, 7.1
 - Video, 7.10
- D-**
- Definitions**, Chap. 3
- E-**
- Explanatory Material**, Annex A
- F-**
- Fire Resistance**
 - Definition, 3.3.1
- I-**
- Informational References**, Annex B
- P-**
- Passive Fire Protection (PFP) Material**
 - Definition, 3.3.2, A.3.3.2
- Passive Fire Protection — Coating Material
 - Definition, 3.3.2.1
- Passive Fire Protection — Panel Material
 - Definition, 3.3.2.2
- Presentation of Results**, Chap. 8
 - Test Report, 8.1
- R-**
- Rear Box**
 - Definition, 3.3.3
- Referenced Publications**, Chap. 2
- S-**
- Shall**
 - Definition, 3.2.1
- Should**
 - Definition, 3.2.2
- Standard**
 - Definition, 3.2.3
- T-**
- Test Location**, Chap. 6
 - Adverse Weather, 6.4
 - Air Temperature, 6.2
 - Environmental Effects, 6.1
 - Wind Limitations, 6.3
- Test Specimens**, Chap. 4
 - Construction of Rear Box, 4.2
 - Construction of Test Specimen, 4.1
 - Passive Fire Protection (PFP) Material, 4.3
- Torch Fire**, Chap. 5
 - Fuel, 5.3
 - Torch Fire Exposure, 5.2
 - Torch Fire Nozzle, 5.1
- Torch Fire**
 - Definition, 3.3.4

Sequence of Events for the Standards Development Process

Once the current edition is published, a Standard is opened for Public Input.

Step 1 – Input Stage

- Input accepted from the public or other committees for consideration to develop the First Draft
- Technical Committee holds First Draft Meeting to revise Standard (23 weeks); Technical Committee(s) with Correlating Committee (10 weeks)
- Technical Committee ballots on First Draft (12 weeks); Technical Committee(s) with Correlating Committee (11 weeks)
- Correlating Committee First Draft Meeting (9 weeks)
- Correlating Committee ballots on First Draft (5 weeks)
- First Draft Report posted on the document information page

Step 2 – Comment Stage

- Public Comments accepted on First Draft (10 weeks) following posting of First Draft Report
- If Standard does not receive Public Comments and the Technical Committee chooses not to hold a Second Draft meeting, the Standard becomes a Consent Standard and is sent directly to the Standards Council for issuance (see Step 4) or
- Technical Committee holds Second Draft Meeting (21 weeks); Technical Committee(s) with Correlating Committee (7 weeks)
- Technical Committee ballots on Second Draft (11 weeks); Technical Committee(s) with Correlating Committee (10 weeks)
- Correlating Committee Second Draft Meeting (9 weeks)
- Correlating Committee ballots on Second Draft (8 weeks)
- Second Draft Report posted on the document information page

Step 3 – NFPA Technical Meeting

- Notice of Intent to Make a Motion (NITMAM) accepted (5 weeks) following the posting of Second Draft Report
- NITMAMs are reviewed and valid motions are certified by the Motions Committee for presentation at the NFPA Technical Meeting
- NFPA membership meets each June at the NFPA Technical Meeting to act on Standards with “Certified Amending Motions” (certified NITMAMs)
- Committee(s) vote on any successful amendments to the Technical Committee Reports made by the NFPA membership at the NFPA Technical Meeting

Step 4 – Council Appeals and Issuance of Standard

- Notification of intent to file an appeal to the Standards Council on Technical Meeting action must be filed within 20 days of the NFPA Technical Meeting
- Standards Council decides, based on all evidence, whether to issue the standard or to take other action

Notes:

1. Time periods are approximate; refer to published schedules for actual dates.
2. Annual revision cycle documents with certified amending motions take approximately 101 weeks to complete.
3. Fall revision cycle documents receiving certified amending motions take approximately 141 weeks to complete.

Committee Membership Classifications^{1,2,3,4}

The following classifications apply to Committee members and represent their principal interest in the activity of the Committee.

1. M *Manufacturer*: A representative of a maker or marketer of a product, assembly, or system, or portion thereof, that is affected by the standard.
2. U *User*: A representative of an entity that is subject to the provisions of the standard or that voluntarily uses the standard.
3. IM *Installer/Maintainer*: A representative of an entity that is in the business of installing or maintaining a product, assembly, or system affected by the standard.
4. L *Labor*: A labor representative or employee concerned with safety in the workplace.
5. RT *Applied Research/Testing Laboratory*: A representative of an independent testing laboratory or independent applied research organization that promulgates and/or enforces standards.
6. E *Enforcing Authority*: A representative of an agency or an organization that promulgates and/or enforces standards.
7. I *Insurance*: A representative of an insurance company, broker, agent, bureau, or inspection agency.
8. C *Consumer*: A person who is or represents the ultimate purchaser of a product, system, or service affected by the standard, but who is not included in (2).
9. SE *Special Expert*: A person not representing (1) through (8) and who has special expertise in the scope of the standard or portion thereof.

NOTE 1: “Standard” connotes code, standard, recommended practice, or guide.

NOTE 2: A representative includes an employee.

NOTE 3: While these classifications will be used by the Standards Council to achieve a balance for Technical Committees, the Standards Council may determine that new classifications of member or unique interests need representation in order to foster the best possible Committee deliberations on any project. In this connection, the Standards Council may make such appointments as it deems appropriate in the public interest, such as the classification of “Utilities” in the National Electrical Code Committee.

NOTE 4: Representatives of subsidiaries of any group are generally considered to have the same classification as the parent organization.