



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

SPECIFICATION

AMS 2605B

Superseding AMS 2605A

Issued 1-1-42

Revised 4-15-78

PRESSURE TESTING 55 psi (380 kPa)

1. SCOPE: This specification provides requirements and procedures for air-pressure leak testing of parts and assemblies.

2. APPLICABLE DOCUMENTS: None.

3. TECHNICAL REQUIREMENTS:

3.1 Equipment:

3.1.1 Fixtures: Test fixtures shall not seal off areas of possible leakage or create excessive stresses on parts.

3.1.2 Gaskets: Suitable gasket material shall be used with plugs or blanking plates to prevent damage to finished surfaces.

3.1.3 Valves: Bleeder valves shall be provided to release entrapped air.

3.1.4 Gauges: Pressure gauges shall have sufficient dial divisions to permit monitoring of pressure specified.

3.1.5 Compressed Air Source: The source of compressed air shall provide the required pressure and shall be equipped with a pressure regulator to control the pressure.

3.1.6 Safety Tank or Screen: A suitable tank or screen shall be provided to protect the operator in case of failure of a part.

3.1.7 Drying Oven: A circulating-air oven shall be provided for drying corrodible parts.

3.2 Test Media: Shall be compressed air for applying internal pressure to the part. In addition, a tank of tap water or other transparent liquid shall be provided for parts tested by immersion or liquid soap solution shall be used on parts not immersed during test.

3.3 Preparation:

3.3.1 Cleaning: The part shall be thoroughly cleaned before testing, so that any leaks will be visible. Loose particles, machine shop chips, oils, and other foreign materials shall be removed before pressure testing.

3.3.2 Processes: The part or subassembly shall be tested following all machining, forming, straightening, welding, brazing, anodizing, etc, and prior to application of protective finishes such as paint, plating, coating, or surface finishes that may mask or blank off areas of possible leakage.

3.3.3 Impregnation: Impregnation of castings shall not be permitted except as authorized by purchaser and then only to correct general seepage leaks. Impregnation shall not be used to correct poor foundry techniques, visible holes, or excessive porosity. Impregnation shall be conducted after all heat treatment, brazing, and welding have been completed.

SAE Technical Board rules provide that: "All technical reports, including standards and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3.3.4 Preliminary Tests: Tests may be performed at any stage of manufacture in order to establish in-process integrity.

3.3.5 Material Removal: Sand blasting, pickling, or any other operation which may remove metal from surfaces shall be done before final pressure tests.

3.4 Procedure: All parts to be tested shall be fitted up for test and, while subjected internally to an air pressure of 55 - 65 psi (380 - 448 kPa), shall be submerged in tap water or other transparent liquid or shall have the surfaces to be tested completely coated with liquid soap.

3.4.1 Duration: Parts, other than castings, shall be held under pressure for not less than 3 min. to permit complete visual inspection while at the specified pressure. Unless a specific time is specified, castings also shall be held for not less than 3 min. at the specified pressure.

3.4.2 Magnesium Alloy Castings, Optional Method: The casting shall be fitted up for test, the surfaces opposite those under pressure shall be dried, and water under pressure of 55 - 65 psi (380 - 448 kPa) applied and held for not less than 5 minutes. All air shall be excluded by the water from the pressure side.

3.4.3 Cleaning: Parts which have been tested with water shall be cleaned and dried, immediately after test, to prevent corrosion due to entrapment of moisture. Visible moisture shall be removed by air blast. Parts containing areas of entrapment and all magnesium parts shall be dried in a circulating-air oven at $250^{\circ}\text{F} \pm 25$ ($120^{\circ}\text{C} \pm 15$) for not less than one hour.

3.4.4 Orientation: The part shall be exposed to permit overall visual inspection during static pressure application.

3.5 Acceptance Standards:

3.5.1 Parts which do not leak under pressure are acceptable.

3.5.2 The effect of any slight leakage of parts shall be reviewed by cognizant personnel and the parts accepted, repaired and retested, or rejected.

3.5.3 Slight leakage from a casting or forging appearing in a line, as if indicating a crack or a cold shut, is not acceptable.

3.5.4 Magnesium alloy castings which leak in a 2-in. (51-mm) diameter area more than 25 drops of test fluid per min. or more than 220 mL of air per min. are not acceptable but those that leak less may be impregnated, when so specified and the method to be used is approved.

3.5.4.1 Those sections of magnesium alloy castings, impregnated or not, which leak in a 2-in. (51-mm) diameter area less than 5 drops of test fluid per min. or less than 50 mL of air per min. are acceptable unless the leakage is into the induction system of the assembled item or through an external surface, in which case leakage is not desirable but is acceptable to the extent of 0.1 mL of air per min. in a 2-in. (51-mm) diameter area.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Reports: The pressure test vendor shall furnish with each shipment three copies of a report showing results of pressure test and stating that the parts conform to the requirements of this specification. This report shall include the purchase order number, this specification number and its revision letter, part number, and quantity.