



400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 3801/3

Issued 4-1-84
Revised

CLOTH, PARACHUTE, META-ARAMID, LOW MODULUS 12.0(400) Weight, Special Weave

1. SCOPE:

1.1 Form: This specification covers one weight and one weave of low modulus meta-aramid cloth.

1.2 Application: Primarily for use in construction of parachutes.

1.3 Classification: 12.0 oz per sq yd (400 g/m²) low modulus meta-aramid cloth with special weave.

2. APPLICABLE DOCUMENTS: See AMS 3801.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the low modulus meta-aramid cloth described herein shall consist of this document and the latest issue of the basic specification, AMS 3801.

3.2 Construction and Properties:

3.2.1 Yarn: Yarn used in weaving the cloth shall be a low modulus meta-aramid with a carbonization (char) temperature not lower than 355°C (670°F).

3.2.1.1 Denier and Filament Count: The yarn shall be 200 denier \pm 15 and shall consist of 100 filaments \pm 10.

3.2.1.2 Ply: The yarn shall be 5 ply.

3.2.1.3 Twist: The final ply of yarn shall be twisted 2.5 to 2.8 turns per in. (25 mm).

3.2.2 Cloth:

3.2.2.1 Weave: Shall be as shown in Fig. 1.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 3801/3

3.2.2.2 Color: Shall be Sage Green 1565 as shown in FED-STD-595, unless otherwise specified. The color shall be obtained by the use of melt spun solution dyed yarn.

3.2.2.3 pH: Shall be 5.0 to 8.0, incl, determined on the water extract of the finished cloth.

3.2.2.4 Width: The width, inclusive of selvage, shall be as ordered.

3.2.2.5 Weight: Shall not exceed 12.0 oz per sq yd (400 g/m^2).

3.2.2.6 Breaking Strength: Breaking strength of the unaged cloth shall be not less than 425 lb per in. ($74,400 \text{ N/m}$) in both warp and fill directions. Breaking strength after heat aging shall be not less than 85% of the unaged value in both the warp and fill directions.

3.2.2.7 Elongation: Shall be not less than 15% in the warp and fill directions.

3.2.2.8 Tearing Strength: Shall be not less than 75 lb (335 N) in the warp and fill directions.

3.2.2.9 Thickness: Shall not exceed 0.032 in. (0.80 mm).

3.2.2.10 Air Permeability: Shall be 40 - 80 cu ft per min. for each sq ft ($12.0 - 24.5 \text{ m}^3/\text{min. for each m}^2$).

3.2.2.11 Count: Warp ends and filling picks shall be not less than 38 per in. (25 mm).

3.3 Length and Put-up: The cloth shall be put up in rolls in accordance with PPP-P-1133. Each roll shall contain not less than 80 yd (75 m) nor more than 120 yd (110 m). Each roll shall contain not more than 2 pieces and each piece shall contain not less than 40 yd (35 m).

4. QUALITY ASSURANCE PROVISIONS: See AMS 3801.

5. PREPARATION FOR DELIVERY: See AMS 3801.

6. ACKNOWLEDGMENT: See AMS 3801.

7. REJECTIONS: See AMS 3801.

8. NOTES: See AMS 3801.