

Aluminum Alloy, Sheet and Plate, Alclad
4.4Cu - 1.5Mg - 0.60Mn (2024, -T3 Sheet/-T351 Plate with 1½% Alclad)
Solution Heat Treated, Cold Worked and Naturally Aged
(Composition similar to UNS A82024)

RATIONALE

AMS4041R is being revised to delete the thin sheet portion of the document (0.008 to 0.187 inch) (Tables 2, 3, and 4) and supersede those requirements by the new AMS4462. Cautionary notes concerning this specification as it pertains to "thin" clad (1 ½%) for material over 0.187 inch were added due to potential for reduced corrosion resistance at reduced cladding thickness. This specification is not equivalent to historical AMS-QQ-A-250/5 applications for thicker gages.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of alclad sheet and plate supplied in the -T3/-T351 temper.

1.2 Supersession Notice

Requirements for thin gage sheet (0.008 to 0.187 inch) in accordance with AMS4041 are superseded by AMS4462. AMS-QQ-A-250/5 and AMS4462 have the same requirements for alclad thickness and tensile properties for material less than 0.187" in thickness.

1.2.1 AMS4041 covers alclad material for sheet greater than 0.187 inch, and plate. The cladding thickness is minimized to provide a commensurate increase in tensile properties for this alclad reduction. Use of this product is not recommended without proper evaluation of corrosion resistance.

1.3 Application

These products have been used typically for high strength parts requiring higher yield strength than is afforded by naturally aged tempers of this alloy and maximum corrosion resistance and whose fabrication does not involve welding, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4041R>**

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

AS1990 Aluminum Alloy Tempers

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B 594 Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium Alloy Products

2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, New York, NY 10036, Tel: 212-642-4900, www.ansi.org.

ANSI H 35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H 35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight as shown in Tables 1, determined in accordance with AMS2355.

TABLE 1A – COMPOSITION, CORE (2024)

Element	min	max
Silicon	--	0.50
Iron	--	0.50
Copper	3.8	4.9
Manganese	0.30	0.9
Magnesium	1.2	1.8
Chromium	--	0.10
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

TABLE 1B – COMPOSITION, CLADDING (1230)

Element	min	max
Iron + Silicon	--	0.70
Copper	--	0.10
Manganese	--	0.05
Magnesium	--	0.05
Zinc	--	0.10
Titanium	--	0.03
Other Elements, each	--	0.03
Aluminum	99.30	--

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Sheet

Solution heat treated, cold worked and naturally aged to the T3 temper in accordance with AMS2772 (See AS1990).

3.2.2 Plate

Solution heat treated, stretched to produce a nominal permanent set of 2% but not less than 1-1/2% nor more than 3%, and naturally aged to the T351 temper in accordance with AMS2772 (See AS1990).

3.2.2.1 Plate shall receive no further straightening operations after stretching.

3.3 Properties

The product shall conform to the following requirements, determined in accordance with AMS2355 on the mill produced size.

3.3.1 Tensile Properties

Shall be as shown in Table 2 (See 8.3).

TABLE 2A – MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Temper	Nominal Thickness, Inches	Tensile Strength, ksi	Yield Strength at 0.2% Offset, ksi	Elongation in 2 inches or 4D, %
-T3	Over 0.187 to 0.249, incl	63.0	41.0	15
-T351	0.250 to 0.499, incl	63.0	41.0	12
	Over 0.499 to 1.000, incl	63.0	42.0	8
	Over 1.000 to 1.500, incl	62.0	42.0	7
	Over 1.500 to 2.000, incl	62.0	42.0	6
	Over 2.000 to 3.000, incl	60.0	42.0	4
	Over 3.000 to 4.000, incl	57.0	41.0	4

TABLE 2B – MINIMUM TENSILE PROPERTIES, SI UNITS

Temper	Nominal Thickness, Millimeters	Tensile Strength, mPa	Yield Strength at 0.2% Offset, mPa	Elongation in 50.8 mm or 4D, %
-T3	Over 4.750 to 6.324, incl	434	283	15
-T351	6.350 to 12.675, incl	434	283	12
	Over 12.675 to 25.400, incl	434	290	8
	Over 25.400 to 38.100, incl	428	290	7
	Over 38.100 to 50.800, incl	428	290	6
	Over 50.800 to 76.200, incl	414	290	4
	Over 76.200 to 101.600, incl	393	283	4

3.3.2 Bending

Product shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 3 – BENDING PARAMETERS

Nominal Thickness; Inches	Nominal Thickness; Millimeters	Bend Factor
Over 0.187 to 0.249, incl	Over 4.750 to 6.324, incl	8
Over 0.249 to 0.499, incl	Over 6.324 to 12.675, incl	10

3.3.3 Cladding Thickness

The aluminum alloy plates that are bonded to the two sides of the aluminum alloy (2024) ingot or slab, to form a composite that is to be rolled, shall each have a thickness as specified in Table 4.

TABLE 4 – CLADDING THICKNESS

Nominal Thickness, Inch	Nominal Thickness, mm	Average Cladding Thickness Per Side; % of Total Thickness; minimum	Average Cladding Thickness Per Side; % of Total Thickness; maximum
Over 0.187 to 0.499, incl	Over 4.750 to 12.675, incl	1.2	--
Over 0.499	Over 12.675	1.2	3.0

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H 35.2/H 35.2M.