

ALUMINUM ALLOY SHEET, CLAD ONE SIDE
1.25Mn - 0.12Cu (No. 11-0 Brazing Sheet)
Annealed

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of sheet.

1.2 Application: Primarily for brazed assemblies which are not subject to heat treatment after joining.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2202 - Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate

MAM 2202 - Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate

AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings

MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units

2.2 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2.1 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

Core (3003)		Cladding (4343)	
	min max		min max
Manganese	1.0 - 1.5	Silicon	6.8 - 8.2
Copper	0.05 - 0.20	Iron	-- 0.8
Iron	-- 0.7	Copper	-- 0.25
Silicon	-- 0.6	Zinc	-- 0.20
Zinc	-- 0.10	Manganese	-- 0.10
Other Impurities, each	-- 0.05	Other Impurities, each	-- 0.05
Other Impurities, total	-- 0.15	Other Impurities, total	-- 0.15
Aluminum	remainder	Aluminum	remainder

3.2 Condition: Annealed.3.3 Properties: Sheet shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:3.3.1 Tensile Properties: Shall be as specified in Table I.TABLE I

Nominal Thickness Inch	Tensile Strength psi, max	Elongation in 2 in. %, min
0.006 to 0.007, incl	20,000	12
Over 0.007 to 0.012, incl	20,000	15
Over 0.012 to 0.031, incl	20,000	18
Over 0.031 to 0.050, incl	20,000	20
Over 0.050 to 0.249, incl	20,000	23

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, max	Elongation in 50 mm %, min
0.15 to 0.18, incl	140	12
Over 0.18 to 0.30, incl	140	15
Over 0.30 to 0.78, incl	140	18
Over 0.78 to 1.25, incl	140	20
Over 1.25 to 6.25, incl	140	23

3.3.2 Bending: Sheet shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.

3.3.3 Cladding: Shall be applied to only one face of the core.

3.3.3.1 Cladding Thickness: After rolling, the average cladding thickness shall be as follows:

Total Thickness of Composite Product		Cladding Thickness % of Total Thickness min avg
Inch	Millimetres	
Up to 0.063, incl	Up to 1.58, incl	8
Over 0.063 to 0.250, excl	Over 1.58 to 6.25, excl	4

3.4 Quality: Sheet, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the sheet.

3.5 Tolerances: Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of sheet shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the sheet conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for bending (3.3.2) and cladding thickness (3.3.3.1) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

4.4.1 The vendor of sheet shall furnish with each shipment a report stating that the sheet conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, AMS 4063B, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4063B, contractor or other direct supplier of sheet, part number, and quantity. When sheet for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of sheet to determine conformance to the requirements of this specification and shall include in the report either a statement that the sheet conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet shall be marked on the clad face in the respective location indicated below, with the brazing sheet number and temper, AMS 4063, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the sheet or its performance.

5.1.1 Flat Sheet Under 6 In. (150 mm) Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm).

5.1.2 Flat Sheet 6 - 48 In. (150 - 1200 mm), Incl, Wide and 36 - 200 In. (900 - 5000 mm), Incl, Long: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced approximately 6 in. (150 mm) on centers across the width and staggered. Every third row shall show the manufacturer's identification and nominal thickness. The other rows shall show the brazing sheet number and temper and AMS 4063.

5.1.3 Coiled Sheet: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1. When the sheet is wound on cores, the tag or label may be attached to the core.

5.2 Protective Treatment: Flat sheet shall be protected, during shipment and storage, by interleaving with suitable paper sheets. Coiled sheet shall not be interleaved.

5.3 Packaging:

5.3.1 Sheet shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the sheet to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.