

AEROSPACE MATERIAL SPECIFICATION

SAE AMS4169

REV. L

Issued 1960-06
Revised 2003-07
Reaffirmed 2008-05
Cancelled 2012-01

Superseded by AMS4154

Aluminum Alloy, Extrusions
5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (7075-T6511)
Solution Heat Treated, Stress Relieved by Stretching, Straightened
and Precipitation Heat Treated
(Composition similar to A97075)

RATIONALE

AMS4169L has been designated Cancelled and Superseded because equivalent technical requirements are provided by other specifications.

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of January 2012 and has been superseded by the specification listed below. The requirements of the latest issue of the specification listed below shall be fulfilled whenever reference is made to the cancelled AMS4169. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications, noting that it has been superseded by the specification listed below.

Cancelled specifications are available from SAE.

Temper	Superseding Material and Specification
T6511	7075-T6511 in accordance with AMS4154 Aluminum Alloy, Extrusions, 5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (7075-T6, 7075-T6510, 7075-T6511) Solution Heat Treated, Stress Relieved by Stretching When Required and Precipitation Heat Treated

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4169L>**

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of extruded bars, rods, wire, profiles, and tubing.

1.2 Application:

These products have been used typically for parts subject to excessive warpage during machining and for parts requiring high strength and whose fabrication does not involve welding or forming, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these extrusions to become susceptible to stress-corrosion cracking; ARP823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

SAENORM.COM : Click to view the full PDF of AMS4169L

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys,
Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
AMS 2772 Heat Treatment of Aluminum Alloy Raw Materials

ARP823 Minimizing Stress-Corrosion Cracking in Wrought Heat-Treatable Aluminum Alloy
Products
AS1990 Aluminum Alloy Tempers

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or
www.astm.org.

ASTM B 594 Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace
Applications
ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products
ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Publications:

Available from ANSI, 25 West 43rd Street, New York, NY 10036 or www.ansi.org.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products
ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with
AMS 2355.

TABLE 1 - Composition

Element	min	max
Silicon	--	0.40
Iron	--	0.50
Copper	1.2	2.0
Manganese	--	0.30
Magnesium	2.1	2.9
Chromium	0.18	0.28
Zinc	5.1	6.1
Titanium	--	0.20
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Solution heat treated, stress-relieved by stretching to produce a nominal permanent set of 1.5%, but not less than 1% nor more than 3%, and precipitation heat treated to the T6511 temper (see AS1900). Heat treatments shall be performed in accordance with AMS 2772.

- 3.2.1 Extrusions may receive minor straightening, after stretching, of an amount necessary to meet the requirements of 3.5.
- 3.2.2 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within specified dimensional tolerances.

3.3 Properties:

Extrusions shall conform to the following requirements, determined in accordance with AMS 2355:

3.3.1 Tensile Properties:

- 3.3.1.1 Longitudinal: Shall be as shown in Table 2.

TABLE 2A - Minimum Longitudinal Tensile Properties, Inch/Pound Units

Nominal Diameter or Least Thickness (bars, rods, wire, profiles) or Nominal Wall Thickness (tubing) Inches	Nominal Cross- Sectional Area Square Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.249, incl	All	78.0	70.0	7
Over 0.249 to 0.499, incl	All	81.0	73.0	7
Over 0.499 to 2.999, incl	All	81.0	72.0	7
Over 2.999 to 4.499, incl	Up to 20, incl	81.0	71.0	7
Over 2.999 to 4.499, incl	Over 20 to 32, incl	78.0	70.0	6
Over 4.499 to 5.000, incl	Up to 32, incl	78.0	68.0	6

TABLE 2B - Minimum Longitudinal Tensile Properties, SI Units

Nominal Diameter or Least Thickness (bars, rods, wire, profiles) or Nominal Wall Thickness (tubing) Millimeters	Nominal Cross- Sectional Area Square Centimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 6.32, incl	All	538	483	7
Over 6.32 to 12.67, incl	All	558	503	7
Over 12.67 to 76.17, incl	All	558	496	7
Over 76.17 to 114.27, incl	Up to 129, incl	558	490	7
Over 76.17 to 114.27, incl	Over 129 to 206, incl	538	483	6
Over 114.27 to 127.00, incl	Up to 206, incl	538	469	6

- 3.3.1.2 Long-Transverse: Bars, rods, and profiles, tested in the long-transverse direction, shall meet the requirements of Table 3. Profiles of a size preventing generation of long-transverse specimens shall be as agreed upon by supplier and user.

TABLE 3A - Minimum Long-Transverse Tensile Properties, Inch/Pound Units

Nominal Diameter or Least Thickness (bars, rods, profiles) Inches	Nominal Cross- Sectional Area Square Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.249, incl	Up to 20, incl	76.0	66.0	5
Over 0.249 to 0.499, incl	Up to 20, incl	78.0	68.0	5
Over 0.499 to 0.749, incl	Up to 20, incl	76.0	66.0	4
Over 0.749 to 1.499, incl	Up to 20, incl	74.0	65.0	3
Over 1.499 to 2.999, incl	Up to 20, incl	70.0	61.0	1
Over 2.999 to 4.499, incl	Up to 20, incl	67.0	56.0	1
Over 2.999 to 4.499, incl	Over 20 to 32, incl	65.0	55.0	1

TABLE 3B - Minimum Long-Transverse Tensile Properties, SI Units

Nominal Diameter or Least Thickness (bars, rods, profiles) Millimeters	Nominal Cross- Sectional Area Square Centimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 6.32, incl	Up to 129, incl	524	455	5
Over 6.32 to 12.67, incl	Up to 129, incl	538	469	5
Over 12.67 to 19.02, incl	Up to 129, incl	524	455	4
Over 19.02 to 38.07, incl	Up to 129, incl	510	448	3
Over 38.07 to 76.17, incl	Up to 129, incl	483	421	1
Over 76.17 to 114.27, incl	Up to 129, incl	462	386	1
Over 76.17 to 114.27, incl	Over 129 to 206, incl	448	379	1

3.4 Quality:

Extrusions, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the extrusions.

- 3.4.1 When specified, extrusions shall be subjected to ultrasonic inspection in accordance with ASTM B 594 and shall meet the following requirements.

- 3.4.1.1 Extrusions, with nominal thickness of 0.500 to 1.499 inches (12.70 to 38.07 mm), not exceeding 600 pounds (272 kg) per piece, or a 10 to 1 width-to-thickness ratio, shall meet ultrasonic Class B.

- 3.4.1.2 Extrusions, with nominal thickness 1.500 inches (38.07 mm) and over, not exceeding 600 pounds (272 kg) per piece, or a 10 to 1 width-to-thickness ratio, shall meet ultrasonic Class A.

3.5 Tolerances:

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of extrusions shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the extrusions conform to specified requirements.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Composition (3.1), longitudinal tensile properties (3.3.1.1), ultrasonic inspection when specified (3.4.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each inspection lot.

- 4.2.2 Periodic Tests: Transverse tensile properties (3.3.1.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2355.

4.4 Reports:

The vendor of extrusions shall furnish with each shipment a report stating that the extrusions conform to the chemical composition, ultrasonic inspection when specified, and tolerances and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number, AMS 4169L, size or section identification number, and quantity. The report shall also identify the producer, the product form, and the size of the mill product.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355.