

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4210 A

Issued 10/15/40

Revised 11/1/41

CAST ALUMINUM ALLOY 5% Silicon (Aged)

1. ACKNOWLEDGMENT: A vendor must mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. COMPOSITION:

Silicon	4.5 - 5.5
Copper	1.0 - 1.5
Magnesium	0.4 - 0.6
Chromium + Titanium	0.08 - 0.30
Iron	0.50 Max
Manganese	0.05 max
Zinc	0.03 max
Other Impurities, each	0.05 max
Aluminum	remainder

3. CASTING: (a) All the metal which is melted for castings shall conform to section 2 ingot; gates, risers and rejected castings, may be used but shall first be converted into such ingot.

(b) During melting, the metal shall be heated to not over 1450°F. The metal being poured into the mold shall not exceed a temperature of 1400°F. Written permission must be obtained from the purchaser by letter or by revising the physical properties on the drawing before deviating from the requirements of this paragraph.

(c) The molten metal for making tensile test bars of the standard size for testing shall be taken from the same melt as the castings immediately before or after the metal for the castings is taken. The test bars shall be poured at the temperature of pouring the castings with a runner length not greater than that of the castings. The mold shall be made with the regular foundry mix of green sand without using chills.

4. HEAT TREATMENT: The test bars, together with the castings which they represent, shall receive the aging treatment only, that is heated uniformly to 420°-450°F, held at heat for 8-10 hours and allowed to cool. Castings shall have a minimum hardness of Brinell 55, but the impression is not to be taken at a sprue or riser.

5. TEST BARS: (a) Tensile test bars shall be cast with each melt of castings, unless otherwise specified. A melt shall mean a furnace charge (1000 pounds or less) of metal as melted for pouring castings. Test bars are to be supplied with the castings when requested.

(b) Unless otherwise specified or noted on the drawing, the test bars poured and treated as specified in sections 3 and 4 shall conform to the following minimum physical properties:

Tensile Strength, lb per sq in 25,000
Elongation, % in 2 in. 1

6. QUALITY: (a) Castings must be homogeneous and free from shrinkage defects, cracks, blowholes, sand holes, hard spots, foreign matter, and other injurious defects, and