

Issued 1980-01
Revised 2004-12
Reaffirmed 2012-02

Superseding AMS4343C

Aluminum Alloy, Extrusions
7.7Zn - 2.4Mg - 1.6Cu - 0.16Cr (7149-T73511)
Solution Heat Treated, Stress Relieved by Stretching, and Overaged
(Composition similar to UNS A97149)

RATIONALE

AMS4343D has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of extruded bars, rods, wire, shapes, and tubing.

1.2 Application:

These extrusions have been used typically for structural parts requiring a combination of high strength, moderate fatigue strength, good stress-corrosion resistance, and good fracture toughness, but usage is not limited to such applications..

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged or Flash Welded Rings
AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials
AS1990	Aluminum Alloy Tempers

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4343D>**

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM B 594	Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications
ASTM B 660	Packaging/Packing of Aluminum and Magnesium Products
ASTM B 666/B 666M	Identification Marking of Aluminum and Magnesium Products
ASTM E 399	Plane-Strain Fracture Toughness of Metallic Materials

2.3 ANSI Publications:

Available from ANSI, 25 West 43rd Street, New York, NY 10036 or www.ansi.org.

ANSI H35.2	Dimensional Tolerances for Aluminum Mill Products
ANSI H35.2M	Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355.

TABLE 1 - Composition

Element	min	max
Silicon	--	0.15
Iron	--	0.20
Copper	1.2	1.9
Manganese	--	0.20
Magnesium	2.0	2.9
Chromium	0.10	0.22
Zinc	7.2	8.2
Titanium	--	0.10
Other Elements, each	--	0.05
Other Elements, total		0.15
Aluminum	remainder	

3.2 Condition:

Solution heat treated, stress-relieved by stretching to produce a nominal permanent set of 1.5% but not less than 1% nor more than 3%, and overaged to the -T73511 temper (See AS1990). Solution and overaging heat treatments shall be in accordance with AMS 2772.

- 3.2.1 Extrusions may receive minor straightening, after stretching, of an amount necessary to meet the tolerance requirements of 3.5.
- 3.2.2 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within the dimensional tolerances.
- 3.3 Properties:

Extrusions shall conform to the following requirements, determined on the mill produced size in accordance with AMS 2355.

- 3.3.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2A - Minimum Tensile Properties, Inch/Pound Units

Nominal Diameter or Least Thickness (bars, rods, wire, profiles) or Nominal Wall Thickness (tubing) Inches	Specimen Orientation	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 inches or 4D %
Up to 2.999, incl	Longitudinal	74.0	64.0	7
	Long-Trans.	70.0	60.0	5
2.500 to 2.999, incl	Short-Trans.	70.0	60.0	5
Over 2.999 to 5.000, incl	Longitudinal	72.0	62.0	7
	Long-Trans.	68.0	58.0	5
	Short-Trans.	68.0	58.0	5

TABLE 2B - Minimum Tensile Properties, SI Units

Nominal Diameter or Least Thickness (bars, rods, wire, profiles) or Nominal Wall Thickness (tubing) Millimeters	Specimen Orientation	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 76.17, incl	Longitudinal	510	441	7
	Long-Trans.	483	414	5
Over 63.50 to 76.17, incl	Short-Trans.	483	414	5
Over 76.17 to 127.00, incl	Longitudinal	496	427	7
	Long-Trans.	469	400	5
	Short-Trans.	469	400	5

- 3.3.2 Electrical Conductivity: Shall be not lower than 40.0% IACS (International Annealed Copper Standard) (23.2 MS/m).
- 3.3.2.1 If the conductivity is below 40.0% IACS (23.2 MS/m), the extrusions are not acceptable. Extrusions found to be unacceptable may be given additional overaging heat treatment; if, upon completion of such treatment, they develop mechanical properties and a conductivity conforming to 3.3.1 and 3.3.2, they shall be acceptable.
- 3.3.3 Stress-Corrosion Resistance: Specimens, cut from extrusions 0.750 inch (19.05 mm) and over in nominal diameter or section thickness, shall show no evidence of stress-corrosion cracking when stressed in the short-transverse (perpendicular to grain flow) direction to 65% of the specified minimum longitudinal (parallel to grain flow) yield strength.
- 3.3.4 Fracture Toughness: When specified, the minimum K_{Ic} shall be 26 ksi $\sqrt{\text{inch}}$ (28.6 MPa $\sqrt{\text{m}}$) in the longitudinal (LT) direction and 19 ksi $\sqrt{\text{inch}}$ (21 MPa $\sqrt{\text{m}}$) in the transverse (TL and ST) directions, determined in accordance with ASTM E 399. A compact tension specimen 1.000 inch $\pm$ 0.025 (25.40 mm $\pm$ 0.64) is recommended. Testing shall be in air at room temperature.
- 3.3.4.1 If a test is invalid due to any single ASTM validity criterion, the test shall be interpreted as having met the requirement if the calculated K_Q is equal to or higher than the minimum K_{Ic} required. If a test fails two ASTM validity requirements, one additional test shall be conducted before submittal to purchaser for disposition.

3.4 Quality:

Extrusions, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the extrusions.

- 3.4.1 When specified, extrusions shall be subjected to ultrasonic inspection in accordance with ASTM B 594. Standards for acceptance shall be specified by the cognizant engineering organization.

3.5 Tolerances:

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of extrusions shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the extrusions conform to specified requirements.