

AEROSPACE MATERIAL SPECIFICATION Society of Automotive Engineers, Inc.

AMS 5500

Issued 5 - 1 - 68Revised

STEEL SHEET, CORROSION RESISTANT, LAMINATED Surface Bonded

- ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when 1. acknowledging purchase orders.
- APPLICATION: Primarily for shims in which thickness is to be adjusted by removal of laminations as required.
- COMPOSITION:

LEXINGTON AVENUE, NEW YORK, N.Y. 10017

Laminations: 3.1

	min	max
Carbon		0.15
Manganese		2.00
Silicon		1.00
Phosphorus		0.040
Sulfur		2 0. 030
Chromium	17.00 -	19.00
Nickel	- 00/8	10.00
Molybdenum	116	0.50
Copper	×O	0.50

- Composition variations shall meet the requirements of the latest issue of 3.1.1 Check Analysis: AMS 2248.
- Adhesive: Shall be of a composition which will meet the fabrication and quality requirements of 3.2 this specification.
- FABRICATION:
- Laminated shim stock shall be fabricated from corrosion resistant steel laminations in the annealed or 1/4 hard temper. Stock shall consist completely of laminations each 0.002 in. ± 0.0002 thick or 0.003 in. \$\frac{1}{2}\$0.0003 thick, or partly of such laminations combined with a single thicker lamination, as ordered, bonded together by an adhesive such that individual laminations may be peeled for adjustment of shim thickness.
- Unless otherwise specified, the product shall be of the following thicknesses and combinations of 4.2 laminations and solid base:

AMS 5500

Nominal Overall Thickness of Shim Stock, Inch	All Laminated (0.002 in. Lamina- tions)	All Laminated (0.003 in. Lamina- tions)	Half Solid Half Laminated (0.002 in. Lamina- tions)	Half Solid Half Laminated (0.003 in. Lamina- tions)	Three Quarters Solid One Quarter Laminated (0.002 in. Lamina- tions)	Three Quarters Solid One Quarter Laminated (0.003 in. Lamina- tions)
0.006	X	*				
0.008	X					
0.010	X					
0.016	X	X				
0.020	X	X			0-	
0.032	X	X			600	
0.047	X	X			3	
0.062	Χ .	X	X	X	, ansisoo	
0.094	X	X	X	X	(D)	
0.125	X	X	X	X	x	X

5. QUALITY:

- 5.1 The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
- 5.2 Laminations shall be bonded together in such a manner that any shape can be cut out of the shim stock without causing the laminations in the shape to separate. Normal handling shall not cause separation of laminations.
- 6. TOLERANCES: Unless otherwise specified, tolerances shall be as specified below:

Nominal Total Thickness	Tolerance, Inch		
Inch (N)	Plus	Minus	
Up to 0.010, incl	0.0005	0.0005	
Over 0.010 to 0.021, incl	0.001	0.001	
Over 0.021 to 0.047, incl	0.002	0.001	
Over 0.047 to 0.078, incl	0.003	0. 001	
Over 0.078	0.005	0.002	
A V Comment of the co			

7. REPORTS:

- 7.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition or stating that the chemical composition of the shim stock conforms to the requirements specified. This report shall include the purchase order number, material specification number, shim stock thickness, foil thickness, size, and quantity.
- 7.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.