

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5580C

Issued 12-4-39

Revised 10-1-51

ALLOY TUBING, SEAMLESS, CORROSION AND HEAT RESISTANT
Nickel Base - 15.5Cr - 8Fe
Annealed

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Parts and assemblies requiring both corrosion and oxidation resistance, and where such parts may require welding during fabrication. Parts and assemblies requiring oxidation resistance up to approximately 2000 F, but useful at the higher temperatures only when stresses are low. Strength at elevated temperatures is similar to that of the 18-8 type of steel.

3. COMPOSITION:

Carbon	0.15	max
Manganese	1.00	max
Silicon	0.50	max
Sulfur	0.015	max
Chromium	14.00 - 17.00	
Nickel + Cobalt	72.00	min
Cobalt, if determined	1.00	max
Iron	6.00 - 10.00	
Copper	0.50	max

4. CONDITION: Cold drawn and annealed, and pickled if necessary, unless otherwise specified.

5. TECHNICAL REQUIREMENTS:

5.1 Tensile Properties:

Tensile Strength, psi	80,000 - 105,000
Yield Strength at 0.2% offset or at 0.0059 inch in 2 in. extension under load, psi	30,000 min
Elongation, % in 2 in.	35 min

- 5.2 Flarability: Tubing with nominal OD of 2.00 in. and under shall be capable of being flared without formation of cracks or other visible defects. Specimens for flaring may be cut from any portion of the tube, or an entire tube may be used as a specimen. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded. The specimen shall, at room temperature, be forced axially with steady pressure over a hardened and polished tapered pin having a 74 degree included angle, to produce a permanent expanded OD not less than 1.3 times the original nominal OD.

Note: Tubing with nominal OD greater than 2.00 in. and less than 0.188 in., flarability shall be as agreed upon by purchaser and vendor.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."