

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 5595C
Superseding AMS 5595B

Issued 11-1-68
Revised 7-1-84

STEEL SHEET, STRIP, AND PLATE, CORROSION RESISTANT

9.0Mn - 20Cr - 6.5Ni - 0.28N

Solution Heat Treated

UNS S21904

1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant steel in the form of sheet, strip, and plate.

1.2 Application: Primarily for parts requiring high strength and corrosion resistance from -423°F to +1100°F (-255°C to +595°C) where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2242 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate

MAM 2242 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate

AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM A708 - Detection of Susceptibility to Intergranular Corrosion in Severely Sensitized Austenitic Stainless Steel

ASTM E112 - Determining Average Grain Size

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

- 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

- 2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, $\emptyset$ determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.04
Manganese	8.00 -	10.00
Silicon	--	1.00
Phosphorus	--	0.060
Sulfur	--	0.030
Chromium	19.00 -	21.50
Nickel	5.50 -	7.50
Nitrogen	0.15 -	0.40
Molybdenum	--	0.75
Copper	--	0.75

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Sheet: Cold rolled, solution heat treated, and descaled (No. 2D finish).

3.2.2 Strip: Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled (No. 1 strip finish).

3.2.3 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Solution Heat Treatment: The product shall be solution heat treated by heating to $1950^{\circ}\text{F} \pm 25$ ($1065^{\circ}\text{C} \pm 15$), holding at heat for 3 min. for each 0.10 in. (2.5 mm) of nominal thickness, and cooling at a rate equivalent to rapid air cool or faster.

3.4 Properties: The product shall conform to the following requirements; tensile, hardness, and bend testing shall be performed in accordance with ASTM A370:

3.4.1 Grain Size: Shall be predominantly 7 or finer, determined by comparison of a polished and etched specimen with the chart in ASTM E112.

3.4.2 Tensile Properties:

TABLE I

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
Up to 0.1875, excl	100,000	60,000	40
0.1875 and over	90,000	50,000	40

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50 mm or 4D %, min
Up to 4.750, excl	690	415	40
4.750 and over	620	345	40

3.4.3 Hardness: Should be not higher than 100 HRB, or equivalent, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.2 are met.

- 3.4.4 Bending: Product 0.749 in. (18.75 mm) and under in nominal thickness shall withstand, without cracking, bending through the angle indicated in Table II around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling. Bend requirements for product over 0.749 in. (18.75 mm) in nominal thickness shall be as agreed upon by purchaser and vendor. Only one type of test will be required in routine inspection; in case of dispute, results of tests using the V-block procedure shall govern.

TABLE II

Nominal Thickness		Type of Bend	Angle deg, min	Bend Factor
Inch	Millimetres			
Up to 0.249, incl	Up to 6.25, incl	Free Bend	180	1
Up to 0.249, incl	Up to 6.25, incl	V-Block	135	1
Over 0.249 to 0.749, incl	Over 6.25 to 18.75, incl	Free Bend	90	1
Over 0.249 to 0.749, incl	Over 6.25 to 18.75, incl	V-Block	135	2

- 3.4.5 Embrittlement: The product shall show no evidence of intercrystalline surface attack when immersed in acidified copper sulfate solution in accordance with ASTM A708 after being sensitized by heating in air to $1250^{\circ}\text{F} \pm 10$ ($675^{\circ}\text{C} \pm 5$), holding at heat for 60 min. ± 5 , and cooling in air. After immersion, specimens shall withstand, without cracking, bending in accordance with ASTM A708.

- 3.5 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

- 3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2242 or MAM 2242.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), grain size (3.4.1), tensile properties (3.4.2), hardness (3.4.3), bending (3.4.4), and tolerances (3.6) are classified as acceptance tests and shall be performed on each heat or lot as applicable.