

AEROSPACE MATERIAL SPECIFICATION

SAE AMS5651

REV. J

Issued 1948-05
Revised 2003-01
Reaffirmed 2012-10

Superseding AMS5651H

Steel, Corrosion and Heat-Resistant, Bars, Wire, Forgings, Tubing, and Rings
25Cr - 20Ni (SAE 30310)
Solution Heat Treated
(Composition similar to UNS S31008)

RATIONALE

AMS5651J has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat-resistant steel in the form of bars, wire, forgings, mechanical tubing, flash welded rings, and stock for forging or flash welded rings.

1.2 Application:

These products have been used typically for parts requiring oxidation resistance up to 2000 °F (1093 °C) and good corrosion resistance, and for parts which will be subjected to elevated temperatures during fabrication or in service and especially where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5651J>**

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2241	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS 2243	Tolerances, Corrosion and Heat-Resistant Steel Tubing
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AMS 7490	Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels and Austenitic-Type Alloys, or Precipitation-Hardenable Alloys

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM A370	Mechanical Testing of Steel Products
ASTM E353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.30	0.80
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	24.00	26.00
Nickel	19.00	22.00
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Bars, Wire, Forgings, Mechanical Tubing, and Flash Welded Rings: Solution heat treated free from continuous carbide network.

3.2.1.1 Bars and Wire:

3.2.1.1.1 All hexagons, regardless of size, other bars 2.75 inches (69.8 mm) and under in nominal diameter or least distance between parallel sides, and wire shall be cold finished.

3.2.1.1.2 Bars over 2.75 inches (69.8 mm) in nominal diameter or least distance between parallel sides shall be hot finished and descaled, or cold finished.

3.2.1.2 Mechanical Tubing: Shall be cold finished.

3.2.1.3 Flash Welded Rings: Shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Properties:

The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A 370:

3.3.1 Tensile Properties: Wire shall have tensile strength not higher than 125 ksi (862 MPa).

3.3.2 Hardness:

3.3.2.1 Bars: Not higher than 187 HB, or equivalent (See 8.2), except that, if supplied cold finished, hardness may be as high as 229 HB, or equivalent (See 8.2), determined at approximately mid-radius or quarter-thickness.

3.3.2.2 Forgings and Flash Welded Rings: Not higher than 187 HB, or equivalent (See 8.2).

3.3.2.3 Mechanical Tubing: Not higher than 90 HRB, or equivalent (See 8.2), determined approximately midway between outer and inner surfaces.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.5 Tolerances:

Shall be as follows:

3.5.1 Bars and Wire: In accordance with AMS 2241.

3.5.2 Mechanical Tubing: In accordance with AMS 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile strength of wire (3.3.1), hardness (3.3.2), and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Grain flow of die forgings (3.4.1) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, and Stock for Forging or Flash Welded Rings: In accordance with AMS 2371.

4.3.2 Forgings: In accordance with AMS 2374.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the following results of tests and relevant information:

4.4.1 For each heat: Composition.