



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
485 LEXINGTON AVENUE, NEW YORK, N.Y. 10017

AMS6455C

Superseding AMS 6455B

Issued 12-4-39

Revised 5-1-68

## STEEL SHEET, STRIP, AND PLATE 0.95Cr - 0.22V (0.48 - 0.53C) (SAE 6150)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for parts requiring high hardness or spring properties.

3. COMPOSITION:

	min	max
Carbon	0.48	0.53
Manganese	0.70	0.90
Silicon	0.20	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Vanadium	0.15	0.30
Nickel	--	0.25
Copper	--	0.35

3.1 Check Analysis: Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Low Alloy Steels".

4. CONDITION: Unless otherwise specified, material shall be supplied cold rolled and bright annealed;  or hot rolled, annealed if necessary, and descaled.

5. TECHNICAL REQUIREMENTS: When ASTM methods are specified for determining conformance to the following requirements, tests shall be conducted in accordance with the issue of the ASTM method listed in the latest issue of AMS 2350.

5.1 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, ASTM E112,  McQuaid-Ehn test.

5.2 Decarburization:

5.2.1 Material Under 0.045 In. in Thickness: The method of test and the allowance shall be as agreed  upon by purchaser and vendor.

5.2.2 Material 0.045 In. and Over in Thickness:

5.2.2.1 Specimens: Shall be the full thickness of the material except that specimens from plate over  0.250 in. thick shall be slices approximately 0.250 in. thick cut parallel to and preserving one original surface of the plate. Recommended specimen size is 1 x 4 inches.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.2.2.2 Procedure: Specimens shall be hardened by austenitizing and quenching; preferably they shall not be tempered but, if tempered, the tempering temperature shall be not higher than 300 F (149 C). During heat treatment, specimens shall be protected by a suitable atmosphere or medium or by suitable plating to prevent carburization or further decarburization. Protective plating, if used, shall then be removed from specimens of material 0.045 to 0.250 in., excl, in thickness and a portion of the specimen shall be step ground to a depth of 0.050 in. or half thickness, whichever is less. Specimens from material 0.250 in. and over in thickness shall be ground to remove from the original surface of the plate the amount of metal shown below and a portion of the specimen shall be further ground to a depth of at least 1/3 the original thickness of the specimen. At least three Rockwell hardness readings shall be taken on each prepared step and each group of readings averaged.

Nominal Original Thickness Inches	Surface Depth Removal Inch
0.250 to 0.375, incl	0.020
Over 0.375 to 0.500, incl	0.025
Over 0.500 to 0.750, incl	0.030
Over 0.750 to 1.000, incl	0.035
Over 1.000 to 2.000, incl	0.040

5.2.2.3 Allowance:

5.2.2.3.1 Material 0.045 to 0.250 In., Excl, Thick: Unless otherwise specified, the product shall be free from complete decarburization. It shall also be free from partial decarburization to the extent that the difference in hardness between the surface and the non-decarburized depth below the surface shall be not greater than 2 points on the Rockwell A scale.

5.2.2.3.2 Material 0.250 In. and Over Thick: The difference in hardness between the two prepared steps shall be not greater than 2 points on the Rockwell C scale.

5.3 Bending: Material shall withstand, without cracking, bending at room temperature through the angle indicated below around a diameter equal to the nominal thickness of the material with axis of bend parallel to the direction of rolling.

Nominal Thickness Inch	Angle deg, min
Up to 0.249, incl	180
Over 0.249 to 0.749, incl	90

6. QUALITY: Steel shall be aircraft quality and shall conform to the latest issue of AMS 2301. The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2252; for strip, tolerances for cold finished shall apply.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition, grain size, and AMS 2301 frequency-severity rating of each heat in the shipment and a statement that the product conforms to the decarburization and bending requirements of this specification. This report shall include the purchase order number, heat number, material specification number and its revision letter, thickness, size, and quantity from each heat.