

# AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



**AMS 7295/9B**

Issued APR 1978  
Revised APR 1993  
Noncurrent JUL 1998

Superseding AMS 7295/9A

## Radiographic Paper 2.0-80

### NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of July 1998. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each "NONCURRENT" specification is available from SAE upon request.

SAENORM.COM : Click to view the full PDF of AMS 7295-9B

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1998 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

**QUESTIONS REGARDING THIS DOCUMENT:**  
**TO PLACE A DOCUMENT ORDER:**  
**SAE WEB ADDRESS:**

(724) 772-7154  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

**1. SCOPE:****1.1 Form:**

This specification covers one type of low-contrast, fine-grain radiographic paper in the form of cut sheets or rolls.

**1.2 Application:**

This paper will provide a radiographic quality level of 2-2T sensitivity when properly utilized (See AMS 7295).

**1.3 Classification:**

Low contrast with gradient of 2.0 to 2.4 and exhibiting resolution of 80 or more lines per millimeter.

**2. APPLICABLE DOCUMENTS:**

See AMS 7295.

**3. TECHNICAL REQUIREMENTS:****3.1 Basic Specification:**

The complete requirements for paper described herein and its procurement shall consist of this document and the latest issue of the basic specification, AMS 7295.

3.1.1 Definition: Properties shall be as defined in AMS 7295.

**3.2 Properties of Radiographic Paper:**

3.2.1 Thickness: Shall be not greater than 0.010 inch (0.25 mm).

3.2.2 Net Optical Density: Shall be not greater than 0.10 H&D units.

3.2.3 Gradient or Contrast: Shall be 2.0 to 2.4 at 0.4 to 1.2 H&D units.

3.2.4 Resolution: Shall be fine, showing at least 80 lines per millimeter.

**4. QUALITY ASSURANCE PROVISIONS:**

See AMS 7295.

**5. PREPARATION FOR DELIVERY:**

See AMS 7295.